

Important information

The tables "Chemical resistance of plastics", "Plastics and their properties" and "Viscosity of liquids" as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical resistance alone is not sufficient for the evaluation of the usability of a product. For example, the regulations concerning flammable liquids (explosion prevention) must also be taken into consideration.

Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that the information about the publisher is retained.

Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to info@buerkle.de. We would also like to receive translations into other languages. Please visit our website at www.buerkle.de from time to time and download the updated version of these lists.

Publisher

Bürkle GmbH
Rheinauen 5
D-79415 Bad Bellingen
Tel +49 (76 35) 8 27 95-0
Fax +49 (76 35) 8 27 95-31
info@buerkle.de
www.buerkle.de

Version 3.4 (24.03.2017)

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT																											
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE /ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM		NBR	SI	AL	V2A	V4A	Haselloy C																					
Acetaldehyde	C ₂ H ₄ O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	Acetic aldehyde; Ethanal; Ethyl aldehyde																					
Acetaldehyde	C ₂ H ₄ O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1																						
Acetamide	C ₂ H ₅ NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1																						
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1																						
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1																						
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1																						
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	1/1																							
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1																							
Acetic acid chloride	-> see: Acetyl chloride																																																			
Acetic acid sodium salt	-> see: Sodium acetate																																																			
Acetic aldehyde	-> see: Acetaldehyde																																																			
Acetic anhydride	C ₄ H ₆ O ₃	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1																						
Acetic chloride	-> see: Acetyl chloride																																																			
Acetone	C ₃ H ₆ O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone																				
Acetonitrile	C ₂ H ₃ N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	Methyl cyanide; Cyanomethane; Ethanenitrile																					
Acetonyl chloride	-> see: Chloroacetone																																																			
Acetophenone	C ₈ H ₈ O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene																					
Acetyl chloride	C ₂ H ₃ ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	Acetic chloride; Ethanoyl chloride; Acetic acid chloride																						
Acetylene	C ₂ H ₂	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	1/1	0/0	1/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	Ethine; Ethyne																						
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																																																			
Acetylsalicylic acid	C ₉ H ₈ O ₄	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;																					
Acrylonitrile	C ₃ H ₃ N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide																						
Adipic acid	C ₆ H ₁₀ O ₄	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	Hexanedioic acid; Butanedicarboxylic acid, 1,4-																					
Alanine, L-	C ₃ H ₇ NO ₂	000056-41-7				1/1	1/1	1/1	4/4	(2)	1/1	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		Aminopropanoic acid, L-2; aminopropanoic acid, alpha-																						
Allspice	ground																																																			
Allyl acetate	C ₅ H ₈ O ₂	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)																							
Allyl alcohol	C ₃ H ₆ O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	(2)	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	Vinyl carbinol; Propenyl alcohol																						
Allyl chloride	C ₃ H ₅ Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	4/4	4/4	0/0	(1)	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0	Chloro-1-propene, 3-; Chloropropylene, 3-																						
Allyl mustard oil	C ₈ H ₈ NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		oleum sinapis																						
Almond oil, sweet	008007-69-0																																																			
Alumina acidic	C ₂ H ₇ AlO ₃ x H ₂ O	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	1/0	1/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1	1/1	1/1	1/1																							
Aluminium fluoride	AlF ₃	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0																						
Aluminum ammonium sulfate dodecahydrate	(NH ₄) ₂ Al(SO ₄) ₂	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0																						
Aluminum chloride	AlCl ₃	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	0/0	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4	1/1																					
Aluminum chloride	AlCl ₃	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1																							
Aluminum chloride	AlCl ₃	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1																						
Aluminum hydroxide	Al(OH) ₃	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected																					
Aluminum nitrate	Al(NO ₃) ₃	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1																							
Aluminum oxide, alpha-	Al ₂ O ₃	001344-28-1	solid			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected																					
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	1/1	0/0																						
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0																							
Aluminum sodium sulfate	NaAl(SO ₄) ₂	010102-71-3		?		1/1	1/1	(3)	(2)	1/1	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)																							
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics														fluoroplastics		elastomers		metals		COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE /ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM		NBR	SI	AL	V2A	V4A	Haselloy C	
Ammonium chloride	(NH ₄)Cl	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac	
Ammonium chloride	(NH ₄)Cl	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac		
Ammonium difluoride	F ₂ H ₃ N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0			
Ammonium ferric sulfate	(NH ₄)Fe(SO ₄) ₂	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0			
Ammonium ferrous sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)				
Ammonium fluoride	(NH ₄)F	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?		
Ammonium fluoride	(NH ₄)F	012125-01-8	aqueous	T, C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1		
Ammonium glycolate	C ₂ H ₂ NO ₂	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		Acetic acid	
Ammonium heptamolybdate	(NH ₄) ₆ Mo ₇ O ₂₄	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(1)	(1)	0/0			
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	2/3	1/2	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	1/1		
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1		
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1		
Ammonium mercaptan	-> see: Ammonium bisulfide																															
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1		Nitric acid; Ammonium salt
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1		
Ammonium nitrite	(NH ₄)NO ₂	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(3)	1/0	0/0	(2)	(1)	(1)				
Ammonium oxalate	C ₂ H ₂ N ₂ O ₄	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0		
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0		
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0		
Ammonium phosphate, Mono-	(NH ₄)H ₂ PO ₄	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1		
Ammonium polyphosphate (APP)	(NH ₄ PO ₃) _n	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)			
Ammonium rhodanide	-> see: Ammonium thiocyanate																															
Ammonium salt	-> see: Ammonium nitrate																															
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1		
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1		
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	Diammonium sulfide;	
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1		
Ammonium sulfocyanide	-> see: Ammonium thiocyanate																															
Ammonium thiocyanate	CH ₃ N ₂ S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		Ammonium sulfocyanide; Ammonium rhodanide; Thiocyanic acid, Ammonium salt; Ammonium sulfocyanate	
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)			
Amyl acetate, normal	C ₇ H ₁₄ O ₂	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0		
Amyl alcohol, n-	-> see: Pentanol, 1-																															
Amyl chloride	C ₅ H ₁₁ Cl	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0		
Amyl cinnamic aldehyde	C ₁₄ H ₁₆ O	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		odoriferous substance	
Aniline	C ₆ H ₅ N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1			
Aniline hydrochloride	C ₆ H ₅ ClN	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4			
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)			
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	0/0			
Anisole	C ₇ H ₈ O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0		
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1		glycol-water-mixture		
Antimony pentachloride	SbCl ₅	007647-18-9		C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0				
Antimony trichloride	SbCl ₃	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0		

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics											fluoroplastics		elastomers		metals		COMMENT								
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE /ETFE	FEP	PTFE		PVDF	EPDM	FPM /FKM	NBR	SI	AL	V2A	V4A
Magnesium bromide	MgBr ₂	007789-48-2		Xi		1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(1)	(2)	0/0	(3)	0/0	0/0		
Magnesium carbonate	MgCO ₃	000546-93-0	saturated	—		1/1	1/1	1/0	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Magnesium chloride	MgCl ₂	007786-30-3	aqueous	Xi		1/1	1/1	1/0	1/0	1/0	1/2	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0L	1/0L	
Magnesium chlorite	Mg(ClO ₂) ₂	??		O		0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	0/0	0/0	0/0		
Magnesium hydroxide	Mg(OH) ₂	001309-42-8	saturated	—		1/1	1/1	1/0	(2)	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	1/1	1/1	1/1	0/0	
Magnesium iodide	MgI ₂	010377-58-9		(Xn)		1/1	1/1	(2)	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/1	(1)	(2)	0/0	(2)	0/0	0/0		
Magnesium nitrate	Mg(NO ₃) ₂	010377-60-3	saturated	O, Xi		1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(2)	0/0	1/0	1/0	1/0	1/1	
Magnesiumsulfat	MgSO ₄	007487-88-9	each	—		1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	2/0	0/0	1/1	1/1	1/1	
Maize-germ oil	—	008001-30-7	techn. pure	—		1/3	0/0	(2)	(1)	1/0	0/0	(2)	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1	
Maleic acid	C ₄ H ₂ O ₄	000110-16-7	saturated	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	
Maleic acid	C ₄ H ₂ O ₄	000110-16-7	aqueous	Xn		1/1	1/1	4/4	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	1/0	0/0	1/1	1/1	1/1	1/1	
Margarine	—	—		—		0/0	0/0	(2)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Menthol	C ₁₀ H ₂₀ O	000089-78-1	solid	Xi		1/3	3/4	3/0	3/4	0/0	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	(1)	1/0	1/0	
Mercuric chloride	HgCl ₂	007487-94-7	aqueous	T+, C		1/1	1/1	4/4	1/0	(2)	1/1	3/0	1/1	1/3	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	4/4	(4)	(4)	1/1	
Mercuric cyanide	C ₂ HgN ₂	000592-04-1	saturated	T+		1/1	1/1	(3)	(2)	(0)	3/0	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	(1)	1/1	(2)	0/0	4/4	1/0	4/4	1/0	1/1	
Mercuric nitrate	Hg(NO ₃) ₂	010045-94-0	saturated	(T+)		1/1	1/1	1/0	(2)	(0)	3/0	1/1	1/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/0	1/1	1/3	0/0	4/4	1/1	1/1	1/1		
Mercury	Hg	007439-97-6	pure	T		1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(3)	1/1	1/1	1/1	1/1	
Mesityl oxide	C ₉ H ₁₀ O	000141-79-7		Xn	X	0/0	0/0	(2)	(4)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	0/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methacetone	—	—		-> see: Pentanone, 3-																										
Methacrylic acid	C ₄ H ₆ O ₂	000079-41-4		C		1/0	1/1	4/4	4/4	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	3/0	4/4	4/4	0/0	(4)	0/0	0/0	
Methane	CH ₄	000074-82-8	techn. pure	F+	X	1/0	0/0	1/0	1/0	1/0	0/0	1/0	1/0	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1	0/0
Methanoic acid	—	—		-> see: Formic acid																										
Methenamine	—	—		-> see: Hexamethylenetetramine																										
Methoxy butanol	C ₈ H ₁₈ O ₂	—	100 %	?	X	0/0	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	3/0	1/0	1/0	0/0	(1)	(1)	(1)	isomer not indicated in the source	
Methoxyethane	C ₃ H ₈ O	000540-67-0	100 %	(F+)	X	0/0	3/0	(1)	(4)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	1/0	(2)	4/4	4/4	4/4	0/0	1/1	(1)	(1)	Methyl ethyl ether;	
Methoxyethyl oleate	—	—		-> see: Ethylene glycol monomethyl ether oleate																										
Methyl acetate	C ₄ H ₈ O ₂	000079-20-9	techn. pure	F, Xn	X	1/0	1/1	1/0	4/4	3/0	(4)	2/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	(1)	1/1	1/1	0/0
Methyl acrylate	C ₅ H ₈ O ₂	000096-33-3		F, Xn	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(2)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl alcohol	CH ₃ O	000067-56-1		F, T	X	1/1	1/1	2/0	4/4	1/0	1/1	1/1	1/1	3/4	3/3	1/3	3/3	3/4	1/1	1/1	1/1	1/1	1/0	3/4	3/3	0/0	1/0	1/1	1/1	
Methyl amine	CH ₅ N	000074-89-5	32 %	F+, C	X	1/0	1/0	4/4	4/4	0/0	0/0	1/0	1/0	0/0	0/0	3/0	4/4	0/0	(1)	1/0	3/0	1/0	4/4	4/4	0/0	1/0	1/0	0/0	0/0	
Methyl benzene	C ₆ H ₆	000108-88-3		F, Xn	X	3/4	3/4	1/0	4/4	1/0	3/3	1/3	3/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/4	4/4	0/0	1/1	1/1	1/1	1/1	
Methyl bromide	CH ₃ Br	000074-83-9	techn. pure	T		3/0	4/4	1/0	(3)	0/0	0/0	1/0	4/4	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0
Methyl butanol	C ₈ H ₁₈ O	—		Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	1/0	1/0	0/0	0/0	1/3	0/0	(1)	1/1	1/1	3/0	2/2	3/3	0/0	(1)	(1)	(1)	isomer not indicated in the source		
Methyl butyl ketone	C ₈ H ₁₆ O	000591-78-6		F, T	X	0/0	0/0	(2)	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)			
Methyl cellosolveat oleate	—	—		-> see: Ethylene glycol monomethyl ether oleate																										
Methyl chloride	CH ₂ Cl	000074-87-3	techn. pure	F+, T	X	3/0	2/0	4/4	(3)	0/0	0/0	1/0	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/0	1/0	1/1	4/4	4/4	4/4	0/0	4/4	1/1L	1/1L	
Methyl cyanide	—	—		-> see: Acetonitrile																										
Methyl dichloroacetate	C ₂ H ₂ Cl ₂ O ₂	000116-54-1		(Xn)		1/1	0/0	(3)	(4)	(4)	(3)	1/1	0/0	0/0	4/4	0/0	0/0	(1)	1/1	3/3	4/4	4/4	4/4	0/0	(3)	0/0	0/0			
Methyl ethyl carbinol	—	—		-> see: Butyl alcohol, sec-																										
Methyl ethyl ether	—	—		-> see: Methoxyethane																										
Methyl ethyl ketone (MEK)	C ₆ H ₁₀ O	000078-93-3		F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/2	1/3	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	3/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0
Methyl ethylene oxide	—	—		-> see: Propylene oxid																										
Methyl formate	C ₂ H ₄ O ₂	000107-31-3		F+	X	0/0	0/0	(2)	4/4	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0	
Methyl isobutyl ketone	C ₈ H ₁₆ O	000108-10-1		F	X	1/2	2/3	1/0	4/4	(4)	3/3	(2)	2/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	0/0
Methyl isopropyl ketone	C ₇ H ₁₄ O	000563-80-4		F	X	0/0	0/0	(2)	4/4	(4)	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	
Methyl ketone	—	—		-> see: Acetone																										
Methyl methacrylate	C ₅ H ₈ O ₂	000080-62-6	100 %	F, Xi	X	0																								

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroelastomers		elastomers		metals		COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM		FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C
Molasses	—	—	—	—	1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)			
Molasses wort	—	—	—	?	1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)			
Monochlorobenzene (MCB)	—	—	-> see: Chlorobenzene	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—		
Monochloroethane	C ₂ H ₅ Cl	000075-00-3	—	F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	1/1L	1/1L	0/0	Ethyl chloride; Chloroethane, 1-
Morpholine	C ₄ H ₉ NO	000110-91-8	techn. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0		
Motor oil	—	—	—	?	?	0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1			
Mowilith D	—	—	—	?	?	1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	dispersion of polyvinyl acetate; Clariant	
Muscat	—	—	ground	?	?	0/0	0/0	(2)	4/4	(2)	0/0	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)			
Mustard	—	—	—	—	—	0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L			
Naphtha	—	008032-32-4	—	(Xn)	—	1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	petroleum ether	
Naphthalene	C ₁₀ H ₈	000091-20-3	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	—	—	—	F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	(3)	0/0	(1)	(1)	(1)	0/0	
Neon	Ne	007440-01-9	—	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1			
Nickel acetate	C ₄ H ₇ NO ₄	000373-02-4	aqueous	(T, N)	—	1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0		
Nickel dichloride	NiCl ₂	007718-54-9	saturated	T	—	1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel dichloride	NiCl ₂	007718-54-9	aqueous	T	—	1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	saturated	Xn	—	1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	aqueous	Xn	—	1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickelous nitrate	Ni(NO ₃) ₂	013138-45-9	saturated	(O, Xn)	—	1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/0	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nicotine	C ₁₀ H ₁₄ N ₂	000054-11-5	—	T+	—	1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0		
Nicotinic acid	C ₆ H ₇ NO ₂	000059-67-6	diluted	Xi	—	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitric acid	HNO ₃	007697-37-2	1-10 %	C	—	1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1		
Nitric acid	HNO ₃	007697-37-2	50 %	C+	—	2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO ₃	007697-37-2	66 %	C+	—	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO ₃	007697-37-2	100 %	O, C+	—	4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO ₃	007697-37-2	70 %	O, C+	—	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	—	—	-> see: Ammonium nitrate	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitric acid, magnesium salt	—	—	-> see: Magnesium nitrate	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitric acid, potassium salt	—	—	-> see: Potassium nitrate	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitro benzoic acid	C ₇ H ₅ NO ₄	—	—	(Xn)	—	1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		isomer not indicated in the source
Nitro reducer	—	—	—	?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		solvent cleaner mixture	
Nitrobenzene	C ₆ H ₅ NO ₂	000098-95-3	—	T	—	3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitroethane	C ₂ H ₅ NO ₂	000079-24-3	—	Xn	X	0/0	0/0	(3)	(4)	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)			
Nitrogen	N ₂	007727-37-9	—	—	—	0/0	0/0	1/0	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1			
Nitrogen hydride	—	—	-> see: Hydrazine	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitrogen tetroxide	N ₂ O ₄	010544-72-6	—	(O), T+, C	—	0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)			
Nitroglycerine	C ₃ H ₅ (NO ₃) ₃	000055-63-0	diluted	(E, T+)	—	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0		
Nitrohydrochloric acid	HNO ₃ + HCl	008007-56-5	—	C	—	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	4/4	0/0	4/4	4/4	4/4	4/4		aquea regia: mixture of hydrochloric acid and nitric acid
Nitropropane	C ₃ H ₇ NO ₂	—	—	(T)	—	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)	(1)		isomer not indicated in the source	
Nitroses gases	—	—	diluted	T	—	1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	nitrogen monoxide + nitrogen dioxide	
Nitrotoluene	C ₇ H ₇ NO ₂	001321-12-6	techn. pure	T	—	1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1	1/1	
Nitrous acid, sodium salt	—	—	-> see: Sodium nitrite	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Nitrous oxide	N ₂ O	010024-97-2	—	(O)	—	0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics		elastomers		metals		COMMENT						
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM		FPM / FKM	NBR	SI	AL	V2A	V4A
Oxalic acid	C ₂ H ₂ O ₄ x 2H ₂ O	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3	
Oxygen	O ₂	007782-44-7	techn. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0
Ozone	O ₃	010028-15-6		(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0
Ozone-air-mixture	—	—		(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0
Palm kernel oil	—	008023-79-8		—		0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1	1/1
Palm oil	—	008002-75-3		—		1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1
Palmitic acid	C ₁₆ H ₃₂ O ₂	000057-10-3	techn. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1
Paraffin wax	—	008002-74-2		—		0	0	0	(2)	0	0	(2)	(2)	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1	1	1
Paraffin-emulsion	—	—		?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0	
Paraffins	C _n H _{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1
Paraformaldehyde	(CH ₂ O) _n H ₂ O	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)	(1)	0/0
Peanut oil	—	008002-03-7		—		0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0	0/0
Pectin	—	009000-69-5	aqueous	—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1
Pectin	—	009000-69-5		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1
Pelargonic alcohol	-> see: Nonyl alcohol	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	antibiotic
Pentachlorobiphenyl	C ₁₂ H ₂ Cl ₅	—		Xn		0/0	0/0	1/0	(3)	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0	0/0	0/0	0/0
Pentamethyleneimine	-> see: Piperidine	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Pentane, normal	C ₅ H ₁₂	000109-66-0		F	X	1/3	1/3	1/0	1/0	(1)	(3)	1/0	(3)	3/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1	1/1	1/1
Pentanethiol, 1-	C ₅ H ₁₂ S	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)	0/0
Pentanol, 1-	C ₅ H ₁₂ O	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	0/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0
Pentanone, 3-	C ₅ H ₁₀ O	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	3/0	0/4	2/3	1/1	(1)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0	0/0
Pentyl alcohol, n-	-> see: Pentanol, 1-	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Pepper	—	—	ground	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	0/0
Perchloric acid	HClO ₄	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?
Perchloric acid	HClO ₄	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1
Perchlorobutadiene	C ₄ Cl ₆	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0	0/0	0/0
Perchloroethylene	-> see: Tetrachloroethylene	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Perfluorocyclobutane	C ₄ F ₈	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)	0/0
Permanganic acid, potassium salt	-> see: Potassium permanganate	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0
Petroleum ether	—	008032-32-4	techn. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1
Phenacetin	C ₁₀ H ₁₃ NO ₂	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0
Phenethyl alcohol	C ₈ H ₁₀ O	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)	0/0
Phenetole	-> see: Ethoxybenzene	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Phenol	C ₆ H ₆ O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0
Phenol	C ₆ H ₆ O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0
Phenolic resin mass	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0
Phenyl chloride	-> see: Chlorobenzene	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Phenyl methyl ketone	-> see: Acetophenone	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Phenylethanone, 1-	-> see: Acetophenone	—		—		—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Phenyldiazine	C ₆ H ₈ N ₂	000100-63-0	techn. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0
Phenyldiazine hydrochloride	C ₆ H ₈ N ₂ -HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)	0/0
Phenylsulfonate	—	070528-83-5		?		0/0																								

CHEMICALS	thermoplastics										fluoroplastics			elastomers			metals			COMMENT										
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE		FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A
Pineapple juice	—	—	—	—	1/1	1/1	1/0	(2)	1/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	(1)	0/0
Pink	—	—	ground	?	0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	(1)	0/0
Piperidine	C ₅ H ₁₁ N	000110-89-4	—	F, T, C	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	(1)	0/0
Plasticiser	—	—	—	?	1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)	(1)	0/0
Polish remover	—	—	—	?	(X)	0/0	0/0	(2)	4/4	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	(1)	0/0
Polyester resins	—	—	—	(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)	(1)	0/0
Polyethylene glycol	HO-(C ₂ H ₄ O) _n -H	025322-68-3	100 %	(—)	1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	(1)	0/0
Polyoxymethylene	—	—	—	-> see: Paraformaldehyde	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—
Polyran M25 N	—	—	80°C	?	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	3	0	0	(1)	(1)	(1)	lubricating oil
Polyran M400	—	—	80°C	?	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0/0	0	0	0/0	0	0	0	(1)	(1)	(1)	(1)	lubricating oil
Polysolvan O	C ₈ H ₁₀ O ₂	007397-62-8	100 %	Xi	0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)	(1)	solvent cleaner, butyl glycolate; Celanese AG
Potassium acetate	C ₂ H ₃ KO ₂	000127-08-2	aqueous	Xi	1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	1/0	1/0	0/0	1/1	1/1	1/0	1/1	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0	
Potassium bisulfate	KHSO ₄	007646-93-7	aqueous	(C)	1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	4/4	4/4	1/1	
Potassium bisulfate	KHSO ₄	007646-93-7	—	C	1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/0	4/4	4/4	?	
Potassium bitartrate	C ₄ H ₄ KO ₆	000868-14-4	saturated	Xi	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0	(4)	1/3	1/2	0/0	
Potassium borate	KBO ₂	012228-88-5	10 %	(Xn)	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	(3)	0/0	0/0	0/0	
Potassium borate	KBO ₂	012228-88-5	aqueous	(Xn)	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	1/0	1/0	1/0	1/0	(3)	0/0	0/0	0/0		
Potassium bromate	KBrO ₃	007758-01-2	saturated	O, T	1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromate	KBrO ₃	007758-01-2	aqueous	O, T	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0	
Potassium bromide	KBr	007758-02-3	each	Xn	1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	0/0	1/3	1/0	1/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	0/0	1/0	1/0L	1/0L	1/1	
Potassium carbonate	K ₂ CO ₃	000584-08-7	saturated	Xn	1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/0	1/0	0/0	4/4	1/1	1/1	1/1	
Potassium carbonate	K ₂ CO ₃	000584-08-7	aqueous	Xn	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/0	1/0	4/4	1/1	1/1	1/1	
Potassium chlorate	KClO ₃	003811-04-9	saturated	O, Xn	1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	1/1	
Potassium chlorate	KClO ₃	003811-04-9	aqueous	O, Xn	1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1	1/1	
Potassium chloride	KCl	007447-40-7	aqueous	Xi	1/1	1/1	1/0	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1	
Potassium chromate	K ₂ CrO ₄	007789-00-6	saturated	T	1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1	
Potassium chromate	K ₂ CrO ₄	007789-00-6	aqueous	T	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1		
Potassium cyanide	KCN	000151-50-8	saturated	T+	1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium cyanide	KCN	000151-50-8	aqueous	T+	1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1	
Potassium dichromate	K ₂ Cr ₂ O ₇	007778-50-9	saturated	T	1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium dichromate	K ₂ Cr ₂ O ₇	007778-50-9	aqueous	T	0/0	0/0	3/0	1/0	3/0	1/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1	
Potassium ferricyanide	C ₆ FeK ₃ N ₆	013746-66-2	each	Xn	1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1	
Potassium ferrocyanide	C ₆ FeK ₃ N ₆ x 3H ₂ O	014459-95-1	saturated	—	1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1	1/1		
Potassium ferrocyanide	C ₆ FeK ₃ N ₆ x 3H ₂ O	014459-95-1	diluted	—	1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1		
Potassium fluoride	KF	007789-23-3	—	T	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0	
Potassium hydrogen carbonate	CHKO ₃	000298-14-6	saturated	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	4/4	(1)	(1)	1/1	
Potassium hydroxide	KHO	001310-58-3	10 %	C+	1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	30 %	C+	1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1		
Potassium hydroxide	KHO	001310-58-3	50 %	C+	1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	concentrated	C+	1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/2	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1	
Potassium hydroxide	KHO	001310-58-3	1 %	Xi	1/1	1/1	1/0	3/4	(4)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/3	3/3	0/0	4/4	1/1	1/1	1/1		
Potassium hypochlorite	KClO	007778-66-7	diluted	(O, C)	1/0	1/3	3/0	(3)	(3)	1/0	4/4	1/3	3/0	1/0	1/0	0/0	0/0	(1)	1/1	1/1	3/0	1/0	3/3	0/0	4/4	3/3L	2/2L	1/1		
Potassium iodate	K ₂ IO ₃	007758-05-6	—	O	0/0	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/0	1/1	(1)	(1)	(2)	0/0	1/1	1/1	1/1	0/0	

CHEMICALS	thermoplastics														fluoroelastomers		elastomers		metals		COMMENT												
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP		PTFE	PVDF	EPDM	FPM /FKM	NBR	SI	AL	V2A	V4A	Haselloy C		
Spindle oil	—	—	?	?	3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Spinning bath acid	—	—	100mg CS ₂ /l	?	1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0					
Spirit (of wine)	C ₂ H ₆ O	—	—	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1		ethyl alcohol	
Spirits	C ₂ H ₆ O	—	—	—	—	1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0		ethyl alcohol 40 %		
Spirits of Turpentine	—	008006-64-2	—	Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	1/1		
Spirits of wine	C ₂ H ₆ O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	1/1		ethyl alcohol
Spirits of wine	C ₂ H ₆ O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	1/1		ethyl alcohol
Spruce oil	—	008008-80-8	—	?	?	1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	3/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)			pinus sylvestris	
Stannic chloride	SnCl ₄	007646-78-8	aqueous	C	1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4					
Stannous chloride	SnCl ₂	007772-99-8	aqueous	(C, Xn)	1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	0/0	4/4	4/4	3/4	1/1			
Stannous chloride	SnCl ₂	007772-99-8	saturated	C, Xn	1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1				
Starch solution	(C ₆ H ₁₀ O ₅) _n	—	each	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	0/0	
Starch syrup	—	—	—	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	0/0	
Stauferr grease, thick	—	—	—	(—)	0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	1/1	1/1	1/1	0/0	
Steam	H ₂ O	—	up to 150°C	?	4	4	4/4	0/0	0	(3)	(3)	0	0	0	0	0	0	0	0	0	0	1	0	3	4/4	0	(1)	1/1	1/1				
Stearic acid	C ₁₈ H ₃₆ O ₂	000057-11-4	crystals	Xi	1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1		
Srtrontium bromide	SrBr ₂	010476-81-0	—	Xi	1/1	1/1	(2)	(1)	0/0	(1)	0/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0					
Strychnine	C ₂₂ H ₂₂ N ₂ O ₂	000057-24-9	—	T+	1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)				
Styrene	C ₈ H ₈	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0			
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	50 %	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1					
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	saturated	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?				
Sugar acid	—	—	saturated	(Xi)	1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0					
Sugar beet juice	—	—	—	—	1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)					
Sugar syrup	—	—	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Sulfur	S ₈	007704-34-9	techn. pure	Xi	1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	1/1	1/1	1/1	flower of sulfur
Sulfur (mono)chloride	S ₂ Cl ₂	010025-67-9	—	C	0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	1/1L	1/1L	0/0					
Sulfur dioxide	SO ₂	007446-09-5	damp	T, C	1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/1	1/1	1/1	1/1	with H2O->sulfurous acid
Sulfur dioxide	SO ₂	007446-09-5	liquid	T, C	3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0			with H2O->sulfurous acid	
Sulfur hexafluoride	SF ₆	002551-62-4	—	—	0/0	0/0	1/0	(2)	1/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	1/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)					
Sulfur trioxide	SO ₃	007446-11-9	—	C+	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	4/4	0/0	4/4	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0					
Sulfur, melted, 121 °C	S ₈	007704-34-9	?	?	0	0	(4)	(3)	0	4	4	4	0	0	0	0	0	0	0	0	0	4	1	4	0	0	3	1	1	0/0			
Sulfuric acid	H ₂ SO ₄	007664-93-9	40 %	C+	1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0				
Sulfuric acid	H ₂ SO ₄	007664-93-9	60 %	C+	1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0				
Sulfuric acid	H ₂ SO ₄	007664-93-9	80 %	C+	1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0				
Sulfuric acid	H ₂ SO ₄	007664-93-9	95 %	C+	3/4	3/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0				
Sulfuric acid	H ₂ SO ₄	007664-93-9	fuming	C+	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0				oleum
Sulfuric acid	H ₂ SO ₄	007664-93-9	1-6 %	Xi	1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0				
Sulfuric acid	H ₂ SO ₄	007664-93-9	20 %	Xi	1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3					
Sulfuric acid	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	
Sulfurous acid	H ₂ SO ₃	007782-99-2	saturated	(C)	1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1	1/1	1/1	1/1	
Sulfurous acid, disodium salt	—	—</																															

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics			elastomers			metals		COMMENT										
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A	Haselloy C					
Wines	—	—	—	—	1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1		
Wort for fermentation	—	—	—	?	1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1				
Xenon	Xe	007440-63-3	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1					
Xylene	C ₈ H ₁₀	001330-20-7	—	(F), Xn X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	1/1						
Yeast	—	—	each	—	1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)							
Zinc acetate	C ₄ H ₆ ZnO ₄	000557-34-6	aqueous	Xn, Xi	1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)								
Zinc bromide	ZnBr ₂	007899-45-8	—	C, Xn	1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0								
Zinc carbonate	ZnCO ₃	003486-35-9	saturated	?	1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)						0/0	small solubility - no chemical effect expected
Zinc chloride	ZnCl ₂	007646-85-7	aqueous	(C, Xn)	1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1							
Zinc nitrate	Zn(NO ₃) ₂	007779-88-6	—	O, C, Xn	1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)								
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	1/1						small solubility - no chemical effect expected
Zinc oxide ointment	—	—	—	?	0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)								
Zinc phosphate	Zn ₃ (PO ₄) ₂	007779-90-0	saturated	?	1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)						0/0
Zinc sludge	—	—	—	?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0								
Zinc stearate	C ₃₆ H ₇₀ ZnO ₄	000557-05-1	—	Xi	1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)									
Zinc sulfate	ZnSO ₄	007733-02-0	10 %	—	1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1	1/1							
Zinkchlorid	ZnCl ₂	007646-85-7	10 %	C, Xn	1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1						

Two values are given per substance
left number = value at +20°C / right number = value at +50°C.

0	no data available
1	resistant
2	practically resistant
3	partially resistant
4	not resistant
K	no general information available
L	danger of pitting or stress-cracking corrosion
()	estimated value
E	explosive
O	oxidizing
F	highly flammable
F+	extremely flammable
T	toxic
T+	very toxic
C	corrosive
Xn	harmful
Xi	irritant
N	dangerous for the environment

Thermoplastics

HDPE	Polyethylene (high density)
LDPE	Polyethylene (low density)
PA	Polyamide (Nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (PET copolymer)
PMP	Polymethylpentene (TPX)
POM	Polyoxymethylene, polyacetal
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene-acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene-tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon, FEP)
PTFE	Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene-propylene-diene rubber
FPM/FKM	Fluorinated rubber (Viton)
NBR	Acryl-nitrile-butadiene rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy