

Important information

The tables "Chemical resistance of plastics", "Plastics and their properties" and "Viscosity of liquids" as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical resistance alone is not sufficient for the evaluation of the usability of a product. For example, the regulations concerning flammable liquids (explosion prevention) must also be taken into consideration.

Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that the information about the publisher is retained.

Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to info@buerkle.de. We would also like to receive translations into other languages. Please visit our website at www.buerkle.de from time to time and download the updated version of these lists.

Publisher

Bürkle GmbH
Rheinauen 5
D-79415 Bad Bellingen
Tel +49 (76 35) 8 27 95-0
Fax +49 (76 35) 8 27 95-31
info@buerkle.de
www.buerkle.de

Version 3.6 (15.12.2017)

CHEMICALS	thermoplastics												fluoroplastics				elastomers			metals				COMMENT								
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM		FPM /FKM	NBR	SI	AL	V2A	V4A	Haselloy C	
Acetaldehyde	C ₂ H ₄ O	000075-07-0	40 %	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	3/4	Acetic aldehyde; Ethanal; Ethyl aldehyde
Acetaldehyde	C ₂ H ₄ O	000075-07-0	techn. pure	F+, Xn	X	3/3	2/4	2/0	4/4	(4)	2/4	2/0	3/4	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	4/4	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1		
Acetamide	C ₂ H ₅ NO	000060-35-5	saturated	Xn		1/1	1/1	1/0	4/4	0/0	1/1	1/0	1/1	1/1	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	1/0	0/0	(1)	(1)	(1)	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	50 %	C		1/1	1/1	4/4	1/2	0/0	1/1	3/4	1/1	2/2	2/2	1/2	0/0	0/0	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/1	1/1	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	100 %	C+	X	0/0	0/0	4/4	4/4	4/4	(3)	4/4	1/3	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	90%	C+	X	1/1	1/2	4/4	4/4	4/4	1/3	4/4	1/2	4/4	3/4	1/2	4/4	4/4	1/1	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/3	1/2	1/2	1/1		
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	10 %	Xi		1/1	1/1	4/4	1/2	1/1	3/0	1/4	1/1	1/0	1/3	1/0	1/3	1/1	1/1	1/1	(2)	(3)	3/3	0/0	1/3	1/1	1/1	1/1	1/1			
Acetic acid	C ₂ H ₄ O ₂	000064-19-7	5 %	Xi		1/1	1/3	4/4	1/2	1/1	1/1	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	3/3	0/0	1/3	1/2	1/1	1/1			
Acetic acid chloride	-> see: Acetyl chloride																															
Acetic acid sodium salt	-> see: Sodium acetate																															
Acetic aldehyde	-> see: Acetaldehyde																															
Acetic anhydride	C ₂ H ₄ O ₃	000108-24-7	techn. pure	C	X	4/4	3/3	3/3	4/4	0/0	4/4	(2)	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	4/4	3/0	4/4	4/4	0/0	(2)	1/1	1/1	1/1		
Acetic chloride	-> see: Acetyl chloride																															
Acetone	C ₂ H ₆ O	000067-64-1		F, Xi	X	1/1	3/3	1/0	4/4	4/4	2/3	1/3	1/3	4/4	4/4	4/4	0/0	4/4	2/3	(1)	1/1	3/4	1/0	4/4	4/4	0/0	1/1	1/1	1/1	1/1	1/1	Propanone, 2-; Dimethyl ketone; Methyl ketone
Acetonitrile	C ₂ H ₃ N	000075-05-8		F, T	X	1/1	1/1	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	0/0	0/0	1/1	(1)	(1)	1/1	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	Methyl cyanide; Cyanomethane; Ethanenitrile	
Acetonyl chloride	-> see: Chloroacetone																															
Acetophenone	C ₈ H ₈ O	000098-86-2		Xn		0/0	1/0	1/0	(4)	(4)	(4)	1/0	1/3	0/4	0/0	4/4	4/4	0/4	1/1	0/0	1/1	1/3	1/0	4/4	4/4	0/0	1/1	(1)	(1)	0/0	Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene	
Acetyl chloride	C ₂ H ₃ ClO	000075-36-5	100 %	F, C	X	0/0	0/0	4/4	4/4	(4)	4/4	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	4/4	1/2L	1/1L	0/0	Acetic chloride; Ethanoyl chloride; Acetic acid chloride		
Acetylene	C ₂ H ₂	000074-86-2	100 %	F+	X	1/0	1/0	1/0	1/0	0/0	1/0	0/0	0/0	0/0	2/0	4/4	3/0	(1)	1/1	1/0	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	1/1	Ethine; Ethyne		
Acetyloxybenzoic acid, 2-	-> see: Acetylsalicylic acid																															
Acetylsalicylic acid	C ₉ H ₈ O ₄	000050-78-2	100 %	Xn		0/0	0/0	1/0	0/0	(2)	0/0	(3)	1/2	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/2	(2)	(3)	0/0	0/0	1/0	1/0	1/0	Acetyloxybenzoic acid, 2-;	
Acrylonitrile	C ₃ H ₃ N	000107-13-1		F, T	X	1/1	1/3	1/0	4/4	(4)	3/4	(3)	3/4	4/4	4/4	4/4	4/4	0/0	1/2	1/1	1/0	3/3	4/4	4/4	4/4	0/0	1/0	1/0	1/0	1/1	Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide	
Adipic acid	C ₆ H ₁₀ O ₄	000124-04-9	saturated	Xi		1/1	1/2	0/0	1/1	(2)	1/1	1/3	1/1	1/1	2/2	1/3	1/3	0/0	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	1/0	(2)	(2)	1/1	Hexanedioic acid; Butanedicarboxylic acid, 1,4-	
Alanine, L-	C ₃ H ₇ NO ₂	000056-41-7				1/1	1/1	1/1	4/4	(2)	1/1	1/1	1/1	4/4	4/4	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(2)	(2)	(2)		Aminopropanoic acid, L-2; aminopropanoic acid, alpha-		
Allspice	ground ?																															
Allyl acetate	C ₆ H ₁₀ O ₂	000591-87-7	100 %	F, T	X	0/0	1/3	4/4	4/4	(4)	(4)	(2)	1/3	4/4	0/0	0/0	4/4	0/0	0/0	(1)	1/1	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)			
Allyl alcohol	C ₃ H ₆ O	000107-18-6	96 %	F, T	X	1/3	3/3	3/0	3/3	1/0	1/2	(2)	2/2	2/4	2/3	2/3	4/4	4/4	1/1	1/1	(1)	2/0	1/0	4/4	3/0	0/0	1/1	1/1	1/1	1/1	Vinyl carbinol; Propenyl alcohol	
Allyl chloride	C ₃ H ₅ Cl	000107-05-1	100 %	F, T+	X	(3)	3/4	0/0	(4)	(4)	(4)	(2)	4/4	0/0	4/4	4/4	0/0	(1)	(2)	1/1	4/4	(3)	4/4	0/0	1/0	(1L)	(1L)	0/0		Chloro-1-propene, 3-; Chloropropylene, 3-		
Allyl mustard oil	C ₈ H ₁₄ NS	000057-06-7		T	X	0/0	0/0	0/0	(4)	(3)	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)		oleum sinapis	
Almond oil, sweet	008007-69-0																															
Alumina acidic	C ₂ H ₇ AlO ₅ x H ₂ O	000142-03-0	saturated	Xi		1/1	1/0	(2)	(2)	0/0	1/0	1/0	0/0	1/0	1/0	1/1	1/1	1/1	(1)	1/0	4/4	3/3	0/0	(1)	1/1	1/1	1/1	1/1	1/1	1/1		
Aluminium fluoride	AlF ₃	007789-18-1	aqueous	Xi		1/1	1/1	(3)	(2)	(2)	1/1	3/4	1/1	0/0	0/0	1/3	1/3	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	0/0		
Aluminum ammonium sulfate dodecahydrate	(NH ₄) ₂ Al(SO ₄) ₂	007784-26-1	saturated	Xi		1/1	1/1	3/4	(2)	(2)	0/0	3/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	1/1	0/0	1/0	1/2	1/3	0/0		
Aluminum chloride	AlCl ₃	007784-13-6	10 %	?		1/1	1/2	1/0	1/0	(2)	1/1	3/4	1/1	0/0	1/1	0/0	1/1	0/0	1/1	2/2	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4	1/1	
Aluminum chloride	AlCl ₃	007784-13-6	solid	C		1/1	1/1	3/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(3)	(3)	(3)	(3)	0/0	4/4	4/4	3/4	1/1		
Aluminum chloride	AlCl ₃	007784-13-6	saturated	C		1/1	1/1	3/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	(1)	1/1	(2)	1/0	1/1	0/0	4/4	4/4	3/4	1/1		
Aluminum hydroxide	Al(OH) ₃	021645-51-2		Xi		1/1	1/2	1/1	1/1	1/1	1/2	1/1	1/2	2/2	2/2	1/2	1/1	1/1	1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected
Aluminum nitrate	Al(NO ₃) ₃	013473-90-0	aqueous	(O)		1/1	1/0	1/4	1/0	(2)	1/0	3/4	1/1	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1		
Aluminum oxide, alpha-	Al ₂ O ₃	001344-28-1	solid			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	small solubility - no chemical effect expected
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	diluted	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	1/1	1/1	0/0		
Aluminum potassium sulfate	KAl(SO ₄) ₂ x 12H ₂ O	010043-67-1	saturated	Xi		1/1	1/1	1/0	1/0	(2)	0/0	3/4	1/1	1/0	1/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	1/0	(1)	(1)	0/0		
Aluminum sodium sulfate	NaAl(SO ₄) ₂	010102-71-3	?	?		1/1	1/1	(3)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	(2)	0/0	1/3	(1)	(1)			
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	10 %	?		1/1	1/1	1/0	1/0	(2)	1/1	3/4	1/1	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/2	1/1	1/1		
Aluminum sulfate	Al ₂ (SO ₄) ₃	010043-01-3	saturated	Xn		1/1	1/1	3/4	1/0	0/0	1/1	3/4	1/1	0/0	0/0	1/1	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	2/2	1/2	1/1		
Aminic acid	-> see: Formic acid																															
Aminoacetic acid	-> see: Glycine																															
Aminoethanol	C ₂ H ₇ NO	000141-43-5		Xn/Xi		0/0	0/0	(3)	(3)	0/0	0/0	(3)	1/2	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0		
Aminopropanoic acid, alpha	-> see: Alanine, L-																															
Ammonium acetate	Nickel-chromium-m	000631-61-8	saturated	Xi		1/1	1/1	1/0	1/1	(2)	1/1	(1)	1/1	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(3)								

						----- thermoplastics -----															--- fluoroplastics ---			--- elastomers ---			----- metals -----					
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C	COMMENT	
						Ammonium chloride	(NH ₄)Cl	012125-02-9	solid	Xn		1/1	1/1	1/0	1/0	(2)	0/0	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0	1/1
Ammonium chloride	(NH ₄)Cl	012125-02-9	aqueous	Xn		1/1	1/1	1/0	1/0	(2)	1/1	2/3	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1	sal ammoniac		
Ammonium difluoride	F ₂ H ₂ N	001341-49-7	50 %	T, C		1/1	1/1	2/0	(4)	0/0	0/0	(4)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	2/3	0/0	(3)	1/0	1/0			
Ammonium ferric sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-83-7	saturated	Xi		1/1	1/1	1/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(2)	(1)	0/0	(4)	0/0	0/0			
Ammonium ferrous sulfate	(NH ₄) ₂ Fe(SO ₄) ₂	007783-85-9		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	4/4	(1)	(1)				
Ammonium fluoride	(NH ₄)F	012125-01-8	saturated	T, C		1/1	1/1	1/0	4/4	(2)	1/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	(1)	(1)	?		
Ammonium fluoride	(NH ₄)F	012125-01-8	aqueous	T, C		1/1	1/1	1/0	(3)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	2/3	1/1	0/0	(4)	1/3	1/3	1/1		
Ammonium glycolate	C ₂ H ₂ NO ₂	035249-89-9		(Xi)		1/1	1/2	(1)	2/3	(2)	1/2	(2)	1/2	1/1	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(2)	(2)	(2)		Acetic acid	
Ammonium heptamolybdate	(NH ₄) ₆ Mo ₇ O ₂₄	012054-85-2		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	1/0	(3)	(1)	0/0	(1)	(1)	0/0			
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	30 %	C, N		1/1	1/2	(3)	4/4	2/4	1/2	1/2	2/3	2/3	1/2	2/3	2/3	1/2	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(3)	2/3	0/0	1/1	1/1	1/1	
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6	5 %	Xi		1/1	1/1	(2)	3/4	(2)	1/1	1/2	1/1	1/3	2/2	1/1	0/0	0/0	1/1	1/1	1/1	(2)	1/0	(2)	2/3	0/0	1/1	1/1	1/1	1/1		
Ammonium hydroxide	NH ₃ + H ₂ O	001336-21-6		C/Xi, N		1/1	1/1	(3)	4/4	2/4	1/1	1/2	1/1	2/3	2/3	1/2	1/3	2/2	1/1	1/1	1/1	1/3	1/0	(3)	4/4	0/0	1/1	1/1	1/1	1/1		
Ammonium mercaptan	-> see: Ammonium bisulfide																															
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	10 %	O		1/3	0/0	1/0	(1)	(2)	0/0	2/4	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	1/1	1/1	1/1	1/1	Nitric acid; Ammonium salt	
Ammonium nitrate	(NH ₄)NO ₃	006484-52-2	saturated	O		1/3	1/1	1/0	1/0	(2)	1/1	2/4	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/2	1/1	0/0	(2)	1/1	1/1	1/1		
Ammonium nitrite	(NH ₄)NO ₂	013446-48-5	aqueous	O, Xn		(1)	(1)	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(3)	1/0	0/0	(2)	(1)	(1)				
Ammonium oxalate	C ₂ H ₂ N ₂ O ₄	014258-49-2		Xn		1/1	1/2	(1)	1/1	(2)	1/2	(2)	1/2	1/1	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	(1)	0/0	1/1	1/1	1/1	0/0		
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	saturated	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0		
Ammonium persulfate	(NH ₄) ₂ S ₂ O ₈	007727-54-0	aqueous	O, Xn		0/0	0/0	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	4/4	0/0	4/4	(4)	3/4	0/0		
Ammonium phosphate, Mono-	(NH ₄)H ₂ PO ₄	007722-76-1	each	Xi		1/1	1/1	1/0	(2)	(2)	1/0	(2)	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/0	3/0	1/1	0/0	4/4	(1)	(1)	1/1		
Ammonium polyphosphate (APP)	(NH ₄ PO ₃) _n	068333-79-9		Xi		1/1	1/1	(1)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	1/0	(3)	1/1	0/0	(3)	(1)	(1)			
Ammonium rhodanide	-> see: Ammonium thiocyanate																															
Ammonium salt	-> see: Ammonium nitrate																															
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	10 %	Xn		1/1	1/1	1/0	1/1	(2)	(1)	1/0	1/1	1/1	1/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/1	1/1		
Ammonium sulfate	(NH ₄) ₂ SO ₄	007783-20-2	saturated	Xn		1/1	1/1	1/0	1/1	(2)	1/1	2/0	1/1	1/0	1/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	2/3	1/1	0/0	1/1	1/1	1/2	1/1		
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	each	T, C	X	1/1	1/1	1/0	4/4	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	1/2	0/0	1/1	(1)	(1)	?	Diammonium sulfide;	
Ammonium sulfide	(NH ₄) ₂ S	012135-76-1	aqueous	T, C	X	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(3)	3/3	0/0	1/1	(1)	(1)	1/1		
Ammonium sulfocyanide	-> see: Ammonium thiocyanate																															
Ammonium thiocyanate	CH ₄ N ₂ S	001762-95-4		Xn		1/1	1/1	(3)	1/0	(2)	1/1	1/0	1/1	1/3	0/0	1/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(3)	1/0	0/0	(2)	(1)	(1)		Ammonium sulfocyanide; Ammonium rhodanide; Thiocyanic acid, Ammonium salt; Ammonium sulfocyanate	
Amomum	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)			
Amyl acetate, normal	C ₇ H ₁₄ O ₂	000628-63-7		—	X	1/2	2/3	2/0	4/4	1/3	2/3	(1)	3/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/3	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0			
Amyl alcohol, n-	-> see: Pentanol, 1-																															
Amyl chloride	C ₅ H ₁₁ Cl	000543-59-9		F, Xn	X	3/4	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	3/4	3/4L	3/4L	0/0			
Amyl cinnamic aldehyde	C ₁₄ H ₁₆ O	000122-40-7		Xi		0/0	0/0	0/0	(4)	0/0	(4)	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(4)	(3)	(4)	0/0	(1)	(1)	(1)		odoriferous substance	
Aniline	C ₆ H ₅ N	000062-53-3		T		1/2	1/3	3/4	4/4	0/0	2/3	1/3	2/3	4/4	4/4	4/4	0/4	2/4	1/1	1/1	1/4	4/4	2/4	4/4	0/0	1/0	1/0	1/0	1/1			
Aniline hydrochloride	C ₆ H ₅ ClN	000142-04-1	saturated	T		1/3	0/0	(3)	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/1	3/0	2/2	3/3	0/0	4/4	4/4	4/4			
Anise	—	—		?		0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)				
Anise oil	—	084775-42-8		Xi		0/0	0/0	(3)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(1)	(1)	0/0				
Anisole	C ₇ H ₈ O	000100-66-3	100 %	Xi	X	1/4	3/4	1/0	4/4	0/0	2/3	(2)	3/3	4/4	0/0	0/0	0/0	0/0	1/1	1/1	(3)	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0			
Antifreeze agent (car)	—	—		Xn		1/1	1/1	3/3	(1)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	1/0	1/2	1/1	0/0	(1)	1/1	1/1		glycol-water-mixture		
Antimony pentachloride	SbCl ₅	007647-18-9		C	0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(2)	(2)	4/4	0/0	(3)	(4)	(4)	0/0				
Antimony trichloride	SbCl ₃	010025-91-9	90 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4	0/0			
Antimony trichloride	SbCl ₃	010025-91-9	anhydrous	C		0/0	0/0	4/4	1/0	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	1/0	1/0	1/0	0/0	1/1	4/4	4/4				
Antimony trichloride	SbCl ₃	010025-91-9	aqueous	C		0/0	0/0	4/4	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/0	1/1	3/0	0/0	4/4	4/4	4/4				
Apple juice	—	—		—		1/1	1/1	(1)	1/0	1/0	0/0	(2)	1/1	1/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	(1)	0/0	(2)	(1)	(1)			
Arsenic acid	H ₂																															

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics													fluoroelastomers			elastomers			metals		COMMENT								
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI		AL	V2A	V4A	Haselloy C				
Azole	-> see: Pyrrole																																		
Barium carbonate	BaCO ₃	000513-77-9	saturated	Xn	1/1	1/1	1/1	(1)	1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	small solubility - no chemical effect expected	
Barium chloride	BaCl ₂	010361-37-2	saturated	T	1/1	1/1	1/0	1/0	1/0	1/1	(2)	1/1	1/1	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1					
Barium chloride	BaCl ₂	010361-37-2	aqueous	T	1/1	1/1	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/2L	1/1L	1/1						
Barium dibromide	BaBr ₂	010553-31-8		Xn	1/1	1/1	(2)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	1/0	(1)	1/1	0/0	(2)	(2L)	(2L)							
Barium hydroxide	Ba(OH) ₂	012230-71-6	saturated	Xn	1/1	1/1	1/0	(3)	0/0	1/1	(2)	1/1	0/0	0/0	1/3	1/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	1/3						
Barium hydroxide	Ba(OH) ₂	012230-71-6	aqueous	Xn	1/1	1/1	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	1/1	1/1	0/0	(3)	1/1	1/1	?							
Barium sulfide	BaS	021109-95-5	saturated	(T)	1/1	1/1	1/0	(2)	(2)	1/1	(2)	1/1	0/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	(2)	1/0	1/0	1/1	0/0	(3)	(1)	(1)	1/1						
Battery acid	H ₂ SO ₄	007664-93-9	38 %	C	1/1	1/1	4/4	1/1	(4)	1/1	4/4	1/1	1/1	1/1	1/3	3/4	0/0	(1)	1/1	1/1	1/1	1/0	1/1	4/4	0/0	3/4	2/3	2/3	1/1				Sulfuric acid;		
Beef tallow	—	061789-97-7		—	0/0	0/0	1/0	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1							
Beef tallow emulsion	—	—	sulfonated	(-)	1/0	0/0	(2)	(2)	0/0	0/0	0/0	1/0	0/0	0/0	1/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	(2)	(2)	0/0	(2)	(1)	(1)	0/0					
Beer	—	—		—	1/1	1/1	1/0	1/0	1/0	1/1	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1						
Beeswax	—	008012-89-3		—	1/1	1/1	1/1	(1)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(3)	(1)	(2)	0/0	1/1	(1)	(1)								
Benzaldehyde	C ₇ H ₆ O	000100-52-7		Xn	1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0					artificial almond oil	
Benzene	C ₆ H ₆	000071-43-2		F, T	X	3/4	3/4	2/0	4/4	4/4	2/3	1/2	3/4	4/4	4/4	4/4	0/0	0/4	1/2	1/1	1/1	1/3	4/4	3/3	4/4	0/0	1/1	1/1	1/1	0/0					Cyclohexatriene; Benzol
Benzene chloride	-> see: Chlorobenzene																																		
Benzenesulfonic acid	C ₆ H ₅ SO ₃	000098-11-3	saturated	C	1/1	1/1	(4)	(3)	(4)	0/0	(4)	2/4	0/0	1/0	2/0	0/0	0/0	0/0	1/1	1/1	1/4	4/4	1/0	4/4	0/0	3/4	0/0	1/0	0/0						
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	saturated	Xn, Xi	1/1	1/1	3/4	4/4	1/0	1/2	2/4	1/3	2/2	3/3	1/2	1/0	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1						
Benzoic acid	C ₇ H ₆ O ₂	000065-85-0	aqueous	Xn, Xi	1/1	1/1	3/4	4/4	1/0	0/0	2/4	1/3	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	3/0	1/1	3/0	0/0	1/2	1/1	1/1	1/1						
Benzoic acid chloride	-> see: Benzoyl chloride																																		
Benzoyl chloride	C ₇ H ₅ ClO	000098-88-4	100 %	C	0/0	3/3	4/4	(4)	0/0	(4)	(3)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	(3)	4/4	0/0	1/0	(2L)	(2L)	0/0					Benzenecarbonyl chloride; Benzoic acid chloride	
Benzyl acetate	C ₉ H ₁₀ O ₂	000140-11-4		Xn/Xi	1/1	1/2	(2)	3/4	0/0	1/2	(2)	1/2	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	1/0	4/4	0/0	1/1	1/1	1/1							
Benzyl alcohol	C ₇ H ₈ O	000100-51-6		Xn	3/4	4/4	4/4	4/4	0/0	4/4	1/0	4/4	4/4	4/4	2/3	0/0	4/4	1/1	1/1	1/1	1/1	3/0	1/0	4/4	0/0	1/1	1/1	1/1	3/3						
Benzyl benzoate	C ₁₄ H ₁₂ O ₂	000120-51-4		Xn	0/0	0/0	(2)	(3)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	(3)	4/4	0/0	(1)	(1)	(1)							
Benzyl chloride	C ₇ H ₇ Cl	000100-44-7	100 %	T/Xi	0/0	4/4	1/0	4/4	0/0	4/4	(2)	4/4	4/4	4/4	4/4	4/4	0/0	0/0	(1)	1/0	(3)	4/4	1/0	4/4	0/0	4/4	1/1L	1/1L	0/0						
Benzyl ether	C ₈ H ₁₀ O	000103-50-4		Xi	0/0	0/0	(2)	(3)	0/0	0/0	(1)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	4/4	4/4	0/0	(1)	(1)	(1)							
Bismuth chloride	BiCl ₃	007787-60-2		Xi	1/1	1/1	(3)	(2)	(2)	0/0	(4)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(4)	0/0	0/0							
Bismuth nitrate, basic	Bi ₂ O(OH) ₂ (NO ₃) ₄	001304-85-4		O, Xi	1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	1/0	(1)	(1)	0/0	(3)	0/0	0/0								
Bisulfite solution	NaHSO ₃	??		Xn	1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	3/0	0/0	(3)	1/1	1/1	1/1						
Bisulfite solution, containing SO ₂	NaHSO ₃	??	saturated	Xn	1/1	1/1	(3)	(3)	0/0	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/1	4/4	0/0	(3)	1/1	1/1	1/1						
Bitter almond oil	C ₇ H ₆ O	090320-35-7		Xn	1/3	3/3	3/0	4/4	4/4	1/2	1/0	1/4	4/4	3/3	4/4	4/4	1/4	1/3	1/1	1/1	1/1	3/4	4/4	4/4	0/0	1/1	1/1	1/1						mainly: benzaldehyde	
Bitumen	—	008052-42-4		—	0/0	0/0	1/0	(2)	(2)	0/0	2/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	(3)	0/0	1/1	(1)	(1)							
Bone oil	—	008001-85-2		—	0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	1/1	1/1							
Boric acid	H ₃ BO ₃	010043-35-3	10 %	Xi	1/1	1/1	1/0	1/1	1/0	1/1	2/3	1/1	1/2	1/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1					
Boric acid	H ₃ BO ₃	010043-35-3	aqueous	Xi	1/1	1/1	3/3	1/1	1/0	0/0	2/3	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/2	1/1	1/1	1/1							
Brake fluid	—	—		?	1/0	1/0	1/0	4/4	0/0	1/1	(3)	1/1	3/0	0/0	1/0	3/0	4/4	0/0	(1)	1/0	(3)	1/0	4/4	4/4	0/0	(1)	(1)	(1)							
Bromic acid	HBrO ₃	007789-31-3	concentrated	C	0/0	0/0	(4)	(4)	(4)	0/0	4/4	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	(4)	(2)	4/4	0/0	(4)	(4)	(4)	(4)							
Bromine	Br ₂	007726-95-6		T+, C	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	2/4	4/4	4/4	1/2	1/1	1/3	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	4/4						
Bromine pentafluoride	BrF ₅	007789-30-2		F, T, C	0/0	0/0	4/4	(4)	(4)	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)								
Bromine steams	Br ₂	007726-95-6		T	(4)	(4)	4/4	(3)	4/4	(4)	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	1/0	(1)	4/4	(2-3)	4/4	0/0	(3)	(4)	(4)	4/4							
Bromine trifluoride	BrF ₃	007787-71-5		T, C	0/0	0/0	4/4	(4)	4/4	(4)	4/4	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	4/4	4/4	4/4	0/0	(3)	(4)	(4)								
Bromine water	Br ₂ +H ₂ O	007726-95-6	saturated	T	4/4	4/4	4/4	(4)	4/4	4/4	4/4	4/4	4/4	0/0	3/4	0/0	0/0	0/0	1/1	1/1	4/4	(2-3)	4/4	0/0	(4)	4/4	4/4	0/0							

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics																		fluoroplastics	elastomers	metals	COMMENT				
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A
Carbon tetrafluoride	CF ₄	000075-73-0		?																										
Carbonyl chloride	-> see: Phosgene																													
Carnauba wax	—	008015-86-9		—			1/1	1/1	1/1	(1)	1/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(1)	(3)	(1)	(1)	0/0	1/1	(1)	(1)
Castor oil	—	008001-79-4	100 %	Xi		1/1	1/1	1/0	1/0	(1)	1/0	(2)	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	(1)	1/1	1/1	1/1
Caustic potash	-> see: Potassium hydroxide																													
Cedar wood oil	—	008000-27-9		?		3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(4)	(2)	(3)	0/0	(1)	(1)	(1)	
Cesium bromide	CsBr	007787-69-1		Xi		1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(2)	0/0	0/0	
Cetyl alcohol	C ₁₈ H ₃₈ O	036653-82-4	100 %	Xi		1/1	1/1	4/4	(2)	1/0	0/0	(1)	1/1	0/0	1/0	1/1	3/3	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(1)	1/1	1/1	
Chalk	CaCO ₃	—		—		1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	calcium carbonate
Chloral hydrate	C ₂ H ₂ Cl ₂ O ₂	000302-17-0	techn. pure	T/Xi		3/3	3/3	4/4	(3)	(4)	0/0	(3)	3/4	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	4/4	3/0	3/4	4/4	0/0	4/4	0/0	0/0	0/0
Chloramine-T	C ₂ H ₃ ClNaNO ₂	000127-65-1	diluted	Xi		1/0	1/0	4/4	1/0	0/0	0/0	(3)	(3)	0/0	0/0	0/0	1/0	0/0	0/0	(1)	1/0	3/4	1/0	4/4	1/0	0/0	3/4	2/2	1/1	0/0
Chloric acid	HClO ₃	007790-93-4	1 %	(C)		0/0	1/1	4/4	(3)	0/0	0/0	(3)	1/3	0/0	0/0	1/3	1/0	0/0	0/0	0/0	1/1	1/1	3/0	1/1	(3)	0/0	(3)	4/4	4/4	1/1
Chloric acid	HClO ₃	007790-93-4	10 %	(O), C		1/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/1	3/0	3/0	4/4	0/0	4/4	4/4	4/4	1/1
Chloric acid	HClO ₃	007790-93-4	20 %	(O), C		3/0	1/4	4/4	(3)	(4)	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	0/0	1/1	1/0	3/0	3/0	4/4	0/0	4/4	4/4	4/4	?
Chloric acid, sodium salt	-> see: Sodium chlorate																													
Chlorine	Cl ₂	007782-50-5	10 % wet	T		3/4	3/4	4/4	2/3	4/4	2/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/1	1/1	1/1	(2)	2/0	3/0	4/4	0/0	4/4	4/4	4/4	0/0
Chlorine	Cl ₂	007782-50-5	97 %	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1
Chlorine	Cl ₂	007782-50-5	steam	T		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	1/1	1/0	1/1	4/4	1/1	4/4	0/0	(3)	1/0	1/0	1/1
Chlorine dioxide	ClO ₂	010049-04-4		E, T		0/0	0/0	4/4	(3)	0/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/0	(2)	4/4	1/0	4/4	0/0	3/4	3/4	3/4	
Chlorine trifluoride	ClF ₃	007790-91-2		(O, T)		0/0	0/0	4/4	(4)	4/4	(4)	4/4	(4)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(4)	4/4	(4)	4/4	0/0	(4)	(4)	(4)	(4)	
Chlorine water	Cl ₂ x H ₂ O	007782-50-5		(T)		3/0	0/4	4/4	4/4	4/4	4/4	4/4	3/4	4/4	0/0	3/3	3/0	3/3	1/1	(1)	1/1	1/1	3/0	1/0	4/4	0/0	4/4	2/0L	2/0L	0/0
Chloro acetophenone, p-	C ₈ H ₇ ClO	000099-91-2		(Xn)		1/1	1/1	(2)	4/4	0/0	1/1	(2)	1/1	4/4	4/4	4/4	0/0	0/0	1/1	1/1	(2)	(2)	(3)	4/4	4/4	0/0	(1)	0/0	0/0	
Chloro-1-propene, 3-	-> see: Allyl chloride																													
Chloro-2-propanone, 1-	-> see: Chloroacetone																													
Chloroacetic acid	C ₂ H ₃ ClO ₂	000079-11-8	50 %	T, C		1/3	1/3	4/4	(4)	4/4	0/0	4/4	1/1	0/0	0/0	1/0	0/0	3/4	0/0	(1)	1/1	1/4	2/0	3/0	4/4	0/0	4/4	2/4	2/4	1/4
Chloroacetic acid	C ₂ H ₃ ClO ₂	000079-11-8		T, C		1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/2	2/4	4/4	3/4	4/4	3/4	1/1	1/1	1/1	4/4	3/0	3/0	4/4	0/0	4/4	4/4	4/4	4/4
Chloroacetone	C ₃ H ₅ ClO	000078-95-5		(F, Xi)	X	0/0	0/0	(3)	(4)	(4)	(4)	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(2)	(3)	1/0	4/4	4/4	0/0	(4)	0/0	0/0	0/0	
Chlorobenzene	C ₆ H ₅ Cl	000108-90-7		Xn	X	3/4	3/4	4/4	4/4	1/4	4/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	1/1	1/1	1/1	1/1	4/4	3/4	4/4	0/0	1/1	1/1	1/1	1/1
Chlorodifluoroethane	C ₂ H ₂ ClF ₂	000075-68-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	1/0	0/0	(3)	0/0	0/0	0/0	
Chlorodifluoromethane	CHClF ₂	000075-45-6		N, Xn		0/0	3/0	1/0	3/0	1/0	0/0	1/0	4/4	4/4	4/4	2/0	4/4	0/0	0/0	3/3	1/0	(3)	1/0	4/4	4/4	0/0	(3)	0/0	0/0	R 22
Chloroethane, 1-	-> see: Monochloroethane																													
Chloroethyl alcohol, 2-	C ₂ H ₄ ClO	000107-07-3	techn. pure	T+		1/1	0/0	4/4	4/4	0/0	0/0	3/4	4/4	0/0	0/0	4/4	0/0	0/0	0/0	1/1	1/0	1/3	3/0	4/4	4/4	0/0	(3)	1/0L	1/0L	1/0
Chloroethylene	-> see: Vinyl chloride (VCM)																													
Chlorofluorocarbons (CFC)	—	—		N		0/0	0/0	(2)	(3)	0/0	0/0	1/0	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(3)	(3)	0/0	(3)	0/0	(3)	0/0	0/0	0/0	resistance depends on type
Chlorofluoromethane	CH ₂ ClF	000593-70-4		N		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Chloroform	CHCl ₃	000067-66-3	100 %	Xn		3/4	4/4	3/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/1	1/1	4/4	3/4	4/4	0/0	(3)	1/1	1/1	1/1
Chloroformyl chloride	-> see: Phosgene																													
Chloronaphthalene, 1-	C ₁₀ H ₇ Cl	000090-13-1		Xn		0/0	0/0	(2)	(3)	0/0	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	4/4	0/0	(2)	1/0	1/0	1/0	
Chloropentafluoroethane	C ₂ ClF ₅	000076-15-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	
Chloroprene	C ₄ H ₅ Cl	000126-99-8		F, Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/4	4/4	0/0	(3)	0/0	0/0	0/0	
Chloropropylene, 3-	-> see: Allyl chloride																													
Chlorosulfonic acid	ClHSO ₃	007790-94-5	techn. pure	C+		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	3/0	4/4	4/4	0/0	0/0	1/0	3/4	4/4	4/4	4/4	0/0	3/3	3/4	3/4	1/0
Chlorotoluene	C ₇ H ₇ Cl	—		Xn		0/0	0/0	(2)	4/4	0/0	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	4/4	0/0	(3)	1/0	1/0	1/1	isomer not indicated in the source
Chlorotrifluoromethane	CClF ₃	000075-72-9		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0	0/0	0/0	
Chromic acid	CrO ₃	001333-82-0	10 %	O, T, C, N		1/1	1/1	4/4	2/3	3/0	1/1	4/4	1/1	1/1	4/4	1/2	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	1/2	1/2	1/1
Chromic acid	CrO ₃	001333-82-0	20 %	O, T, C, N		0/0	1/3	4/4	3/4	(4)	0/0	4/4	3/3	1/0	1/0	1/0	1/0	0/0	0/0	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/3	(2)	(2)	1/1
Chromic acid	CrO ₃	001333-82-0	50 %	O, T, C, N		3/4	3/4	4/4	3/4	(4)	2/3	4/4	3/3	4/4	1/3	1/0	3/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	(3)	2/3	2/3	1/1	
Chromic potassium sulfate	KCr(SO ₄) ₂ x 12H ₂ O	007788-99-0	saturated	Xn		1/1	0/0	(2)	1/0	(2)	0/0	(3)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(3)	1/3	1/3	1/1
Chromic-sulfuric acid	CrO ₃ + H ₂ SO ₄	065272-71-1	concentrated	O, T, C, N		4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	4/4	4/4	1/1	0/0	1/1	4/4	4/4	1/0	4/4	4/4	2/3	2/3	0/0
Chromium salts	—	—	each	T/Xn		0/0	0/0	0/0	(2)	(2)	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(1)	0/0	K	K	K	0/0
Chromium trioxide	-> see: Chromic acid																													
Cinnamaldehyde	C ₉ H ₈ O	000104-55-2		Xn, Xi		0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(1)	(1)	(1)	1/1
Cinnamon	—	—	ground	?																										

----- thermoplastics ----- | --- fluoroplastics --- | --- elastomers --- | ----- metals -----

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE		PA		PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C	COMMENT				
					HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A							
Cinnamon oil	—	008007-80-5	—	Xn, Xi			3/4	4/4	(2)	2/3	0/0	4/4	(2)	4/4	4/4	3/3	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)					
Citric acid	C ₆ H ₈ O ₇	000077-92-9	10 %	Xi			1/1	1/1	1/1	1/2	1/3	1/1	2/4	1/1	1/2	1/1	1/3	1/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/0	1/1	1/1	1/1					
Citric acid	C ₆ H ₈ O ₇	000077-92-9	50 %	Xi			1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/3	1/2	1/1				
Citric acid	C ₆ H ₈ O ₇	000077-92-9	saturated	Xi			1/1	1/1	3/0	1/0	0/0	1/0	2/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/0	(1)	1/1	0/0	1/0	1/0	1/3	1/2	1/1						
Citrus juices	—	—	aqueous	—			1/1	1/1	1/0	1/0	0/0	1/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	(1)	1/0	1/1	0/0	(2)	1/1	1/1						
Cleaning agents	—	—	—	?			1/1	1/1	1/0	1/1	1/1	0/0	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	(2)	0/0	1/1	1/1	1/1						
Clophen A60	—	011096-82-5	—	Xn, N			0/0	0/0	1/0	(3)	0/0	0/0	(2)	4/4	0/0	4/4	0/0	0/0	0/0	(1)	(2)	4/4	2/3	4/4	0/0	1/0	1/0	1/0	1/0	0/0	polychlorinated Biphenyls, PCB, Bayer				
Coal gas, without benzene	—	—	—	F+, T	X		1/0	1/0	1/0	1/0	(2)	1/0	(2)	1/0	1/0	0/0	1/0	1/0	0/0	(1)	1/0	1/0	4/4	1/0	3/0	0/0	1/1	1/1	1/1	0/0					
Cobalt dichloride	CoCl ₂	007646-79-9	aqueous	Xn			1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	0/0	(3)	0/0	0/0					
Cocoa	—	—	—	(—)			1/1	1/1	(2)	(1)	(2)	0/0	(1)	2/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)					
Cocoa butter	—	008002-31-1	—	—			0/0	0/0	1/0	(1)	1/0	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	4/4	1/0	4/4	0/0	(1)	1/1	1/1						
Coconut butter	—	—	—	—			0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/0	0/0	(1)	1/1	1/1						
Coconut fatty alcohol	—	068425-37-6	techn. pure	(Xi)			1/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	(1)	1/1	1/1						
Coconut oil	—	008001-31-8	techn. pure	—			1/3	1/3	1/0	(2)	1/0	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	4/4	1/1	1/1	0/0	(1)	1/1	1/1						
Cod-liver oil	—	008001-69-2	—	—			1/3	1/3	(2)	1/0	(2)	0/0	(2)	1/3	1/1	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/0	1/0	0/0	1/0	(1)	(1)	1/1				
Colza oil	—	008002-13-9	—	—			0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	(1)	1/1	1/1							
Compressed air	—	—	oleaginous	—			1/0	0/0	(2)	(2)	(1)	0/0	(1)	3/0	0/0	0/0	3/0	0/0	0/0	(1)	1/1	1/1	(3)	(1)	(2)	0/0	1/1	1/1	1/1						
Condy's crystals	—	—	—	—			-> see: Potassium permanganate																												
Copper acetate	C ₄ H ₈ CuO ₄	004180-12-5	aqueous	Xn			1/1	1/1	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	(3)	3/3	0/0	4/4	1/1	1/1	1/1	verdigris				
Copper sulfate	CuSO ₄ x 5H ₂ O	007758-99-8	aqueous	Xn			1/1	1/1	1/0	1/0	(2)	1/0	1/0	1/1	1/1	1/0	1/3	1/0	1/1	1/1	(1)	1/1	1/1	1/0	1/1	2/0	0/0	4/4	1/1	1/1	blue stone				
Cotton oil	—	008001-29-4	techn. pure	?			0/0	0/0	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	3/0	1/0	1/0	0/0	(1)	1/1	1/1						
Creosote	—	—	—	(T)			1/1	1/1	3/0	(3)	0/0	0/0	(3)	3/4	0/0	1/0	3/0	4/4	0/0	(1)	1/1	(3)	4/4	(3)	1/0	0/0	(2)	1/1	1/1	0/0					
Creosote	—	—	—	—			-> see: Carbolineum																												
Cresol (-mixtures)	C ₇ H ₈ O	001319-77-3	—	T, C			3/4	4/4	4/4	4/4	4/4	4/4	4/4	2/3	4/4	4/4	4/4	4/4	3/4	1/2	1/1	1/1	1/1	4/4	1/0	4/4	0/0	1/1	1/0	1/0	1/1				
Crotonaldehyde	C ₆ H ₈ O	004170-30-3	techn. pure	F, T	X		1/0	0/0	(2)	(4)	0/0	(4)	(2)	1/0	0/0	0/0	4/4	0/0	0/0	(1)	1/0	1/3	1/0	3/0	4/4	0/0	1/0	1/1	1/1	0/0					
Crude oil	—	—	100 %	(N)			0/0	1/3	1/0	(3)	1/0	0/0	1/0	1/3	3/0	1/0	1/0	3/0	0/0	(1)	1/1	1/1	4/4	1/0	3/3	0/0	(2)	(1)	(1)						
Cumene	C ₉ H ₁₂	000098-82-8	—	Xi	X		2/3	3/4	(2)	4/4	0/0	4/4	(2)	3/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	0/0					
Cupric chloride	CuCl ₂	007447-39-4	saturated	Xn			1/3	1/1	(3)	1/0	(2)	1/0	(2)	1/3	0/0	0/0	1/1	1/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1					
Cupric nitrate	Cu(NO ₃) ₂	003251-23-8	saturated	O, Xn			1/1	1/1	1/0	(2)	(2)	1/0	1/0	1/1	1/0	0/0	1/0	1/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	4/4	1/1	1/1	1/1					
Cupric nitrate	Cu(NO ₃) ₂	003251-23-8	aqueous	O, Xn			0/0	0/0	(3)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	1/1	1/1	1/1					
Cuprous chloride	CuCl	007758-89-6	aqueous	Xn			0/0	0/0	(3)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	4/4	4/4	4/4	1/1					
Cuprous cyanide	CCuN	000544-92-3	saturated	T			1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/3	0/0	0/0	1/0	1/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	(3)	1/1	1/1						
Curry	—	—	—	?			0/0	0/0	(2)	(2)	0/0	(1)	(2)	3/3	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	possibility of discoloration					
Cyanoethylene	—	—	—	—			-> see: Acrylonitrile																												
Cyanomethane	—	—	—	—			-> see: Acetonitrile																												
Cyclanon	—	—	—	(Xn, Xi)			1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/1	0/0	3/4	(1)	(1)	0/0	appliances for dyeing-mill; BASF				
Cyclohexane	C ₆ H ₁₂	000110-82-7	—	F	X		3/4	3/4	1/0	3/3	1/0	4/4	1/1	3/4	4/4	4/4	2/3	1/0	1/3	1/2	1/1	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	0/0					
Cyclohexanol	C ₆ H ₁₂ O	000108-93-0	techn. pure	Xn			1/1	1/1	1/1	3/0	0/0	1/2	1/0	1/3	3/3	1/0	1/1	4/4	1/3	0/0	(1)	1/1	1/3	4/4	4/4	3/3	0/0	1/1	(1)	(1)	0/0				
Cyclohexanone	C ₆ H ₁₀ O	000108-94-1	techn. pure	Xn	X		1/3	3/4	1/0	4/4	(4)	3/4	1/0	2/4	4/4	4/4	4/4	4/4	0/0	(1)	1/1	1/3	4/4	4/4	4/4	0/0	1/0	(1)	(1)	0/0					
Cyclohexatriene	—	—	—	—			-> see: Benzene																												
Cymene, p-	C ₁₀ H ₁₄	000099-87-6	—	F, Xn/Xi	X		0/0	0/0	(2)	4/4	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	4/4	0/0	1/1	1/1	1/1	0/0					
DDT (emulsion)	C ₁₄ H ₉ Cl ₅	000050-29-3	—	T			0/0	0/0	(2)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(2)	(3)	(3)	0/0	(2)	(2)	(2)	0/0					
Decahydronaphthalene	C ₁₀ H ₁₈	000091-17-8	—	Xn			1/3	3/4	1/0	4/4	3/0	4/4	1/0	3/4	4/4	4/4	1/2	3/0	3/4	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	1/1	(1)	0/0					
Decane	C ₁₀ H ₂₂	000124-18-5	—	Xn	X		0/0	0/0	(1)	(2)	(1)	(3)	1/1	(3)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	4/4	1/0	3/3	0/0	1/1	(1)	(1)						
Dehydroacetic acid	C ₈ H ₈ O ₄	000520-45-6	—	Xn			0/0	0/0	(3)	(2)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	1/1	0/0	1/1	1/1	(2)	(2)	(2)	0/0	(4)	(1)	(1)						
Densodrin W	—	—	aqueous	?			0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	(1)	1/1	1/0	0/0	0/0	1/0	0/0	0/0	0/0	0/0							

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics											fluoroplastics	elastomers	metals				COMMENT																									
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETEFE	FEP	PTFE		PIVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Hastelloy C																
Diaminoethane	C ₂ H ₈ N ₂	000107-15-3	techn. pure	C, Xn																																											
Diammonium sulfide	-> see: Ammonium sulfide																																														
Diamyl phthalate	C ₁₈ H ₂₆ O ₄	000131-18-0	100 %	(T)																																											
Dibenzyl sebacate	C ₂₂ H ₂₆ O ₄	??		?																																							plasticiser				
Dibromoethane, 1,2-	-> see: Ethylene dibromiden (EDB)																																														
Dibromotetrafluoroethane	C ₂ Br ₂ F ₄	000124-73-2		?																																											
Dibutyl phthalate, n-	C ₁₆ H ₂₂ O ₄	000084-74-2	FR, 80°C	T																																							plasticiser				
Dibutyl phthalate, n-	C ₁₆ H ₂₂ O ₄	000084-74-2		T																																							plasticiser				
Dibutyl sebacate	C ₁₈ H ₃₄ O ₄	000109-43-3	techn. pure	—																																							plasticiser				
Dibutylamine	C ₈ H ₁₉ N	000111-92-2		Xn	X																																										
Dichloroacetic acid	C ₂ H ₂ Cl ₂ O ₂	000079-43-6	50 %	C																																											
Dichloroacetic acid	C ₂ H ₂ Cl ₂ O ₂	000079-43-6	techn. pure	C																																											
Dichlorobenzene, 1,2-	C ₆ H ₄ Cl ₂	000095-50-1		Xn																																											
Dichlorobenzene, 1,4-	C ₆ H ₄ Cl ₂	000106-46-7		Xn																																											
Dichlorodifluoromethane	CCl ₂ F ₂	000075-71-8	techn. pure	N																																											
Dichlorodifluoromethane	CCl ₂ F ₂	000075-71-8		N																																											
Dichloroethane	C ₂ H ₄ Cl ₂	—		F, T	X																																								isomer not indicated in the source		
Dichloroethylene	C ₂ H ₂ Cl ₂	—	techn. pure	F+, Xn	X																																							isomer not indicated in the source			
Dichlorofluoromethane	CHCl ₂ F	000075-43-4	100 %	N																																											
Dichlorohexafluorocyclobutane	C ₂ Cl ₆ F ₆	000356-18-3		?																																											
Dichloroisopropyl ether	C ₆ H ₁₂ Cl ₂ O	—		(Xn)																																									isomer not indicated in the source		
Dichloropropane	C ₃ H ₆ Cl ₂	—	100 %	F, T/Xn	X																																								isomer not indicated in the source		
Dichlorotetrafluoroethane	C ₂ Cl ₂ F ₄	000076-14-2		?																																											
Dicyclohexyl phthalate	C ₂₀ H ₂₆ O ₄	000084-61-7	techn. pure	(Xn)																																										plasticiser	
Dicyclohexylamine (DCHA)	C ₁₂ H ₂₃ N	000101-83-7		C, Xn																																											
Diesel fuel	—	—		Xn, N																																											
Diesel fuel for heating	—	—		Xn																																											
Diesel oil	—	068334-30-5	100 %	(Xn)																																											
Diethanolamine (DEA)	C ₄ H ₁₁ NO ₂	000111-42-2	100 %	Xi																																											
Diethyl ethyl	C ₁₀ H ₂₀ O	000060-29-7	techn. pure	F+, Xn	X																																										
Diethyl ketone	-> see: Pentanone, 3-																																														
Diethyl malonate	C ₇ H ₁₂ O ₄	000105-53-3		Xi																																											
Diethyl sebacate	C ₁₄ H ₂₆ O ₄	000110-40-7		Xi																																											plasticiser
Diethyl succinate	C ₈ H ₁₄ O ₄	000123-25-1		—																																											
Diethylamine	C ₄ H ₁₁ N	000109-89-7	techn. pure	F, C, Xn	X																																										
Diethylbenzene	C ₁₀ H ₁₄	000135-01-3		Xi																																											
Diethylene glycol	C ₄ H ₁₀ O ₃	000111-46-6		T																																											
Diethylene glycoether	—	—		(Xn)																																											
Difluoroethane	C ₂ H ₂ F ₂	000075-37-6		(E), F+																																											
Difluoromethane	CH ₂ F ₂	000075-10-5		?																																											
Diglycolic acid	C ₄ H ₆ O ₅	000110-99-6	aqueous	Xn																																											
Diglycolic acid	C ₄ H ₆ O ₅	000110-99-6	30 %	Xn, Xi																																											
Diisobutyl ketone	C ₈ H ₁₆ O	000108-83-8	techn. pure	Xi	X																																										
Diisobutylene (DIB)	C ₈ H ₁₀	025167-70-8		F	X																																										
Diisopropyl ether	C ₈ H ₁₈ O	000108-20-3	techn. pure	F	X																																										
Di-isopropyl ketone	C ₈ H ₁₆ O	000565-80-0		F	X																																										
Dimethyl ether	C ₂ H ₆ O	000115-10-6	gas	F+	X																																										
Dimethyl formamide (DMF)	C ₃ H ₇ NO	000068-12-2		T, F	X																																										
Dimethyl ketone	-> see: Acetone																																														
Dimethyl phthalate (DMP)	C ₁₀ H ₁₀ O ₄	000131-11-3	100 %	(Xn)																																										plasticiser	
Dimethyl sulfoxide (DMSO)	C ₂ H ₆ SO	000067-68-5		Xi																																											
Dimethylacetone	-> see: Pentanone, 3-																																														
Dimethylamine	C ₂ H ₇ N	000124-40-3	techn. pure	F+, Xn	X																																										

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	thermoplastics												fluoroplastics		elastomers		metals		COMMENT							
						HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM		FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C
Dimethylaniline	C ₉ H ₁₁ N	—		T																										isomer not indicated in the source	
Dinitro ethylene glycol	C ₂ H ₄ (NO ₂) ₂	000628-96-6	diluted	(E, T+)		0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	4/4	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	(1)	(1)	0/0	
Dinonyl phthalate (DNP)	C ₂₈ H ₄₂ O ₄	000084-76-4	techn. pure	Xn		3/0	0/0	(2)	(3)	0/0	0/0	(2)	(1)	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/0	(2)	(3)	4/4	4/4	0/0	(1)	(1)	(1)	plasticiser	
Diocyl adipate	C ₂₂ H ₄₂ O ₄	000103-23-1	?	?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(4)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	plasticiser	
Diocyl phthalate (DOP)	C ₂₄ H ₃₈ O ₄	000117-81-7	techn. pure	Xn		4/4	4/4	1/0	4/4	1/0	1/0	(2)	4/4	4/4	1/0	4/4	4/4	0/0	0/0	1/1	1/0	(2)	3/0	2/3	4/4	0/0	(1)	(1)	(1)	plasticiser	
Diocyl sebacate	C ₂₆ H ₅₀ O ₄	002432-87-3		—		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	2/0	3/0	4/4	0/0	(1)	(1)	(1)	plasticiser	
Dioxane	C ₄ H ₈ O ₂	000123-91-1		F, Xn	X	2/2	2/3	1/0	4/4	1/0	2/3	1/2	3/3	4/4	2/3	3/4	4/4	4/4	1/3	1/1	1/1	3/3	2/0	4/4	4/4	0/0	1/1	1/0	1/0	0/0	
Diphenyl ether	C ₁₂ H ₁₀ O	000101-84-8		Xn/Xi		0/0	1/0	3/0	(3)	(4)	0/0	1/1	4/4	4/4	0/0	0/0	4/4	4/4	0/0	(1)	1/0	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	0/0	
Diphenylamine	C ₁₂ H ₁₁ N	000122-39-4		T		0/0	0/0	0/0	(3)	0/0	0/0	(2)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	(4)	0/0	(1)	(1)	(1)	0/0	
Diphenyl ether	—	008004-13-5		?		0/0	0/0	1/1	(3)	4/4	0/0	1/1	4/4	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	(1)	(1)	mixture with diphenyl and diphenyl ether; Bayer	
Dipropyl ketone	C ₉ H ₁₈ O	000123-19-3		—	X	0/0	0/0	(3)	(4)	(4)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Dipropylene glycol	C ₈ H ₁₆ O ₃	025265-71-8		Xi		1/1	1/1	(2)	2/3	0/0	1/1	1/0	1/1	1/1	2/2	2/3	0/0	0/0	1/1	1/1	(1)	(2)	4/4	3/0	3/3	0/0	(1)	(1)	(1)		
Dipropylene glycol (mono)methyl ether	C ₈ H ₁₆ O ₂	—		—	X	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	0/0	isomer not indicated in the source
Disodium phosphate	Na ₂ HPO ₄	007558-79-4		(Xi)		1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	(1)	0/0	(1)	1/1	1/1	0/0	
Dispersion of rubber	—	—		?		0/0	0/0	1/0	(2)	(2)	0/0	2/3	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(3)	(1)	(2)	0/0	(3)	(1)	(1)	latex	
Dithionous acid, disodium salt	-> see: Sodium hydrosulfite																														
Divinylene oxide	-> see: Furan																														
Dope, viscous -	—	—		(Xn, Xi)		1/1	1/1	4/4	(3)	0/0	0/0		1/1	0/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	(3)	(2)	4/4	0/0	(3)	3/4	2/4	0/0	
Emulsifiers	—	—		?		0/0	0/0	(2)	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(3)	0/0	0/0	K	K		
Emulsions for fotos	—	—		?		1/0	0/0	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(2)	(2)	(1)	0/0	(2)	0/0	0/0		
Ephetin	—	—	10% in water	?		0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0		
Epichlorhydrin	C ₂ H ₄ ClO	000106-89-8	100 %	F, T	X	1/0	1/0	4/4	(4)	0/0	(4)	1/0	2/2	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/0	(3)	3/0	4/4	4/4	0/0	(3)	0/0	0/0	0/0	
Epoxypropane, 1,2-	-> see: Propylene oxid																														
Ethanal	-> see: Acetaldehyde																														
Ethanedioic acid	-> see: Oxalic acid																														
Ethanenitrile	-> see: Acetonitrile																														
Ethanoyl chloride	-> see: Acetyl chloride																														
Ethoxybenzene	C ₈ H ₁₀ O	000103-73-1		?		0/0	0/0	(2)	(4)	0/0	(3)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	Ethyl phenyl ether; Phenyl ether; Phenetole	
Ethyl acetate	C ₄ H ₈ O ₂	000141-78-6	100 %	F	X	1/3	3/4	1/0	4/4	4/4	4/4	1/1	1/3	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	3/3	3/0	4/4	4/4	0/0	1/1	(1)	(1)	1/0	
Ethyl acrylate	C ₈ H ₁₀ O ₂	000140-88-5	100 %	F, Xn	X	4/4	4/4	1/0	(4)	(4)	(4)	(2)	4/4	0/0	0/0	4/4	4/4	0/0	0/0	1/1	1/0	3/0	4/4	4/4	4/4	0/0	(1)	(1)	(1)	1/0	
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	40 %	—	X	1/1	1/2	1/0	1/2	1/1	1/2	1/2	1/1	2/3	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1		
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	50 %	—	X	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1		
Ethyl alcohol	C ₂ H ₆ O	000064-17-5	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		
Ethyl aldehyde	-> see: Acetaldehyde																														
Ethyl benzoate	C ₈ H ₁₀ O ₂	000093-89-0		Xn		2/2	3/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	4/4	4/4	0/0	4/4	1/2	1/1	1/0	(3)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethyl butyrate	C ₈ H ₁₂ O ₂	000105-54-4		F	X	2/3	2/4	(2)	4/4	0/0	3/4	(2)	2/4	4/4	4/4	4/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl chloride	-> see: Monochloroethane																														
Ethyl chloroacetate	C ₄ H ₇ ClO ₂	000105-39-5	techn. pure	T/Xi		1/1	1/1	(3)	4/4	(4)	(4)	(3)	1/1	4/4	0/0	3/4	3/4	0/0	0/0	(1)	1/1	1/4	3/0	4/4	4/4	0/0	3/4	0/0	0/0	0/0	
Ethyl cyanoacetate	C ₃ H ₅ NO ₂	000105-56-6		Xn/Xi		1/1	1/1	0/0	3/4	0/0	1/1	(2)	1/1	2/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	(3)	(2)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Ethyl formate	C ₃ H ₆ O ₂	000109-94-4		F	X	0/0	0/0	0/0	(4)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)	(1)		
Ethyl lactate	C ₅ H ₁₀ O ₃	000097-64-3		—	X	1/1	1/1	(2)	3/4	0/0	1/1	(2)	1/1	3/4	3/3	3/4	0/0	0/0	1/1	1/1	(1)	3/0	(3)	(3)	(3)	0/0	(1)	(1)	(1)		
Ethyl mercaptan	C ₂ H ₆ S	000075-08-1		F, Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)		
Ethyl phenyl ether	-> see: Ethoxybenzene																														
Ethyl silicate	C ₈ H ₂₀ SiO ₄	000078-10-4		Xn	X	0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	1/0	0/0	(1)	(1)	(1)		
Ethylbenzene	C ₈ H ₁₀	000100-41-4		F, Xn	X	2/3	3/4	(2)	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	4/4	2/3	1/1	1/0	1/1	4/4	(2)	4/4	0/0	(1)	(1)	(1)	0/0	
Ethylene	C ₂ H ₄	000074-85-1		F+	X	0/0	0/0	1/0	(2)	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	3/0	3/3	0/0	(1)	(1)	(1)	0/0	
Ethylene dibromiden (EDB)	C ₂ H ₄ Br																														

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics															fluoro			elastomers			metals			COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A		V4A	Haselby C					
Ethylene oxide	C_2H_4O	000075-21-8		F+, T	X	2/3	3/3	3/0	3/4	1/0	3/4	1/0	3/3	4/4	1/1	3/4	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0		
Ethylenediaminetetraacetic acid (EDTA)	$C_{10}H_{16}N_2O_8$	000060-00-4		Xi		1/1	1/1	(2)	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(2)	(1)	0/0	(3)	0/0	0/0	0/0					0/0		
Ethylhexanol-1	$C_8H_{18}O$	000104-76-7		Xn/Xi		0/0	1/3	(2)	(2)	(1)	1/0	1/0	1/0	3/0	0/0	1/0	4/4	0/0	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)					1/1		
Ethyne				-> see: Acetylene																																
Eucalyptus oil	—	008000-48-8		?		0/0	0/0	(2)	(3)	0/0	0/0	(2)	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(1)	(1)	(1)					0/0		
Exhaust gases, alkaline	—	—		?		1/1	0/0	(2)	0/0	0/0	0/0	(1)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	0/0	1/1	1/4	1/0	1/0	1/0	0/0	(2)	(1)	(1)					0/0		
Exhaust gases, containing carbon dioxide	—	—	small	?		1/1	0/0	(1)	(1)	(1)	1/1	(1)	1/1	(1)	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/0	1/0	(1)	(1)	(1)	(1)	(1)					0/0			
Exhaust gases, containing hydrochloric acid	—	—	each	?		1/1	0/0	(3)	0/0	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	2/2L	2/2L	3/3				3/3		
Exhaust gases, containing hydrogen fluoride	—	—	small	?		1/1	0/0	(3)	(3)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	(2)	(2)	1/1				1/1		
Exhaust gases, containing nitrose	—	—	small	?		1/1	0/0	(3)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	(3)	0/0	(2)	(1)	(1)					0/0			
Exhaust gases, containing sulfur dioxide	—	—	small	?		1/1	0/0	(2)	0/0	0/0	(4)	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/0	0/0	(4)	1/1	1/1					0/0			
Exhaust gases, containing sulfur trioxide	—	—	small	?		1/1	0/0	(4)	0/0	0/0	(4)	4/4	0/0	0/0	1/1	0/0	0/0	(2)	(2)	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)					0/0			
Exhaust gases, containing sulfuric acid	—	—	each	?		1/1	0/0	(4)	0/0	0/0	(4)	1/3	0/0	0/0	1/1	0/0	0/0	(2)	1/1	1/1	1/1	1/0	1/0	4/4	0/0	(4)	(2)	(1)					0/0			
Fat, animal	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1					1/1		
Fat, mineral	—	—		(—)		0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	(1)	1/0	0/0	(1)	1/1	1/1					1/1		
Fat, vegetable	—	—		—		0/0	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1					1/1			
Fats, edible oil	—	—		—		0/0	1/0	1/0	1/0	1/0	1/0	1/1	3/0	0/0	1/0	1/0	3/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1					1/1		
Fatty alcohol sulfonates	—	—	aqueous	(Xn, Xi)		1/1	0/0	1/0	(2)	1/0	0/0	1/1	1/3	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	(2)	(2)	1/1	0/0	3/4	1/0	1/0	0/0					detergents		
Ferric chloride	$FeCl_3$	007705-08-0	saturated	Xn		1/1	1/1	3/0	1/0	0/0	1/0	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	(1)	1/1	1/1	0/0	4/4	4/4	4/4	1/1					1/1		
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	aqueous	(O, Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1					1/1	
Ferric nitrate	$Fe(NO_3)_3$	010421-48-4	saturated	O, Xn		1/1	1/1	1/0	1/0	0/0	1/0	(3)	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1					1/1		
Ferric sulfate	$Fe_2(SO_4)_3$	010028-22-5	saturated	Xi		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	0/0	4/4	1/1	1/1	1/1					1/1		
Ferrous chloride	$FeCl_2$	007758-94-3	saturated	Xn		1/1	1/1	3/0	1/0	(2)	1/0	(3)	1/1	1/1	1/0	1/1	1/0	1/1	1/1	1/1	1/1	(1)	1/1	(1)	0/0	4/4	(2)	1/1	1/1					1/1		
Ferrous sulfate	$FeSO_4$	007720-78-7	saturated	(Xn)		1/1	1/1	(2)	1/0	0/0	1/0	(3)	1/1	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1					1/1	
Ferrous sulfate	$FeSO_4$	007720-78-7	aqueous	(Xn)		1/1	1/1	(2)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	1/0	0/0	4/4	1/1	1/1	1/1					1/1	
Ferrous sulfate	$FeSO_4$	007720-78-7		Xn		1/1	1/1	(2)	1/0	(2)	0/0	(3)	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/0	(1)	0/0	4/4	1/1	1/1	1/1					1/1	
Fire-damp	—	—		F+	X	0/0	0/0	1/0	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	1/1	(1)	(1)					mainly methane		
Fixer for fotos	—	—		?		1/0	1/1	1/0	(2)	0/0	0/0	1/0	1/1	0/0	0/0	1/3	1/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/0	1/0						1/0		
Fluid 101, 100°C	—	—		?		0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	0	0	0	0	0	3	0	0	0	0					Brake fluid, based on polyglycoles	
Fluorides	—	—		T		1/1	1/1	(2)	1/1	(2)	1/1	(1)	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	(1)	0/0	0/0	K	K					0/0		
Fluorine	F_2	007782-41-4		O, T+, C+		4/4	4/4	4/4	4/4	4/4	3/4	4/4	4/4	4/4	4/4	1/2	0/0	4/4	1/3	1/2	1/2	4/4	4/4	3/0	4/4	0/0	4/4	(4)	(4)	(4)	(4)				0/0	
Fluorobenzene	C_6H_5F	000462-06-6		F, (Xn)	X	0/0	0/0	(2)	(4)	0/0	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0						0/0		
Fluorocarbons	—	—		?		0/0	0/4	(2)	(3)	(2)	0/0	(2)	(3)	4/4	0/0	0/0	0/0	0/4	1/1	0/0	1/1	(3)	(3)	(3)	(3)	0/0	(1)	0/0	0/0					resistance depends on type		
Formaldehyde solution	CH_2O	000050-00-0	10 %	Xn		1/1	1/1	3/3	1/2	1/0	1/2	1/2	1/1	3/4	2/3	2/3	3/3	1/3	1/1	1/1	1/1	1/1	1/0	3/0	(2)	0/0	1/1	1/1	1/1	1/1					1/1	
Formaldehyde solution	CH_2O	000050-00-0	30 %	T		1/1	1/1	3/3	1/2	1/0	0/0	1/2	1/1	4/4	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	3/0	1/0	0/0	1/1	1/1	1/1	1/1					1/1		
Formaldehyde solution	CH_2O	000050-00-0	40 %	T		1/2	2/3	1/3	1/2	1/0	1/2	1/2	1/2	4/4	2/3	2/3	3/3	0/4	1/1	1/1	1/1	1/1	1/0	3/0	(3)	0/0	1/1	1/1	1/1	1/1					1/1	
Formamide	CH_3NO	000075-12-7	techn. pure	T/Xi		1/1	1/1	1/0	(3)	0/0	0/0	1/0	1/1	1/0	0/0	4/4	0/0	0/0	1/0	1/1	(3)	3/0	2/3	4/4	0/0	1/1	1/1	1/1	1/1					1/1		
Formic acid	CH_2O_2	000064-18-6	50 %	C, F		1/1	1/2	4/4	3/3	0/0	1/2	4/4	1/2	3/3	2/2	2/3	0/0	1/3	1/1	1/1	1/1	1/1	3/4	4/4	4/4	0/0	(3)	1/3	1/2	1/1					Hydrogen carboxylic acid; Methanoic acid; Aminic acid; Formylc acid	
Formic acid	CH_2O_2	000064-18-6	98-100 %	C, F, T		1/1	1/2	4/4	3/4	0/0	1/3	4/4	1/3	3/4	3/3	3/4	1/3	3/4	1/1	(1)	1/1	1/1	3/4	4/4	4/4	0/0	1/0	1/3	1/2	1/1					1/0	
Formic acid	CH_2O_2	000064-18-6	3 %	Xi		1/1	1/2	3/4	1/2	1/0	1/2	2/4	1/2	1/2	2/2	2/3	0/0	0/0	1/1	1/1	1/1	1/1	3/0	(3)	4/4	0/0	(3)	1/2	1/1	1/1					1/1	
Freon 11	-> see: Trichlorofluoromethane																																			
Freon 11	-> see: Trichlorofluoromethane																																			
Freon 112	-> see: Tetrachlorodifluoroethane																																			
Freon 112	-> see: Tetrachlorodifluoroethane																																			
Freon 113	-> see: Trichlorotrifluoroethane																																			
Freon 113	-> see: Trichlorotrifluoroethane																																			
Freon 114	-> see: Dichlorotetrafluoroethane																																			
Freon 114	-> see: Dichlorotetrafluoroethane																																			
Freon 114 B2	-> see: Dibromotetrafluoroethane																																			
Freon 114 B2	-> see: Dibromotetrafluoroeth																																			

CHEMICALS	thermoplastics																								fluoroplastics			elastomers			metals			COMMENT			
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C	COMMENT						
Ginger	—	—	ground	?	0/0	0/0	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	
Glucose	$C_6H_{12}O_6$	000050-99-7	each	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Glue (bone glue)	—	—	each	—	1/0	1/1	(1)	(1)	1/1	0/0	(2)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	(1)	(1)	1/0	1/0	0/0	(3)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	
Glycerol	$C_3H_8O_3$	000056-81-5	each	Xi	1/1	1/1	1/0	3/3	1/0	1/1	1/0	1/1	1/1	1/1	1/1	2/3	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Glycerin; Propanetriol, 1,2,3-; Trihydroxypropane, 1,2,3-	
Glycine	$C_2H_5NO_2$	000056-40-6	10 %	—	1/1	1/1	1/1	1/1	(1)	0/0	1/1	1/1	0/0	0/0	1/3	1/3	0/0	1/1	1/1	1/1	1/1	1/1	1/0	3/3	0/0	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	(2)	Glycocol; Aminoacetic acid	
Glycolic acid	$C_2H_4O_3$	000079-14-1	37 %	Xn	1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/3	1/0	2/0	1/0	0/0	1/0	1/0	1/3	1/3	1/1							
Glycolic acid	$C_2H_4O_3$	000079-14-1	70 %	C, Xn	1/1	1/1	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	2/0	1/0	3/0	(2)	0/0	(2)	1/3	1/3	1/1								
Glysantin	—	—	—	Xn	1/1	1/1	3/3	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/2	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	antifreeze agent, based on glycol; BASF	
Gum tragacanth	—	009000-65-1	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
HD-Oil motor oil, without aromatics	—	—	—	?	1/0	1/3	1/0	1/1	1/1	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	4/4	(1)	3/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Helium	He	007440-59-7	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	1/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	1/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Henkel-P3-solution	—	—	—	?	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(2)	(2)	1/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	cleaner
Heptane, normal	C_7H_{16}	000142-82-5	—	F, Xn	X	2/3	3/4	1/0	1/2	1/0	3/3	1/2	2/4	4/4	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	4/4	1/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0		
Heptanol, 1-	$C_7H_{16}O$	000111-70-6	—	Xn	0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)		
Heptanone	$C_7H_{14}O$	—	—	(Xn)	X	0/0	0/0	(3)	(4)	(4)	(4)	(2)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(4)	(4)	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	isomer not indicated in the source	
Hexachlorbenzene (HCB)	C_6Cl_6	000118-74-1	—	T	0/0	0/0	(3)	(4)	(0)	(4)	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	(1)	(2)	0/0	4/4	(3)	4/4	0/0	(1)	0/0	0/0							
Hexachlorocyclohexane (alpha-BHC)	$C_6H_6Cl_6$	000319-84-6	—	T	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	4/4	1/0	4/4	0/0	(3)	0/0	0/0									
Hexahydropyridine	-> see: Piperidine			—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—		
Hexaldehyde, n-	$C_6H_{12}O$	000066-25-1	—	F, Xi	X	0/0	0/0	0/0	(4)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)		
Hexamethylenetetramine	$C_6H_{12}N_4$	000100-97-0	—	F, Xn	X	0/0	0/0	(2)	(2)	1/0	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	(1)	(2)	(2)	(2)	(3)	0/0	(1)	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	Methenamine; Hexamine; Urotropin	
Hexane, n-	C_6H_{14}	000110-54-3	—	F, Xn	X	2/3	4/4	1/0	(2)	1/0	3/4	1/1	2/3	4/4	1/2	2/4	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	0/0	0/0		
Hexanedioic acid	-> see: Adipic acid			—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—		
Hexanetriol	$C_6H_{14}O_3$	—	100 %	?	1/1	1/1	(2)	(2)	(1)	0/0	(1)	1/1	1/0	0/0	1/1	3/3	1/1	0/0	(1)	1/1	(1)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	isomer not indicated in the source	
Hexene, 1-	C_6H_{12}	000592-41-6	—	F, Xn	X	0/0	0/0	1/0	(2)	(1)	(4)	(1)	(3)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	1/0	3/3	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	Butyl ethylene; Hexylene
Hexyl alcohol	$C_6H_{14}O$	000111-27-3	—	Xn	1/0	1/0	(2)	(2)	(1)	0/0	(1)	1/2	0/0	3/0	1/0	3/0	1/3	0/0	(1)	1/0	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	(1)	0/0		
Honey	—	—	—	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	(1)	1/1	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0				
Hydraulic fluids, HFA	—	—	50°C	?	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0									
Hydraulic fluids, HFB	—	—	50°C	?	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	4	0	1	0	(2)	0	0									
Hydraulic fluids, HFC	—	—	60°C	?	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	1	0	(2)	0	0									
Hydraulic fluids, HFD-R	—	—	100°C	?	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	4	0	(2)	0	0									
Hydraulic fluids, HFD-S	—	—	100°C	?	0	0	0	0	0	0	0	(3)	0	0	0	0	0	0	0	(1)	0	0	0	4	0	(2)	0	0									
Hydraulic oil (based on mineral oil)	—	—	—	?	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	4/4	(1)	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Hydrazine	N_2H_4	000302-01-2	10 %	T	X	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	Diamide; Diamine; Nitrogen hydride	
Hydrazine hydrate	N_2H_4O	010217-52-4	aqueous	(T, C)	(X)	1/1	1/0	4/4	(4)	0/0	0/0	2/0	1/1	0/0	0/0	1/0	0/0	0/0	1/0	1/0	1/3	1/0	3/4	4/4	0/0	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Hydrocyanic acid, sodium salt	-> see: Sodium cyanide			—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—	—		
Hydrogen	H_2	001333-74-0	techn. pure	F+	X	1/1	1/1	1/0	1/0	0/0	0/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Hydrogen bromide	HBr	010035-10-6	40 %	C	1/0	1/1	4/4	4/4	(4)	4/4	4/4	1/1	4/4	0/0	1/1	3/3	0/0	0/0	1/1	1/1	1/1	3/0	1/0	4/4	0/0	(4)	(4)	(4)	(4)	(4)	(4)	(4)	(4)	(4)	(4)	0/0	
Hydrogen bromide	HBr	010035-10-6	50 %	C	1/1	1/2	4/4	4/4	(4)	4/4	4/4	1/2	4/4	0/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1	3/0	1/0	4													

----- thermoplastics ----- | --- fluoroelastics --- | --- elastomers --- | ----- metals -----

CHEMICALS	FORMULA		CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE											METALS											COMMENT				
	HDPE	LDPE				PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM	NBR	SI	AL	V2A	V4A		Haselloy C			
Molasses	---	---	---	---	---	1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	1/0	3/4			
Molasses wort	---	---	---	---	?	1/1	1/1	1/0	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)			
Monochlorobenzene (MCB)	-> see: Chlorobenzene			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---			
Monochloroethane	C ₂ H ₅ Cl	000075-00-3	---	---	F+, Xn	X	3/3	3/4	1/0	4/4	0/0	3/4	1/0	3/4	4/4	4/4	4/4	4/4	1/1	1/1	1/0	1/1	4/4	3/0	4/4	0/0	(3)	1/1L	1/1L	0/0	Ethyl chloride; Chloroethane, 1-	
Morpholine	C ₄ H ₉ NO	000110-91-8	---	techn. pure	C, Xn	X	1/1	1/1	(3)	(3)	0/0	0/0	(2)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/3	3/0	2/3	4/4	0/0	1/0	(1)	(1)	0/0	
Motor oil	---	---	---	---	?	---	0/0	0/0	1/0	(2)	(1)	0/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/1	4/4	1/0	1/0	0/0	1/1	1/1			
Mowilith D	---	---	---	---	?	---	1/0	0/0	(2)	0/0	(2)	0/0	(2)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(2)	(2)	(2)	0/0	(2)	(1)	(1)	0/0	dispersion of polyvinyl acetate; Clariant
Muscat	---	---	---	ground	?	---	0/0	0/0	(2)	4/4	(2)	0/0	(2)	4/4	0/0	0/0	0/0	3/3	0/0	(1)	(1)	(2)	(2)	(2)	(2)	0/0	(1)	(1)				
Mustard	---	---	---	---	---	---	0/0	0/0	(2)	1/0	(1)	0/0	1/0	1/1	1/1	0/0	0/0	1/1	0/0	1/1	(1)	(1)	(2)	1/0	1/0	0/0	(2)	1/0L	1/0L			
Naphtha	---	008032-32-4	---	---	(Xn)	---	1/3	3/4	1/0	(2)	(1)	1/0	1/0	1/3	3/0	1/0	1/0	4/4	0/0	(1)	1/1	1/1	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	petroleum ether	
Naphthalene	C ₁₀ H ₈	000091-20-3	---	100 %	F, Xn	X	0/0	1/3	1/0	(3)	0/0	0/0	1/2	1/3	3/4	1/0	4/4	4/4	1/4	0/0	(1)	1/1	1/3	4/4	1/1	4/4	0/0	1/1	1/1	1/1	0/0	
Naphthalene (in alcohol)	---	---	---	---	F, Xn	X	1/4	1/4	(2)	(3)	0/0	0/0	1/2	1/3	3/4	0/0	0/0	0/0	3/4	0/0	(1)	1/1	(2)	4/4	(3)	0/0	(1)	(1)	(1)	0/0		
Neon	Ne	007440-01-9	---	---	---	---	0/0	0/0	1/0	(1)	1/1	0/0	1/1	(1)	0/0	0/0	0/0	0/0	0/0	1/1	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1			
Nickel acetate	C ₄ H ₇ NO ₄	000373-02-4	---	aqueous	(T, N)	---	1/1	1/1	(3)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/0	0/0	4/4	0/0	0/0			
Nickel dichloride	NiCl ₂	00718-54-9	---	saturated	T	---	1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	0/0	1/1	1/1	0/0	0/0	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel dichloride	NiCl ₂	00718-54-9	---	aqueous	T	---	1/1	1/1	(3)	(2)	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	2/0L	2/0L	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	---	saturated	Xn	---	1/1	1/1	1/0	1/0	(1)	1/0	2/0	1/1	1/1	0/0	1/1	1/3	1/1	0/0	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1		
Nickel sulfate	NiSO ₄	007786-81-4	---	aqueous	Xn	---	1/1	1/1	(3)	1/0	(1)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	1/1	1/1	1/1	
Nickelous nitrate	Ni(NO ₃) ₂	013138-45-9	---	saturated	(O, Xn)	---	1/1	1/1	(3)	(2)	(1)	1/0	(2)	1/0	1/0	1/0	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	1/0	1/0	1/1	
Nicotine	C ₁₀ H ₁₄ N ₂	000054-11-5	---	---	T+	---	1/0	1/0	(3)	(3)	0/0	0/0	(2)	1/0	1/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	1/0	0/0	(1)	(1)	(1)	0/0	
Nicotinic acid	C ₆ H ₇ NO ₂	000059-67-6	---	diluted	Xi	---	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/0	0/0	0/0	1/1	0/0	0/0	0/0	1/1	(1)	(2)	(2)	(3)	(2)	0/0	(3)	0/0	0/0	0/0	
Nitric acid	HNO ₃	007697-37-2	---	1-10 %	C	---	1/1	1/1	4/4	1/2	(2)	1/1	4/4	1/1	2/4	1/3	1/2	0/0	1/3	1/1	1/1	1/1	2/0	1/1	4/4	0/0	3/4	1/1	1/1	1/1		
Nitric acid	HNO ₃	007697-37-2	---	50 %	C+	---	2/4	3/4	4/4	4/4	(2)	2/4	4/4	3/4	4/4	2/3	2/3	0/0	0/3	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2	
Nitric acid	HNO ₃	007697-37-2	---	66 %	C+	---	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/2	1/2	1/2		
Nitric acid	HNO ₃	007697-37-2	---	100 %	O, C+	---	4/4	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	0/0	4/4	0/0	4/4	0/0	0/0	1/1	4/4	4/4	4/4	4/4	0/0	1/1	2/3	3/3	?	
Nitric acid	HNO ₃	007697-37-2	---	70 %	O, C+	---	2/4	3/4	4/4	4/4	(4)	2/3	4/4	4/4	4/4	3/4	0/0	0/0	1/1	1/1	1/1	1/1	4/4	2/3	4/4	0/0	4/4	1/2	1/2	1/2		
Nitric acid	-> see: Ammonium nitrate			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Nitric acid, magnesium salt	-> see: Magnesium nitrate			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Nitric acid, potassium salt	-> see: Potassium nitrate			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Nitro benzoic acid	C ₇ H ₅ NO ₄	---	---	---	(Xn)	---	1/0	1/0	(3)	(3)	0/0	0/0	(3)	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	(3)	(2)	0/0	(3)	0/0	0/0		isomer not indicated in the source
Nitro reducer	---	---	---	---	?	X	0/0	0/0	3/0	(4)	0/0	(4)	(3)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	4/4	0/0	(1)	(1)		solvent cleaner mixture	
Nitrobenzene	C ₆ H ₅ NO ₂	000098-95-3	---	---	T	---	3/4	4/4	4/4	4/4	1/0	4/4	3/0	2/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/1	1/1	4/4	4/4	4/4	0/0	1/1	1/1	1/1		
Nitroethane	C ₂ H ₅ NO ₂	000079-24-3	---	---	Xn	X	0/0	0/0	(3)	(4)	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)			
Nitrogen	N ₂	007727-37-9	---	---	---	---	0/0	0/0	1/0	1/1	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	0/0	1/1	1/1	1/1				
Nitrogen hydride	-> see: Hydrazine			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Nitrogen tetroxide	N ₂ O ₄	010544-72-6	---	---	(O), T+, C	---	0/0	0/0	3/0	(3)	1/0	0/0	4/4	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	4/4	4/4	0/0	(2)	(1)	(1)			
Nitroglycerine	C ₃ H ₅ (NO ₃) ₃	000055-63-0	---	diluted	(E, T+)	---	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	3/0	4/4	0/0	0/0	(1)	(1)	(3)	1/0	1/0	4/4	0/0	0/0	0/0	0/0	0/0	
Nitrohydrochloric acid	HNO ₃ + HCl	008007-56-5	---	---	C	---	4/4	4/4	4/4	4/4	3/3	4/4	4/4	4/4	4/4	4/4	3/4	1/1	(2)	1/1	3/0	4/4	4/4	0/0	4/4	4/4	4/4	4/4	4/4	4/4		agua regia: mixture of hydrochloric acid and nitric acid
Nitropropane	C ₃ H ₇ NO ₂	---	---	---	(T)	---	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(1)	(1)		isomer not indicated in the source	
Nitroses gases	---	---	---	diluted	T	---	1/1	0/0	3/0	4/4	0/0	0/0	4/4	1/4	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	3/0	3/0	4/4	0/0	(2)	(1)	(1)	0/0	nitrogen monoxide + nitrogen dioxide
Nitrotoluene	C ₇ H ₇ NO ₂	001321-12-6	---	techn. pure	T	---	1/3	1/3	4/4	4/4	1/0	(4)	3/0	1/3	4/4	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/1	4/4	4/4	4/4	0/0	(1)	1/1	1/1		
Nitrous acid, sodium salt	-> see: Sodium nitrite			---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---	---		
Nitrous oxide	N ₂ O	010024-97-2	---	---	(O)	---	0/0	0/0	(2)	(2)	(1)	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	2/0	1/0	1/0	0/0	1/1	(1)	(1)		nitric oxide
Nonanol	-> see: Nonyl alcohol																															

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics												fluoroplastics		elastomers		metals		COMMENT								
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF		EPDM	FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C
Oxalic acid	C ₂ H ₂ O ₄ x 2H ₂ O	000144-62-7		Xn		1/1	1/1	3/4	1/0	0/0	1/1	4/4	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/3	1/0	1/1	3/3	0/0	1/0	2/3	1/3	1/3			
Oxygen	O ₂	007782-44-7	techn. pure	O		1/3	1/3	2/0	1/0	(1)	0/0	1/0	1/3	1/0	0/0	1/1	1/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	(2)	(1)	(1)	0/0	
Ozone	O ₃	010028-15-6	(O, T)	(O, T)		3/4	3/4	4/4	1/2	0/0	1/1	4/4	3/4	2/2	1/1	1/2	0/0	1/1	1/1	1/1	(1)	1/3	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Ozone-air-mixture	—	—	(O, T)	(O, T)		0/0	0/0	4/4	(2)	0/0	0/0	4/4	3/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	1/0	1/0	4/4	0/0	(2)	0/0	0/0	0/0	
Palm kernel oil	—	008023-79-8				0/0	0/0	1/0	(2)	1/0	0/0	(2)	1/3	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1	1/1		
Palm oil	—	008002-75-3				1/3	0/0	1/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	1/0	0/0	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/1	0/0	(1)	1/1	1/1		
Palmitic acid	C ₁₆ H ₃₂ O ₂	000057-10-3	techn. pure	Xi		3/3	2/2	1/1	(2)	1/0	0/0	1/0	3/4	1/1	0/0	1/1	3/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	3/3	0/0	1/1	1/1	1/1		
Paraffin wax	—	008002-74-2	melted	(—)		0	0	0	(2)	0	0	(2)	0	0	0	0	0	0	0	(1)	1	0	4	(2)	1	0	1	1	1		
Paraffin-emulsion	—	—	?	?		1/3	0/0	1/0	(2)	(2)	0/0	(2)	1/3	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/0	1/1	0/0	(2)	(1)	(1)	0/0		
Paraffins	C _n H _{2n+2}	—	100 %	?		1/0	1/1	1/0	1/0	1/0	1/1	1/1	1/0	1/0	1/0	1/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/3	0/0	1/1	1/1	1/1	1/1		
Paraformaldehyde	(CH ₂ O) _n ·H ₂ O	030525-89-4		F, T	X	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	1/0	3/3	0/0	(1)	(1)	(1)	0/0		
Peanut oil	—	008002-03-7				0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/1	1/1	0/0	0/0	0/0	0/0	(1)	1/1	(1)	4/4	1/0	1/0	0/0	(1)	(1)	(1)	0/0		
Pectin	—	009000-69-5	aqueous			1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Pectin	—	009000-69-5				1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1		
Pelargonic alcohol	-> see: Nonyl alcohol																														
Penicillin	—	—		Xn		(1)	(1)	(2)	(1)	(1)	0/0	(1)	(2)	0/0	0/0	0/0	0/0	1/1	(1)	1/1	(1)	(1)	(2)	(1)	(2)	0/0	(1)	(1)	(1)	antibiotic	
Pentachlorobiphenyl	C ₁₂ H ₂ Cl ₅	—		Xn		0/0	0/0	1/0	(3)	0/0	(2)	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	4/4	3/0	4/4	0/0	(1)	0/0	0/0				
Pentamethyleneimine	-> see: Piperidine																														
Pentane, normal	C ₅ H ₁₂	000109-66-0		F	X	1/3	1/3	1/0	1/0	(1)	(3)	1/0	(3)	3/0	0/0	0/0	1/0	0/0	(1)	(1)	(1)	4/4	1/0	1/2	0/0	1/1	1/1	1/1			
Pentanethiol, 1-	C ₅ H ₁₂ S	000110-66-7		Xn	X	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	4/4	(3)	(4)	0/0	(2)	(1)	(1)		
Pentanol, 1-	C ₅ H ₁₂ O	000071-41-0		Xn	X	1/1	1/2	1/0	1/0	1/0	2/3	1/0	1/1	1/3	3/0	2/3	0/0	0/4	1/1	1/1	1/1	1/1	3/0	2/4	3/0	0/0	1/2	1/1	1/1	0/0	
Pentanone, 3-	C ₅ H ₁₀ O	000096-22-0		F		2/2	2/3	(3)	4/4	(4)	2/3	1/0	2/2	4/4	4/4	4/4	3/0	0/4	2/3	1/1	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	0/0		
Pentyl alcohol, n-	-> see: Pentanol, 1-																														
Pepper	—	—	ground	?		0/0	0/0	(2)	1/0	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(1)	(1)	(1)		
Perchloric acid	HClO ₄	007601-90-3	70 %	E, O, C+		2/4	3/4	4/4	4/4	(4)	2/4	4/4	4/4	2/3	4/4	3/4	4/4	0/0	1/2	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	0/0	0/0	?	
Perchloric acid	HClO ₄	007601-90-3	20 %	Xi		0/0	1/3	4/4	3/0	0/0	4/4	1/3	0/0	0/0	1/3	3/0	0/0	0/0	1/1	1/1	1/1	2/0	1/1	4/4	0/0	4/4	0/0	0/0	1/1		
Perchlorobutadiene	C ₄ Cl ₆	000087-68-3		T		0/0	0/0	(3)	4/4	0/0	(4)	1/0	(3)	4/4	0/0	0/0	0/0	0/0	(1)	(2)	(3)	4/4	1/0	4/4	0/0	(3)	0/0	0/0			
Perchloroethylene	-> see: Tetrachloroethylene																														
Perfluorocyclobutane	C ₄ F ₈	000115-25-3		?		0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	3/0	1/0	0/0	(3)	0/0	0/0			
Perfumes	—	—		?		3/0	3/0	1/0	(3)	1/0	0/0	(2)	1/0	4/4	0/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	(3)	(2)	(3)	0/0	(1)	(1)	(1)		
Permanganic acid, potassium salt	-> see: Potassium permanganate																														
Petroleum	—	008002-05-9		(Xn)		0/0	0/0	1/0	(3)	1/0	0/0	1/0	1/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	1/1	4/4	1/0	3/3	0/0	(1)	(1)	(1)	0/0	
Petroleum ether	—	008032-32-4	techn. pure	(F, Xn)	X	1/3	1/3	1/0	3/0	1/0	1/0	1/1	1/3	4/4	1/0	1/1	3/3	3/3	0/0	(1)	1/1	1/1	4/4	1/0	1/3	0/0	1/1	1/1	1/1		
Phenacetin	C ₁₀ H ₁₃ NO ₂	000062-44-2		Xn		0/0	0/0	0/0	0/0	0/0	(2)	1/2	0/0	0/0	0/0	1/1	0/0	0/0	(1)	(1)	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)			
Phenethyl alcohol	C ₈ H ₁₀ O	000060-12-8		Xn		0/0	0/0	3/0	4/4	0/0	0/0	(2)	1/0	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(2)	(3)	(2)	4/4	0/0	(1)	(1)	(1)		
Phenetole	-> see: Ethoxybenzene																														
Phenol	C ₆ H ₆ O	000108-95-2	10 %	T		1/1	1/1	4/4	4/4	4/4	1/0	4/4	1/1	4/4	4/4	1/3	3/3	3/3	0/0	1/0	1/1	1/1	4/4	2/3	4/4	0/0	1/1	1/2	1/1	0/0	
Phenol	C ₆ H ₆ O	000108-95-2	100 %	T, C		2/3	3/3	4/4	4/4	4/4	1/1	4/4	1/2	4/4	3/3	4/4	3/0	4/4	1/1	1/1	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	0/0	
Phenolic resin mass	—	—		?		1/1	1/1	(3)	(3)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	(4)	(3)	(3)	0/0	(2)	(1)	(1)	0/0	
Phenyl chloride	-> see: Chlorobenzene																														
Phenyl methyl ketone	-> see: Acetophenone																														
Phenylethanone, 1-	-> see: Acetophenone																														
Phenyldiazine	C ₆ H ₈ N ₂	000100-63-0	techn. pure	T		3/0	0/0	(3)	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/3	4/4	0/0	(2)	0/0	0/0	0/0	
Phenyldiazine hydrochloride	C ₆ H ₈ N ₂ ·HCl	000059-88-1		T		0/0	0/0	(3)	(2)	0/0	0/0	(3)	1/3	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(3)	1/3	1/3	0/0	(4)	(4L)	(4L)		
Phenylsulfonate	—	070528-83-5		?		0/0	1/1	0/0	0/0	0/0	0/0	0/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	
Phosgene	COCl ₂	000075-44-5	liquid	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(3)	(3)	1/0	3/0	0/0	(3)	3/4	3/4	0/0	Carbonyl chloride; Chloroformyl chloride
Phosgene	COCl ₂	000075-44-5	gaseous	T+, C		0/0	0/0	1/0	(3)	0/0	0/0	(2)	3/4	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	(3)	3/0	0/0	(3)	3/4	3/4	0/0		
Phosphates	—	—	aqueous	?		1/1	1/1	0/0	0/0	(1)	0/0	(2)	3/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(2)	0/0	0/0	(1)	(1)		
Phosphine	PH ₃	007803-51-2	concentrated	F+, T+	X	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	1/0	4/4	0/0	(1)	0/0	0/0	0/0	
Phosphoric acid	H ₃ PO ₄	007664-38-2	30 %	C		1/1	1/1	4/4	1/0	0/0	0/0	4/4	1/1	1/1	0/0	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	4/4	1/3	1/2	1/1	
Phosphoric acid	H ₃ PO ₄	007664-38-2	85 %	C		1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	1/1	1/2	1/1	1/1	1/1	1/1	3/0	1/1	4/4	0/0	4/4	2/4	1/3	1/1	
Phosphoric acid	H ₃ PO ₄	007664-38-2	1-5 %	Xi		1/1	1/1	(3)	1/1	1/0	1/1	3/4	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	(4)	1/1	1/1	1/1	
Phosphoric acid	H ₃ PO ₄	007664-38-2	20%	Xi		1/1	1/1	4/4	(2)	0/0	0/0	4/4	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	3/3						

			thermoplastics														fluoroplastics			elastomers			metals														
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE														PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FKM / FKM	NBR	SI	AL	V2A	V4A	Hasselloy C	COMMENT			
					HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE																	FEP	PTFE	PVDF
Pineapple juice	—	—	—	—	—	1/1	1/1	1/0	(2)	1/0	(0)	(2)	1/0	(0)	(2)	1/0	(0)	(0)	0	0	0	0	0	1/1	1/1	1/1	1/1	(1)	(1)	(2)	(1)	(0)	(2)	(1)	(1)	(1)	
Pink	—	—	ground	?	—	0/0	0/0	(2)	4/4	(1)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	4/4	0/0	(1)	1/1	(2)	(2)	(2)	(2)	(2)	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)	0/0		
Piperidine	C ₅ H ₁₁ N	000110-89-4		F, T, C	—	0/0	0/0	(3)	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	(1)		Hexahydropyridine; Azacyclohexane; Pentamethylenimine		
Plasticiser	—	—	—	?	—	1/3	1/3	(2)	(3)	0/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	3/3	0/0	(1)	(1)	0/0	(2-3)	0/0	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)					
Polish remover	—	—	?	?	(X)	0/0	0/0	(2)	4/4	0/0	(2)	1/3	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(3)	(3)	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)	0/0				
Polyester resins	—	—	—	(Xn)	(X)	3/4	3/4	1/0	4/4	1/0	0/0	(2)	3/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3	4/4	0/0	(1)	(1)	(1)	(1)	(1)	(1)					
Polyethylene glycol	HO-(C ₂ H ₄ O) _n -H	025322-68-3	100 %	(—)	—	1/1	1/1	(3)	0/0	0/0	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	(2-3)	(2)	(3)	0/0	(1)	(1)	(1)	(1)	(1)	0/0					
Polyoxymethylene	-> see: Paraformaldehyde																																				
Polyran M25 N	—	—	80°C	?	—	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	(1)	lubricating oil
Polyran M400	—	—	80°C	?	—	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	0	(1)	(1)	lubricating oil
Polysolvan O	C ₆ H ₁₂ O ₂	007397-62-8	100 %	Xi	—	0/0	1/1	(2)	(3)	1/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	0/0	0/0	0/0	(3)	0/0	(1)	(1)	(1)	(1)				solvent cleaner, butyl glycolate; Celanese AG			
Potassium acetate	C ₂ H ₃ KO ₂	000127-08-2	aqueous	Xi	—	1/1	1/1	1/0	(1)	(2)	0/0	1/1	1/1	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/0	3/3	0/0	1/3	1/1	1/1	0/0					
Potassium bisulfate	KHSO ₄	007646-93-7	aqueous	(C)	—	1/1	1/1	4/4	1/0	(2)	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	1/1					
Potassium bisulfate	KHSO ₄	007646-93-7		C	—	1/1	1/1	4/4	1/0	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/0	4/4	4/4	?						
Potassium bitartrate	C ₄ H ₄ KO ₆	000868-14-4	saturated	Xi	—	1/1	1/1	(2)	(2)	0/0	0/0	(2)	1/1	0/0	1/0	1/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	(2)	(1)	(1)	(0)	(4)	1/3	1/2	0/0						
Potassium borate	KBO ₂	012228-88-5	10 %	(Xn)	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/1	0/0	(3)	0/0	0/0	0/0					
Potassium borate	KBO ₂	012228-88-5	aqueous	(Xn)	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/0	1/0	0/0	(3)	0/0	0/0	0/0						
Potassium bromate	KBrO ₃	007758-01-2	saturated	O, T	—	1/3	1/3	(2)	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0							
Potassium bromate	KBrO ₃	007758-01-2	aqueous	O, T	—	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/1	0/0	(2)	0/0	0/0	0/0							
Potassium bromide	KBr	007758-02-3	each	Xn	—	1/1	1/1	3/0	1/0	(1)	1/0	1/1	1/1	0/0	1/3	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	1/0	1/0	1/0L	1/0L	1/1							
Potassium carbonate	K ₂ CO ₃	000584-08-7	saturated	Xn	—	1/1	1/1	1/1	3/3	(2)	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1								
Potassium carbonate	K ₂ CO ₃	000584-08-7	aqueous	Xn	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	4/4	1/1	1/1	1/1								
Potassium chlorate	KClO ₃	003811-04-9	saturated	O, Xn	—	1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1								
Potassium chlorate	KClO ₃	003811-04-9	aqueous	O, Xn	—	1/1	0/0	1/0	(2)	0/0	0/0	2/0	1/1	1/0	0/0	1/1	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	1/1	1/1	1/1	1/1								
Potassium chloride	KCl	007447-40-7	aqueous	Xi	—	1/1	1/1	1/0	1/0	1/0	1/1	1/1	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/3	1/1L	1/1L	1/1						
Potassium chromate	K ₂ CrO ₄	007789-00-6	saturated	T	—	1/0	1/1	2/0	(2)	0/0	1/0	(2)	1/1	1/1	0/0	1/1	1/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1							
Potassium chromate	K ₂ CrO ₄	007789-00-6	aqueous	T	—	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1									
Potassium cyanide	KCN	000151-50-8	saturated	T+	—	1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	4/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1							
Potassium cyanide	KCN	000151-50-8	aqueous	T+	—	1/1	1/1	1/0	4/4	0/0	0/0	3/0	1/1	0/0	0/0	1/3	1/4	0/0	0/0	1/1	1/1	1/3	1/0	1/1	3/3	0/0	3/4	1/0	1/0	1/1							
Potassium dichromate	K ₂ Cr ₂ O ₇	007778-50-9	saturated	T	—	1/1	1/0	4/4	3/0	3/0	1/0	3/0	1/1	1/3	0/0	1/3	1/0	1/3	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1							
Potassium dichromate	K ₂ Cr ₂ O ₇	007778-50-9	aqueous	T	—	0/0	0/0	3/0	1/0	3/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	2/0	3/3	0/0	1/1	1/1	1/1	1/1								
Potassium ferricyanide	C ₆ FeK ₃ N ₆	013746-66-2	each	Xn	—	1/1	1/1	1/0	(1)	(1)	0/0	2/0	1/1	1/1	0/0	1/3	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1	1/1							
Potassium ferrocyanide	C ₆ FeK ₄ N ₆ x 3H ₂ O	014459-95-1	saturated	—	—	1/1	1/1	1/0	(2)	(1)	0/0	2/0	1/1	0/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	(1)	1/1	1/1									
Potassium ferrocyanide	C ₆ FeK ₄ N ₆ x 3H ₂ O	014459-95-1	diluted	—	—	1/0	1/1	1/0	(1)	(1)	0/0	2/0	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	1/1									
Potassium fluoride	KF	007789-23-3		T	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	1/0	(1)	0/0	1/1	1/1	1/1	0/0									
Potassium hydrogen carbonate	CHKO ₃	000298-14-6	saturated	—	—	1/1	1/1	1/0	(2)	(2)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	4/4	(1)	(1)	1/1								
Potassium hydroxide	KHO	001310-58-3	10 %	C+	—	1/1	1/1	1/0	4/4	4/4	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1							
Potassium hydroxide	KHO	001310-58-3	30 %	C+	—	1/1	1/1	1/3	4/4	4/4	1/0	(3)	1/1	1/0	1/0	1/3	1/0	0/0	0/0	1/1	(2)	1/0	4/4	3/3	0/0	4/4	1/1	1/1	1/1								
Potassium hydroxide	KHO	001310-58-3	50 %	C+	—	1/1	1/1	1/3	4/4	4/4	1/1	3/0	1/1	2/2	1/1	1/3	1/0	1/3	1/1	1/1	1/1	3/3	1/0	4/4	3/4	0/0	4/4	1/1	1/1	1/1							
Potassium hydroxide	KHO	001310-58-3	concentrated	C+	—	1/1	1/1	1/0	4/4	4/4	1/1	3/0	1/1																								

				thermoplastics												fluoroplastics			elastomers			metals			COMMENT									
CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM		NBR	SI	AL	V2A	V4A	Haselloy C			
Propanone, 2-	-> see: Acetone																																	
Propargyl alcohol	C_3H_4O	000107-19-7	7 %	Xn		1/1	1/1	(3)	1/0	0/0	0/0	(2)	1/1	0/0	0/0	1/1	1/0	0/0	0/0	(1)	1/1	1/3	1/0	1/1	1/1	0/0	1/0	(1)	(1)	0/0				
Propenenitrile, 2-	-> see: Acrylonitrile																																	
Propenyl alcohol	-> see: Allyl alcohol																																	
Propionic acid	$C_2H_3O_2$	000079-09-4	50 %	C, F	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/1	4/4	4/4	1/3	3/3	0/0	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	1/1	(1)	(1)	1/1				
Propionic acid	$C_2H_3O_2$	000079-09-4		C, F+	X	1/3	1/3	3/3	4/4	0/0	0/0	4/4	1/3	4/4	4/4	4/4	4/4	0/0	0/0	1/0	1/1	1/1	4/4	3/0	4/4	0/0	1/1	1/2	1/1	1/1				
Propyl acetate, normal	$C_5H_{10}O_2$	000109-60-4		F	X	0/0	0/0	(1)	4/4	0/0	(4)	1/0	(2)	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	3/0	4/4	4/4	0/0	(1)	(1)	(1)						
Propyl alcohol	C_3H_7O	000071-23-8		F	X	1/1	1/1	1/0	1/0	0/0	0/0	1/1	3/0	0/0	2/2	3/3	1/4	0/0	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/1	(1)	(1)	0/0					
Propyl carbinol	-> see: Butyl alcohol, normal																																	
Propyl nitrate	$C_3H_7NO_2$	000627-13-4		(E, Xn)	(X)	0/0	0/0	(3)	(3)	0/0	0/0	(3)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	3/0	4/4	4/4	0/0	(2)	(1)	(1)					
Propylamine, n-	C_3H_7N	000107-10-8		F, C, Xn	X	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(1)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	4/4	4/4	0/0	(1)	(1)	(1)					
Propylene	C_3H_6	000115-07-1		F+	X	1/1	1/1	1/0	(3)	1/0	0/0	1/0	1/1	4/4	0/0	3/4	4/4	0/0	(1)	1/1	(1)	4/4	1/0	4/4	0/0	1/1	1/1	1/1						
Propylene glycol	$C_3H_8O_2$	000057-55-6				1/1	1/1	4/4	2/3	(2)	1/1	1/0	1/1	1/1	2/2	3/4	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/3	0/0	1/1	(1)	(1)	1/1				
Propylene oxid	C_3H_6O	000075-56-9		F+, T	X	1/1	1/2	(3)	2/3	0/0	1/2	(2)	1/2	4/4	2/2	3/4	0/0	4/4	3/4	1/1	1/0	1/4	3/0	4/4	4/4	0/0	(1)	(1)	0/0			Epoxypropane, 1,2;- Methylloxirane; Methyl ethylene oxide		
Pydraul C (312, 540)	—	—		(Xn)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	4/4	1/0	4/4	0/0	0/0	(1)	(1)				based on phosphoric ester; Monsanto		
Pydraul E (29, 30, 50, 65, 90, 11)	—	—		(Xn)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	0/0	1/0	1/0	4/4	0/0	0/0	(1)	(1)				based on phosphoric ester; Monsanto		
Pyridine	C_5H_5N	000110-86-1		F, Xn	X	1/3	0/2	1/0	4/4	0/0	0/2	1/1	3/3	4/4	4/4	4/4	4/4	1/1	(2)	1/1	1/3	4/4	4/4	4/4	0/0	1/1	1/1	1/1	0/0			Azine; Azabenzene		
Pyrogallic acid	$C_6H_6O_3$	000087-66-1		Xn	0/0	0/0	1/0	(3)	0/0	0/0	3/4	1/0	3/0	0/0	0/0	0/0	0/0	1/3	0/0	(1)	(1)	1/1	(3)	(3)	(3)	0/0	1/1	1/1	1/1	1/1				
Pyroigneous oil	—	008001-20-5		—	0/0	0/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	4/4	(1)	1/0	0/0	1/1	(1)	(1)					Azole; Imidole	
Pyrrole	C_4H_5N	000109-97-7		Xn	X	0/0	0/0	(3)	(4)	0/0	0/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(3)	4/4	4/4	4/4	0/0	(1)	(1)	(1)						
Quinine	$C_{20}H_{24}N_2O_6$	000130-95-0		Xn	1/1	1/1	(2)	(2)	(2)	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	0/0	(2)	(1)	(1)	0/0				
Quinol	-> see: Hydroquinone																																	
Ramasit	—	—		?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	for moisture-proofing of textiles; BASF
Resorcinol	$C_6H_4O_2$	000108-46-3	5 %	—	1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	2/4	0/0	3/3	1/3	1/1	(1)	(3)	(3)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0	0/0			
Resorcinol	$C_6H_4O_2$	000108-46-3	saturated	Xn	1/1	1/1	4/4	2/3	0/0	1/1	(3)	1/1	2/3	4/4	3/4	0/0	0/0	1/1	(1)	(1)	(3)	(3)	(3)	(3)	(3)	0/0	(2)	0/0	0/0	0/0				
Roaster off-gas	—	—	each	(T)	0/0	0/0	(2)	0/0	0/0	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	4/4	0/0	(4)	(2)	(2)	0/0					
Rose oil	—	008007-01-0		?	0/0	0/0	(2)	(3)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	0/0	0/0	3/0	0/0	(1)	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)					
Rum ether	—	008030-89-5		?	0/0	0/0	(2)	(3)	0/0	(2)	(2)	4/4	0/0	0/0	1/0	0/0	0/0	(1)	(1)	(3)	(3)	(4)	(3)	0/0	(1)	(1)	(1)							
Sagrotan	—	—	liquid	?	1/2	1/3	0/0	3/0	0/0	0/0	(3)	1/3	3/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	1/0	3/0	0/0	(2)	(1)	(1)				disinfectant; Schülke & Mayr		
Salicyl acid	$C_7H_6O_3$	000069-72-7	saturated	(Xn, Xi)	1/1	1/1	1/0	1/2	1/0	1/1	4/4	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1					
Salicyl acid	$C_7H_6O_3$	000069-72-7	powder	Xn, Xi	1/1	1/1	1/0	1/2	(1)	1/2	(3)	1/1	1/1	1/1	2/3	0/0	1/1	1/1	1/0	1/1	1/0	1/0	3/3	0/0	1/0	1/0	1/0	1/1						
Salicyldehyde	$C_7H_6O_2$	000090-02-8		Xn, Xi	1/1	1/2	(3)	2/3	0/0	1/2	(3)	1/2	4/4	3/3	3/4	0/0	0/0	1/4	1/1	(1)	(3)	(3)	(3)	4/4	0/0	(2)	(1)	(1)	1/1					
Salt spring	NaCl	007647-14-5	saturated	—	1/1	1/1	1/0	(1)	(1)	0/0	1/2	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/3	1/2	0/0				
Salt water, sea water	—	—		—	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1					
Salt peter	-> see: Potassium nitrate																																	
Saturated steam condensate	—	—		?	0/0	0/0	(2)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(2)	(2)	(2)	(2)	0/0	(2)	1/1	1/1						
Sea water	—	—		—	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/3L	1/2L	1/1				
Silicofluoric acid	H_2SiF_6	016961-83-4	32 %	C	1/1	1/1	4/4	1/0	4/4	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	3/0	2/2	3/4	0/0	4/4	(2)	1/1	1/1					
Silicone greases	—	—		(—)	0/0	0/0	1/0	1/0	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	1/0	1/0	1/1	0/0	1/1	1/1	1/1						
Silicone oil	—	—		?	1/1	1/1	1/0	1/0	1/0	1/1	1/1	3/3	1/0	1/4	0/0	1/1	0/0	1/1	1/1	(1)	(1)	1/0	1/1	1/1	0/0	1/1	1/1	1/1	1/1				polysiloxane	
Silver acetate	$C_2H_3AgO_2$	000563-63-3		Xi	1/1	1/1	(2)	1/2	(2)	1/1	(2)	1/1	2/2	1/1	2/2	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	(3)	0/0	(4)	0/0	0/0	0/0					
Silver cyanide	CAgN	000506-64-9		T	1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	(1)	(1)	(1)	(1)	(3)	0/0	(4)	0/0	0/0	0/0				
Silver nitrate	AgNO ₃	007761-88-8	aqueous	C	1/1	0/0	1/0	1/1	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/1	3/3	0/0	4/4	1/1	1/1						

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics											fluoroelastics		elastomers		metals				COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM		FPM / FKM	NBR	SI	AL	V2A	V4A	Haselloy C
Sodium carbonate	Na ₂ CO ₃	000497-19-8		Xi	1/1	1/1	1/0	1/0	0/0	1/1	1/1	2/0	0/0	1/1	0/0	1/3	0/0	0/0	0/1	1/1	1/1	1/3	1/1	1/1	1/1	0/0	3/4	1/1	1/1	1/1	Chloric acid, sodium salt;
Sodium chlorate	NaClO ₃	007775-09-9	each	O, Xn	1/1	1/0	1/0	1/0	0/0	1/0	2/0	1/1	1/0	0/0	1/3	0/0	0/0	0/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1L	1/1L	1/1		
Sodium chlorite	NaClO ₂	007775-09-9	aqueous	O, Xn	0/0	0/0	3/0	1/0	1/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/1	1/1	1/1	1/1	1/0	1/1	3/3	0/0	1/0	1/1L	1/1L	1/1		
Sodium chloride	NaCl	007647-14-5	each	—	1/1	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/1	1/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/2	1/2	1/1		
Sodium chloride	NaCl	007647-14-5	aqueous	—	1/1	1/1	1/1	1/1	1/1	1/2	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	3/4	1/2	1/2	1/1		
Sodium chlorite	NaClO ₂	007758-19-2	diluted	(O, Xn)	1/0	1/3	1/4	(2)	0/0	0/0	(2)	1/3	0/0	0/0	3/0	4/4	0/0	0/0	(1)	1/1	1/1	1/0	1/1	4/4	0/0	3/4	3/4	3/3	0/0		
Sodium chromate	NaCrO ₄	007775-11-3	diluted	T	1/0	1/0	1/1	(2)	0/0	0/0	(2)	1/1	1/1	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	1/3	0/0	1/1	1/1	1/1	0/0		
Sodium cyanide	CNNa	000143-33-9	saturated	T	1/1	1/1	1/0	(3)	0/0	0/0	3/0	1/1	0/0	0/0	3/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	3/3	0/0	4/4	(2)	(2)	0/0	Hydrocyanic acid, sodium salt;	
Sodium cyanide	CNNa	000143-33-9	aqueous	T	1/1	1/1	1/0	(3)	1/0	0/0	3/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	(2)	(2)	0/0		
Sodium dichromate	Na ₂ Cr ₂ O ₇	010588-01-9		T	0/0	1/1	1/0	1/0	3/0	1/1	(3)	1/1	1/1	0/0	1/0	0/0	0/0	1/1	(1)	1/1	1/1	1/0	1/0	3/3	0/0	1/1	(1)	(1)	1/1		
Sodium dithionite	-> see: Sodium hydrosulfite																														
Sodium dodecylbenzene sulfonate	C ₁₈ H ₂₃ NaSO ₃	025155-30-0		Xn	1/1	1/1	(2)	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	(1)	1/1	(1)	(1)	(1)	(1)	(2)	0/0	(2)	(1)	(1)			
Sodium ferrocyanide	C ₅ FeNa ₆	013601-19-9		Xn	1/1	1/1	(1)	(2)	(1)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(1)	(1)	(1)	(2)	0/0	(1)	(1)	(1)		
Sodium fluoride	NaF	007681-49-4	saturated	T	1/1	1/1	1/0	(2)	(1)	1/0	1/1	1/1	1/0	0/0	1/0	1/3	1/1	0/0	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	0/0	0/0	1/1		
Sodium hydrosulfite	Na ₂ S ₂ O ₄	007775-14-6	10 %	Xn	1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1	Sodium dithionite; Dithionous acid, disodium salt; Sodium sulfoxylate;		
Sodium hydrosulfite	Na ₂ S ₂ O ₄	007775-14-6		Xn	1/1	0/0	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	1/3	0/0	1/1	0/0	(1)	1/1	1/3	1/0	1/1	3/3	0/0	4/4	1/1	1/1			
Sodium hydroxide	NaOH	001310-73-2	concentrated	C	1/1	1/1	1/3	4/4	4/4	(3)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/1	(2)	1/0	4/4	3/4	0/0	4/4	(2)	(2)	?	caustic soda, sodium hydrate, soda lye			
Sodium hydroxide	NaOH	001310-73-2	30 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/0	1/0	1/3	1/3	0/0	0/1	1/1	(2)	1/0	(3)	2/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye		
Sodium hydroxide	NaOH	001310-73-2	45 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	1/3	1/1	1/1	1/0	1/3	1/3	1/1	0/0	0/0	1/1	(2)	1/0	2/4	2/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye	
Sodium hydroxide	NaOH	001310-73-2	50 %	C+	1/1	1/1	1/0	4/4	4/4	1/1	1/3	1/1	2/2	1/1	1/2	0/0	0/3	1/1	1/1	3/3	1/0	3/4	3/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye		
Sodium hydroxide	NaOH	001310-73-2	60 %	C+	1/1	1/1	1/0	4/4	4/4	1/0	(3)	1/1	1/0	1/0	0/0	0/0	0/0	0/0	1/1	(2)	1/0	3/4	2/3	0/0	4/4	1/3	1/3	1/1	caustic soda, sodium hydrate, soda lye		
Sodium hydroxide	NaOH	001310-73-2	1 %	Xi	1/1	1/1	1/0	3/4	(3)	1/1	1/1	1/1	2/2	1/1	1/1	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/3	0/0	(4)	1/1	1/1	1/1	caustic soda, sodium hydrate, soda lye		
Sodium hypochlorite	NaClO	007681-52-9	diluted	(O, C)	2/3	2/3	4/4	(3)	3/0	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	15 %	O, C	2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/1	0/0	1/1	1/1	1/1	1/1	3/4	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	saturated	O, C	2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	0/0	1/1	0/0	(1)	1/1	(3)	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide	
Sodium hypochlorite	NaClO	007681-52-9	12,5 % Cl	O, C	2/3	2/3	4/4	2/3	(3)	1/3	4/4	2/3	1/3	1/1	1/3	1/0	1/1	1/1	1/1	1/1	3/0	1/3	4/4	0/0	4/4	3/3L	2/2L	0/0	sodium oxychloride, sodium chloride oxide		
Sodium iodide	NaJ	007681-82-5	each	Xi	1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/0	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/3	(1)	(1)	1/1	0/0	1/1	3/4	3/4	0/0			
Sodium metabisulfite	Na ₂ S ₂ O ₅	007681-57-4	each	Xn	1/1	1/1	1/0	(2)	(2)	0/0	4/4	1/1	0/0	0/0	1/3	0/0	0/0	(1)	1/1	1/1	1/0	1/0	1/0	0/0	1/0	1/1	1/1				
Sodium nitrate	NaNO ₃	007631-99-4	saturated	O, Xn	1/1	1/1	1/0	1/0	(1)	1/0	1/1	1/1	1/1	1/1	1/3	1/3	1/1	1/1	1/1	1/1	1/0	1/1	2/3	0/0	1/1	1/1	1/1	1/1	chile saltpeter		
Sodium nitrate	NaNO ₃	007631-99-4	aqueous	O, Xn	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	chile saltpeter		
Sodium nitrite	NaNO ₂	007632-00-0	saturated	O, T	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/0	1/0	1/0	0/0	(1)	1/1	1/1	1/0	1/1	2/3	0/0	1/0	1/1	1/1	Nitrous acid, sodium salt;		
Sodium nitrite	NaNO ₂	007632-00-0	aqueous	O, T	1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/1	1/0	0/0	1/0	1/1	1/1			
Sodium oxalate	C ₂ Na ₂ O ₄	000062-76-0	saturated	Xn	1/1	1/1	(1)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/3	0/0	0/0	1/1	1/1	1/1	1/3	(1)	1/0	1/0	0/0	1/1	(2)	(2)			
Sodium perborate	NaBO ₂ (HO) ₂ x 3H ₂ O	013517-20-9	saturated	(O, Xn)	1/1	1/1	4/4	(2)	0/0	0/0	2/0	1/1	1/1	0/0	1/0	3/0	1/1	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0			
Sodium perborate	NaBO ₂ (HO) ₂ x 3H ₂ O	013517-20-9	aqueous	(O, Xn)	1/1	1/1	4/4	(2)	3/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	3/0	0/0	1/0	1/0	1/0			
Sodium perchlorate	NaClO ₄	007601-89-0	saturated	O, Xn	1/1	1/1	(2)	(1)	(1)	0/0	1/1	1/1	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(1)	0/0	1/1	1/1	1/1			
Sodium peroxide	Na ₂ O ₂	001313-60-6	10 %	O, C+	0/0	1/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	3/0	0/0	4/4	1/1	1/1	0/0			
Sodium peroxide	Na ₂ O ₂	001313-60-6	saturated	O, C+	0/0	3/3	4/4	(3)	(4)	0/0	4/4	2/2	0/0	0/0	1/0	0/0	0/0	0/0	0/0	1/1	1/1	1/0	1/0	(4)	0/0	4/4	(2)	(2)	0/0		
Sodium persulfate	Na ₂ S ₂ O ₈	007775-27-1	saturated	O, Xi	1/1	0/0	4/4	(2)	0/0	0/0	(3)	1/1	0/0	0/0	1/3	0/0	0/0	0/0	(1)	1/1	1/1	1/0	1/0	(3)	0/0	4/4	0/0	1/0	0/0		
Sodium phosphate	Na ₃ PO ₄ x 12H ₂ O	010101-89-0	saturated	Xi	1/1	1/1	1/0	(2)	(1)	0/0	1/1	1/1	1/1	0/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1			
Sodium phosphate	Na ₃ PO ₄ x 12H ₂ O	010101-89-0	aqueous	Xi	1/1	1/1	1/0	(2)	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1			
Sodium polyphosphates	(NaPO ₃) ₆	068915-31-1	saturated	—	1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	1/0	1/0	(3)	0/0	0/0	0/0			
Sodium silicate	Na ₂ Si ₂ O ₇	001344-09-8	each	C, Xn	1/1	1/1	1/0	1/0	1/0	0/0	(2)	1/1	1/0	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/0	1/1	0/0	1/1	1/1	1/1			
Sodium silicate	Na ₂ Si ₂ O ₇	001344-09-8	saturated	C, Xn	1/1	1/1	1/0	1/0	1/0	0/0	0/0	1/1	1/1	0/0	1/3	1/4	1/1	0/0	1/1	1/1	1/3	1/0	1/1	0/0	1/1	1/1	1/1	1/1	waterglass		
Sodium stearate	C ₁₈ H ₃₅ NaO ₂	000822-16-2	aqueous	(Xi)	1/1	1/1	(1)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	(1)	(2)	(1)	1/0	0/0	(1)	1/1	1/1			
Sodium sulfate	Na ₂ SO ₄	007757-82-6	saturated	—	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/1	1/1	0/0	1/0																

CHEMICALS	thermoplastics																					fluoroelastomers				metals					
	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM /FKM	NBR	SI	AL	V2A	V4A	Haselloy C	COMMENT
Spindle oil	—	—	?		3/3	2/3	(2)	(2)	1/0	0/0	(2)	1/4	0/0	0/0	3/0	0/0	0/0	0/0	(1)	1/1	1/1	(4)	1/1	1/1	0/0	1/1	1/1	1/1	1/1		
Spinning bath acid	—	—	100mg CS ₂ /l	?	1/0	0/0	4/4	(3)	0/0	0/0	4/4	1/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	1/1	1/0	(3)	(2)	4/4	0/0	(4)	3/4	2/4	0/0		
Spirit (of wine)	C ₂ H ₅ O	—	—	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1		ethyl alcohol
Spirits	C ₂ H ₅ O	—	—	—		1/1	1/0	1/0	1/1	1/1	0/0	1/2	1/1	0/0	1/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	1/1	1/1	0/0	ethyl alcohol 40 %
Spirits of Turpentine	—	008006-64-2	—	Xn	X	2/2	3/4	1/0	4/4	1/0	3/3	1/1	4/4	4/4	4/4	2/3	4/4	3/3	1/1	1/1	1/0	1/3	4/4	1/1	3/3	0/0	1/1	1/1	1/1	1/1	
Spirits of wine	C ₂ H ₅ O	—	50 %	(F)	X	1/0	1/1	1/0	1/1	1/1	1/0	1/2	1/1	1/0	1/0	1/0	3/0	0/0	0/0	1/1	1/1	1/1	1/0	(2)	1/1	0/0	1/1	1/1	1/1	1/1	ethyl alcohol
Spirits of wine	C ₂ H ₅ O	—	96 %	F	X	1/0	1/3	1/0	1/3	1/1	1/2	1/2	1/1	3/4	1/2	1/3	3/0	1/3	1/1	1/1	1/1	1/1	1/0	3/0	3/3	0/0	1/1	1/1	1/1	1/1	ethyl alcohol
Spruce oil	—	008008-80-8	—	?		1/2	2/4	(2)	2/3	0/0	2/3	(2)	1/2	4/4	3/3	4/4	0/0	3/4	1/2	1/1	(1)	(2)	4/4	1/0	3/3	0/0	(1)	(1)	(1)		pinus sylvestris
Stannic chloride	SnCl ₄	007646-78-8	aqueous	C	1/1	1/1	4/4	(3)	0/0	0/0	(4)	1/1	4/4	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	4/4	4/4	3/4			
Stannous chloride	SnCl ₂	007772-99-8	aqueous	(C, Xn)	1/1	1/1	(4)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/0	1/0	0/0	4/4	4/4	3/4	1/1	
Stannous chloride	SnCl ₂	007772-99-8	saturated	C, Xn	1/1	1/1	4/4	1/0	0/0	0/0	(2)	1/1	1/1	0/0	1/0	1/0	1/1	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	4/4	4/4	3/4	1/1	0/0	
Starch solution	(C ₆ H ₁₀ O ₅) _n	—	each	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	0/0	0/0	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	1/1	0/0	
Starch syrup	—	—	—	—	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	0/0	0/0	1/1	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	1/1	1/1	1/1	0/0	
Staufer grease, thick	—	—	—	(—)	0/0	0/0	(2)	(2)	(1)	0/0	(1)	(2)	1/4	0/0	0/0	0/0	0/1	0/0	(1)	1/1	(1)	4/4	(1)	(2)	0/0	(1)	1/1	1/1	0/0		
Steam	H ₂ O	—	up to 150°C	?	4	4	4/4	0/0	0	(3)	(3)	0	0	0	0	0	0	0	0	0	1	0	3	4/4	0	(1)	1/1	1/1			
Stearic acid	C ₁₈ H ₃₆ O ₂	000057-11-4	crystals	Xi	1/3	1/3	1/0	1/2	1/0	1/1	1/0	1/3	1/2	2/2	1/2	1/1	1/1	1/1	1/1	1/1	1/1	3/0	1/1	3/3	0/0	1/1	1/1	1/1	1/1		
Srtrontium bromide	SrBr ₂	010476-81-0	—	Xi	1/1	1/1	(2)	(1)	0/0	(1)	0/0	1/1	0/0	0/0	0/0	1/1	0/0	0/0	1/1	1/1	(1)	(1)	(1)	(2)	0/0	(3)	0/0	0/0			
Strychnine	C ₂₂ H ₂₂ N ₂ O ₂	000057-24-9	—	T+	1/1	1/1	(1)	(1)	(2)	0/0	(2)	(1)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(2)	(2)	(2)	0/0	(2)	(1)	(1)		
Styrene	C ₈ H ₈	000100-42-5	100 %	Xn, Xi	X	4/4	3/4	1/1	4/4	1/1	(4)	1/1	3/4	0/0	0/0	4/4	4/4	0/0	0/0	1/0	1/1	(2)	4/4	3/0	4/4	0/0	1/1	1/1	1/1	0/0	
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	50 %	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	0/0	0/0	2/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	(1)	0/0	1/1	1/0	1/0	1/1			
Succinic acid	C ₄ H ₆ O ₄	000110-15-6	saturated	Xi	1/1	1/1	(3)	(2)	0/0	0/0	(3)	1/1	1/1	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/0	?		
Sugar acid	—	—	saturated	(Xi)	1/1	1/1	(3)	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(1)	(1)	0/0	(3)	0/0	0/0			
Sugar beet juice	—	—	—	—	1/1	1/1	1/0	1/0	0/0	1/0	1/1	1/1	1/0	0/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	(1)	(1)			
Sugar syrup	—	—	—	—	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/3	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	
Sulfur	S ₈	007704-34-9	techn. pure	Xi	1/1	1/1	1/0	1/0	(2)	0/0	1/0	1/1	1/1	0/0	3/0	3/4	1/1	0/0	(1)	1/1	1/1	3/0	1/1	4/4	0/0	(1)	1/1	1/1	1/1	flower of sulfur	
Sulfur (mono)chloride	S ₂ Cl ₂	010025-67-9	—	C	0/0	0/0	4/4	(3)	0/0	0/0	4/4	4/4	0/0	0/0	0/0	0/0	0/0	0/0	1/0	1/1	1/0	4/4	1/0	4/4	0/0	3/4	1/1L	1/1L	0/0		
Sulfur dioxide	SO ₂	007446-09-5	damp	T, C	1/1	1/1	(3)	(3)	0/0	1/1	4/4	1/3	3/4	2/2	1/2	0/0	0/0	1/1	1/1	1/1	1/4	1/0	4/4	4/4	0/0	3/4	1/1	1/1	1/0	with H ₂ O→sulfurous acid	
Sulfur dioxide	SO ₂	007446-09-5	liquid	T, C	3/4	4/4	(3)	3/4	0/0	4/4	4/4	4/4	4/4	2/2	3/4	0/0	0/0	1/2	1/1	1/1	4/4	1/0	4/4	4/4	0/0	(3)	(1)	(1)	1/0	with H ₂ O→sulfurous acid	
Sulfur hexafluoride	SF ₆	002551-62-4	—	—	0/0	0/0	1/0	(2)	1/0	0/0	(2)	0/0	0/0	0/0	0/0	0/0	1/0	0/0	0/0	0/0	(1)	(2)	1/0	3/0	1/0	0/0	(1)	(1)	(1)		
Sulfur trioxide	SO ₃	007446-11-9	—	C+	4/4	4/4	4/4	(4)	0/0	4/4	4/4	0/0	4/4	0/0	0/0	0/0	0/0	0/0	(2)	(2)	3/4	3/0	1/0	4/4	0/0	(3)	(1)	(1)	0/0		
Sulfur, melted, 121 °C	S ₈	007704-34-9	?	?	0	0	(4)	(3)	0	4	4	0	0	0	0	0	0	0	0	0	1	0	4	1	4	0	(3)	1	1	0/0	
Sulfuric acid	H ₂ SO ₄	007664-93-9	40 %	C+	1/1	1/1	4/4	2/0	(4)	1/2	4/4	1/1	2/0	3/0	1/3	1/3	1/1	1/1	1/1	1/1	1/1	(3)	1/1	4/4	0/0	3/4	2/3	2/3	0/0		
Sulfuric acid	H ₂ SO ₄	007664-93-9	60 %	C+	1/3	1/3	4/4	3/3	(4)	1/2	4/4	1/3	2/4	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	4/4	3/4	0/0		
Sulfuric acid	H ₂ SO ₄	007664-93-9	80 %	C+	1/1	1/1	4/4	3/4	4/4	1/2	4/4	1/1	3/4	3/0	1/1	1/3	0/0	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	2/4	2/3	0/0		
Sulfuric acid	H ₂ SO ₄	007664-93-9	95 %	C+	3/4	3/4	4/4	4/4	2/2	4/4	3/4	4/4	4/4	2/4	0/0	4/4	1/1	1/1	1/1	1/1	1/1	4/4	1/1	4/4	0/0	4/4	1/3	1/3	0/0		
Sulfuric acid	H ₂ SO ₄	007664-93-9	fuming	C+	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	(1)	1/0	4/4	4/4	1/0	4/4	0/0	(3)	1/2	1/1	0/0		oleum
Sulfuric acid	H ₂ SO ₄	007664-93-9	1-6 %	Xi	1/1	1/1	4/4	1/1	0/0	1/1	4/4	1/1	1/2	1/1	1/2	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	3/0	0/0	(3)	2/2	1/2	0/0		
Sulfuric acid	H ₂ SO ₄	007664-93-9	20 %	Xi	1/1	1/1	4/4	1/2	0/0	1/2	4/4	1/2	1/2	1/1	1/2	0/0	0/0	1/1	1/1	1/1	1/1	2/0	1/1	4/4	0/0	(3)	2/3	2/3			
Sulfuric acid	-> see: Battery acid																														
Sulfurous acid	H ₂ SO ₃	007782-99-2	saturated	(C)	1/1	1/1	4/4	4/4	1/0	0/0	4/4	1/1	0/0	0/0	1/1	0/0	0/0	0/0	1/1	1/1	1/1	3/0	(3)	3/4	0/0	3/4	1/1	1/1	1/1		
Sulfurous acid, disodium salt	-> see: Sodium sulfite																														
Sulfuryl chloride	Cl ₂ SO ₂	007791-25-5	techn. pure	C	4/4	4/4	4/4	1/0	0/0	0/0	4/4	4/4	0/0	0/0	4/4	4/4	0/0	0/0	0/0	1/0	3/0	3/0	1/0	4/4	0/0	3/4	0/0	0/0			
Tallow	—	—	techn. pure	—	1/1																										

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics															fluoroelastics		elastomers		metals		COMMENT			
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE/ETFE	FEP	PTFE	PVDF	EPDM	FPM/FKM	NBR		SI	AL	V2A
Titanium (tetra)chloride	TiCl ₄	007550-45-0		C	0/0	0/0	4/4	(3)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	4/4	(3)	4/4	0/0	(4)	0/0	0/0	
Toluene	—	092045-38-0	100 %	T	1/0	1/3	1/0	(3)	0/0	0/0	1/0	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	3/0	4/4	0/0	(1)	1/1	1/1	
Train oil	—	—	—	—	0/0	0/0	1/0	(2)	1/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(1)	3/4	1/0	1/0	0/0	(1)	(1)	(1)	
Transformer oil	—	—	—	?	1/3	3/3	1/0	(3)	1/1	1/0	3/3	1/3	1/3	1/0	1/0	0/0	1/3	0/0	(1)	1/1	(3)	4/4	2/3	3/3	0/0	1/1	(1)	(1)	0/0
Triacetin	C ₂₁ H ₄₀ O ₆	000102-76-1		Xn	0/0	0/0	0/0	(3)	0/0	0/0	(2)	(2)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	1/0	4/4	3/3	0/0	(1)	(1)	(1)	
Tribromomethane	CHBr ₃	000075-25-2		T	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/0	0/0	2/3	1/1	(1)	(2)	4/4	(4)	4/4	0/0	(3)	0/0	0/0	0/0
Tributyl citrate (TBC)	C ₁₈ H ₃₂ O ₇	000077-94-1		—	1/2	2/3	(2)	4/4	0/0	2/3	(2)	2/3	4/4	3/3	3/4	0/0	0/0	1/2	1/1	(1)	(2)	(3)	(3)	(3)	0/0	(1)	(1)	(1)	
Tributyl phosphate (TBP)	C ₁₇ H ₃₇ PO ₄	000126-73-8	techn. pure	Xn	1/1	1/1	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	4/4	0/0	0/0	(1)	1/1	1/0	3/0	4/4	4/4	0/0	(1)	(1)	(1)	1/1
Trichloroacetaldehyde	C ₂ HCl ₃ O	000075-87-6	100 %	T/Xi	1/1	1/1	4/4	(3)	(4)	0/0	(3)	1/1	0/0	0/0	4/4	4/4	0/0	0/0	(1)	0/0	(4)	3/0	(4)	4/4	0/0	4/4	0/0	0/0	0/0
Trichloroacetic acid (TCA)	C ₂ HCl ₃ O ₂	000076-03-9		C+	1/4	3/4	4/4	4/4	4/4	0/0	4/4	1/1	4/4	0/0	4/4	4/4	0/0	0/0	1/0	1/1	1/4	3/0	4/4	4/4	0/0	1/3	3/0L	2/0L	1/1
Trichlorobenzene	C ₆ H ₃ Cl ₃	—	100 %	(Xn)	4/4	4/4	(3)	(3)	0/0	(4)	(2)	4/4	4/4	0/0	4/4	4/4	4/4	0/0	(1)	(2)	(3)	(4)	(3)	4/4	0/0	(2)	0/0	0/0	0/0
Trichloroethane	C ₂ HCl ₃	—		Xn	3/4	4/4	3/0	4/4	4/4	4/4	(2)	4/4	4/4	4/4	4/4	4/4	1/2	1/1	(1)	1/3	4/4	1/0	4/4	0/0	4/4	0/0	4/4	0/0	0/0
Trichloroethylene (TRI)	C ₂ HCl ₃	000079-01-6	100 %	Xn	3/4	4/4	3/0	4/4	4/4	4/4	4/4	4/4	4/4	4/4	4/4	0/4	1/2	1/1	1/0	1/1	4/4	1/3	4/4	0/0	1/3	1/1L	1/1L	1/0	
Trichlorofluoromethane	CCl ₃ F	000075-69-4		N	0/0	0/0	1/0	(3)	0/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(3)	(1)	0/0	4/4	2/0	1/0	0/0	(3)	0/0	0/0	0/0
Trichlorophenol	C ₆ H ₂ Cl ₃ O	—		(Xn, Xi)	0/0	0/0	(3)	(4)	0/0	0/0	(3)	(3)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(4)	(3)	(4)	0/0	(3)	0/0	0/0	
Trichlorotrifluoroethane	C ₂ Cl ₃ F ₃	000076-13-1		?	0/0	0/0	1/0	(3)	1/0	0/0	1/0	(3)	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Trichlorotrifluoroethane	C ₂ Cl ₃ F ₃	—	100 %	?	4/4	3/4	1/0	3/0	0/0	0/0	1/0	4/4	1/0	3/4	4/4	3/3	0/0	0/0	(1)	1/0	4/4	3/0	1/0	0/0	(3)	0/0	0/0		
Tricresyl phosphate (TCF)	C ₁₉ H ₂₁ PO ₄	—	techn. pure	T/Xn, N	1/1	1/1	1/0	4/4	1/0	0/0	1/0	1/3	4/4	0/0	4/4	4/4	4/4	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	1/1	1/1	1/1	1/1
Triethanolamine (TEA)	C ₆ H ₁₅ NO ₃	000102-71-6	techn. pure	Xi	1/1	1/2	(2)	(2)	1/0	0/0	2/2	1/1	1/1	0/0	3/0	4/4	1/1	0/0	1/1	1/0	1/0	2/0	4/4	4/4	0/0	(1)	(1)	(1)	0/0
Triethylamine (TEA)	C ₆ H ₁₅ N	000121-44-8	techn. pure	F, C, Xn	X	0/0	0/0	(2)	(3)	0/0	1/1	4/4	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	3/4	4/4	3/0	3/4	0/0	(1)	(1)	(1)	0/0
Triethylene glycol	C ₆ H ₁₄ O ₄	000112-27-6		Xi	1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/2	1/1	2/3	0/0	1/1	1/1	1/1	(1)	(2)	(2)	(1)	(3)	0/0	(1)	(1)	0/0	
Triethylene glycol diacetate	C ₁₀ H ₁₈ O ₆	000111-21-7		?	0/0	0/0	(3)	(3)	0/0	0/0	1/0	(2)	0/0	0/0	0/0	0/0	4/4	0/0	(1)	(1)	(3)	(3)	(4)	(4)	0/0	(1)	(1)	(1)	
Trihydroxypropane, 1,2,3-	-> see: Glycerol																												
Triiodomethane	-> see: Iodoform																												
Triisopropylbenzene	C ₁₂ H ₂₄	000717-74-8		—	0/0	0/0	(2)	(3)	0/0	(4)	(2)	(3)	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	1/0	1/0	0/0	1/1	(1)	(1)	
Trimethylbenzene, 1,2,4-	C ₉ H ₁₂	000095-63-6		Xn	X	0/0	0/0	(1)	(4)	0/0	(2)	3/3	4/4	0/0	0/0	0/0	0/0	0/0	(1)	(1)	(2)	4/4	(2)	4/4	0/0	1/1	1/1	1/1	0/0
Trimethylolpropane	C ₆ H ₁₄ O ₃	000077-99-6	aqueous	—	0/0	0/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	(1)	(2)	(2)	0/0	(1)	(1)	(1)		
Trimethylpentane, 2,2,4-	C ₈ H ₁₈	000540-84-1	techn. pure	F, Xn	X	1/3	1/3	1/0	(2)	1/0	(4)	1/0	1/3	3/4	1/0	1/0	4/4	1/1	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	0/0
Trioctyl phosphate	C ₂₄ H ₅₂ PO ₄	000078-42-2	techn. pure	(Xn)	3/0	1/0	1/0	(3)	0/0	0/0	(2)	1/3	0/0	0/0	4/4	0/0	0/0	0/0	(1)	1/1	(3)	3/0	3/4	4/4	0/0	(1)	(1)	(1)	0/0
Tripolyethylene glycol (TPG)	C ₈ H ₁₆ O ₄	024800-44-0		(—)	1/1	1/1	(3)	1/2	0/0	1/1	1/0	1/1	1/1	1/1	2/3	0/0	0/0	1/1	1/1	1/1	(2)	(3)	(2)	(3)	0/0	(1)	(1)	(1)	
Trisodium phosphate	Na ₃ PO ₄	007601-54-9		Xi	1/1	1/1	1/0	(2)	(2)	0/0	1/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	0/0	(4)	1/1	1/1	0/0
Turbine oil (based on mineral oil)	—	—	—	?	0/0	0/0	(1)	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	(2)	1/0	0/0	1/1	1/1	1/1	
Turpentine surrogate	—	—	—	Xn, N	X	0/0	0/0	1/0	(3)	1/0	(4)	1/0	(3)	4/4	0/0	0/0	1/3	0/0	(1)	1/1	(1)	4/4	1/1	(3)	0/0	1/1	1/1	1/1	1/1
Two-stroke oil	—	—	100 %	—	0/0	1/3	1/0	(2)	1/0	1/1	1/3	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	1/1	1/1	1/1		
Undecanol	C ₁₁ H ₂₄ O	000112-42-5		Xi	1/2	1/3	(1)	2/3	(1)	1/2	1/0	1/2	2/2	3/3	1/3	0/0	1/1	1/2	1/1	1/1	(1)	(3)	(1)	(2)	0/0	(1)	(1)	(1)	
Urea	CH ₄ N ₂ O	000057-13-6	aqueous	Xi	1/1	1/1	1/0	1/1	1/0	0/0	1/1	1/1	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	0/0	1/1	1/0	1/1
Urea	CH ₄ N ₂ O	000057-13-6		Xi	1/1	1/1	1/0	1/1	1/0	1/2	1/1	1/2	3/3	2/4	3/3	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/1	0/0	1/1	1/0	1/1
Uric acid	C ₅ H ₄ N ₄ O ₃	000069-93-2		Xi	1/1	1/1	(2)	1/0	1/0	0/0	1/0	1/0	0/0	1/1	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	(1)	(1)	0/0	4/4	1/1	1/1	0/0
Urine	—	—		—	1/1	1/1	1/0	1/0	1/0	0/0	1/1	1/1	3/0	0/0	1/3	1/0	0/0	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	(2)	1/1	1/1	1/1
Urotropin	-> see: Hexamethylenetetramine																												
Valerian drops	—	—		?	0/0	0/0	(2)	(2)	(2)	0/0	(2)	(2)	4/4	0/0	0/0	0/0	1/0	0/0	1/1	1/1	(1)	(3)	(3)	(2)	0/0	(2)	(1)	(1)	
Vaseline	—	008009-03-8	techn. pure	(—)	3/4	2/3	1/0	1/0	1/0	0/0	—	1/3	1/1	0/0	3/0	0/0	1/1	0/0	(1)	1/1	1/1	3/0	1/1	1/1	0/0	1/1	1/1	1/1	petrolatum
Vaseline oil	—	008012-95-1	100 %	?	0/0	1/3	1/0	(2)	1/0	1/0	—	1/3	1/0	1/0	3/0	0/0	0/0	(1)	(1)	(1)	3/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	paraffin oil
Vaseline oil	—	008012-95-1		?	1/1	1/3	1/0	1/0	0/0	0/1	1/3	1/1	0/0	1/3	1/0	1/1	0/0	(1)	1/1	1/1	4/4	1/1	1/3	0/0	1/1	1/1	1/1	1/1	paraffin oil
Vegetable oils	—	—		—	0/0	0/0	0/0	(2)	1/0	0/0	(2)	1/3	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	4/4	1/0	1/0	0/0	(1)	1/1	1/1		
Vinegar	C ₂ H ₄ O ₂	000064-19-7		(Xi)	1/1	1/3	4/4	1/2	1/1	1/0	1/3	1/1	1/0	1/0	1/0														

CHEMICALS	FORMULA	CAS-NR.	CONCENTRATION	HAZARD NOTE	thermoplastics													fluoroplastics			elastomers			metals		COMMENT							
					FLAMMABLE	HDPE	LDPE	PA	PC	PETG	PMP	POM	PP	PS	PSU	PVC HART	PVC WEICH	SAN	ECTFE / ETFE	FEP	PTFE	PVDF	EPDM	FPM / FKM	NBR		SI	AL	V2A	V4A	Haselloy C		
Wines	—	—	—	—	1/1	1/1	1/0	1/0	1/1	1/0	(2)	1/1	1/1	1/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/0	1/0	0/0	(4)	1/1	1/1	1/1
Wort for fermentation	—	—	—	?	1/1	1/1	(2)	(2)	(1)	0/0	1/1	1/1	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	0/0	
Xenon	Xe	007440-63-3	—	—	0/0	0/0	1/0	(1)	1/1	0/0	1/1	(2)	0/0	0/0	0/0	0/0	0/0	0/0	0/0	0/0	(1)	1/1	1/1	1/1	1/0	1/0	0/0	1/1	1/1	1/1	0/0		
Xylene	C ₈ H ₁₀	001330-20-7	—	(F), Xn X	3/4	3/4	1/0	4/4	0/0	3/4	1/2	4/4	4/4	4/4	4/4	4/4	4/4	1/2	1/1	1/0	1/3	4/4	1/3	4/4	0/0	1/1	1/1	1/1	1/1	1/1			
Yeast	—	—	each	—	1/1	1/1	1/0	(1)	1/0	0/0	1/1	1/1	0/0	0/0	1/0	1/0	0/0	1/1	1/1	1/1	1/1	1/1	1/0	1/0	1/1	0/0	1/1	(1)	(1)				
Zinc acetate	C ₄ H ₇ ZnO ₄	000557-34-6	aqueous	Xn, Xi	1/1	1/1	(2)	(2)	(2)	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	(1)	1/0	(3)	3/3	0/0	(3)	(1)	(1)					
Zinc bromide	ZnBr ₂	007899-45-8	—	C, Xn	1/1	1/1	4/4	(2)	0/0	0/0	(2)	1/1	0/0	0/0	0/0	0/0	0/0	1/1	0/0	1/1	(1)	(2)	(1)	(2)	0/0	(3)	0/0	0/0					
Zinc carbonate	ZnCO ₃	003486-35-9	saturated	?	1/1	1/1	(1)	1/1	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0			
Zinc chloride	ZnCl ₂	007646-85-7	aqueous	(C, Xn)	1/1	1/1	3/4	(2)	0/0	0/0	2/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	1/1	1/1	1/1	1/0	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1				
Zinc nitrate	Zn(NO ₃) ₂	007779-88-6	—	O, C, Xn	1/1	1/1	1/4	(2)	0/0	0/0	(2)	1/1	1/0	1/0	1/0	1/1	0/0	1/1	1/1	(1)	1/0	(1)	(2)	0/0	(3)	(1)	(1)	0/0					
Zinc oxide	ZnO	001314-13-2	solid	Xn, Xi	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	1/1				
Zinc oxide ointment	—	—	—	?	0/0	0/0	(1)	(2)	(2)	0/0	(2)	(2)	1/1	0/0	0/0	0/0	1/1	0/0	(1)	1/1	(2)	(4)	(2)	(2)	0/0	(2)	(1)	(1)					
Zinc phosphate	Zn ₃ (PO ₄) ₂	007779-90-0	saturated	?	1/1	1/1	(1)	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	(1)	(1)	0/0			
Zinc sludge	—	—	—	?	0/0	0/0	0/0	0/0	0/0	0/0	0/0	1/1	0/0	0/0	0/0	0/0	0/0	0/0	(1)	(2)	0/0	0/0	0/0	0/0	(3)	0/0	0/0						
Zinc stearate	C ₃₆ H ₇₀ ZnO ₄	000557-05-1	—	Xi	1/1	1/1	(1)	1/1	0/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	(2)	1/1	(2)	0/0	(2)	(1)	(1)							
Zinc sulfate	ZnSO ₄	007733-02-0	10 %	—	1/1	1/1	(3)	1/0	(2)	1/0	2/0	1/1	1/1	0/0	1/1	1/0	1/1	1/1	1/1	1/1	1/1	1/0	1/1	1/0	0/0	3/4	1/1	1/1					
Zinkchlorid	ZnCl ₂	007646-85-7	10 %	C, Xn	1/1	1/1	3/4	1/0	0/0	1/1	2/0	1/1	1/3	0/0	1/3	1/0	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	1/1	0/0	3/4	1/4L	1/3L	1/1			

Two values are given per substance
left number = value at +20°C / right number = value at +50°C.

0	no data available
1	resistant
2	practically resistant
3	partially resistant
4	not resistant
K	no general information available
L	danger of pitting or stress-cracking corrosion
()	estimated value
E	explosive
O	oxidizing
F	highly flammable
F+	extremely flammable
T	toxic
T+	very toxic
C	corrosive
Xn	harmful
Xi	irritant
N	dangerous for the environment

Thermoplastics

HDPE	Polyethylene (high density)
LDPE	Polyethylene (low density)
PA	Polyamide (Nylon)
PC	Polycarbonate
PETG	Polyethylene terephthalate glycol (PET copolymer)
PMP	Polymethylpentene (TPX)
POM	Polyoxymethylene, polyacetal
PP	Polypropylene
PS	Polystyrene
PSU	Polysulfone
PVC	Polyvinyl chloride
SAN	Styrene-acrylonitrile

Fluoroplastics

E-CTFE	Ethylene-chlorotrifluoroethylene (Halar)
ETFE	Ethylene-tetrafluoroethylene
FEP	Tetrafluoroethylene-perfluoropropylene (Teflon, FEP)
PTFE	Polytetrafluoroethylene (Teflon)
PVDF	Polyvinylidene fluoride

Elastomers

EPDM	Ethylene-propylene-diene rubber
FPM/FKM	Fluorinated rubber (Viton)
NBR	Acryl-nitrile-butadiene rubber
SI	Silicone rubber

Metals

Al	Aluminium
V2A	Stainless steel 1.4301 (AISI 304)
V4A	Stainless steel 1.4401 (AISI 316)
Hastelloy C	Nickel-chromium-molybdenum alloy