

Important information

The tables "Chemical resistance of plastics", "Plastics and their properties" and "Viscosity of liquids" as well as the information about chemical resistance given in the particular product descriptions have been drawn up based on information provided by various raw material manufacturers. These values are based solely on laboratory tests with raw materials. Plastic components produced from these raw materials are frequently subject to influences that cannot be recognized in laboratory tests (temperature, pressure, material stress, effects of chemicals, construction features, etc.). For this reason the values given are only to be regarded as being guidelines. In critical cases it is essential that a test is carried out first. No legal claims can be derived from this information; nor do we accept any liability for it. A knowledge of the chemical and mechanical resistance alone is not sufficient for the evaluation of the usability of a product. For example, the regulations concerning flammable liquids (explosion prevention) must also be taken into consideration.

Copyright

This table has been published and updated by Bürkle GmbH, D-79415 Bad Bellingen as a work of reference. This Copyright clause must not be removed. The table may be freely passed on and copied, provided that the information about the publisher is retained.

Extensions, additions and translations

If your own experiences with materials and media could be used to extend this table then we would be pleased to receive any additional information. Please send an E-Mail to info@buerkle.de. We would also like to receive translations into other languages. Please visit our website at www.buerkle.de from time to time and download the updated version of these lists.

Publisher

Bürkle GmbH
Rheinauen 5
D-79415 Bad Bellingen
Tel +49 (76 35) 8 27 95-0
Fax +49 (76 35) 8 27 95-31
info@buerkle.de
www.buerkle.de

Version 3.2 (26.01.2015)

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | thermoplastics | | | | | | | | fluoroplastics | | elastomers | | metals | | COMMENT |
|---|---|-------------|---------------|-------------|-----------|------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|-----|----------------|-----|------|------|------|-----------|-----|------|----------------|------|------------|--|--|---|---------|
| | | | | | | | | | | | | | | | | | | | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | SI | AL | V2A | V4A | Haselloy C | | | |
| Acetaldehyde | C ₂ H ₄ O | 000075-07-0 | 40 % | F+, Xn | X | 3/3 | 2/4 | 2/0 | 4/4 | (4) | 2/4 | 2/0 | 3/4 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 4/4 | 2/3 | (1) | 1/1 | 4/4 | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 3/4 | Acetic aldehyde; Ethanal; Ethyl aldehyde | |
| Acetaldehyde | C ₂ H ₄ O | 000075-07-0 | techn. pure | F+, Xn | X | 3/3 | 2/4 | 2/0 | 4/4 | (4) | 2/4 | 2/0 | 3/4 | 4/4 | 4/4 | 4/4 | 0/0 | 4/4 | 2/3 | (1) | 1/1 | 4/4 | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 1/1 | | | |
| Acetamide | C ₂ H ₅ NO | 000060-35-5 | saturated | Xn | | 1/1 | 1/1 | 1/0 | 4/4 | 0/0 | 1/1 | 1/0 | 1/1 | 1/1 | 4/4 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 4/4 | 1/0 | 0/0 | (1) | (1) | (1) | 1/1 | | | |
| Acetic acid | C ₂ H ₄ O ₂ | 000064-19-7 | 50 % | C | | 1/1 | 1/1 | 4/4 | 1/2 | 0/0 | 1/1 | 3/4 | 1/1 | 2/2 | 2/2 | 1/2 | 0/0 | 0/0 | 1/2 | 1/1 | 1/1 | 1/1 | 4/4 | 4/4 | 4/4 | 0/0 | 1/3 | 1/1 | 1/1 | 1/1 | | | |
| Acetic acid | C ₂ H ₄ O ₂ | 000064-19-7 | 100 % | C+ | X | 0/0 | 0/0 | 4/4 | 4/4 | 4/4 | (3) | 4/4 | 1/3 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 4/4 | 4/4 | 4/4 | 0/0 | 1/3 | 1/2 | 1/2 | 1/1 | | | |
| Acetic acid | C ₂ H ₄ O ₂ | 000064-19-7 | 90% | C+ | X | 1/1 | 1/2 | 4/4 | 4/4 | 4/4 | 1/3 | 4/4 | 1/2 | 4/4 | 3/4 | 1/2 | 4/4 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 4/4 | 4/4 | 0/0 | 1/3 | 1/2 | 1/2 | 1/1 | | | |
| Acetic acid | C ₂ H ₄ O ₂ | 000064-19-7 | 10 % | Xi | | 1/1 | 1/1 | 4/4 | 1/2 | 1/1 | 3/0 | 1/4 | 1/1 | 1/0 | 1/3 | 1/0 | 1/3 | 1/1 | 1/1 | 1/1 | (2) | (3) | 3/3 | 0/0 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | | | | |
| Acetic acid | C ₂ H ₄ O ₂ | 000064-19-7 | 5 % | Xi | | 1/1 | 1/3 | 4/4 | 1/2 | 1/1 | 1/1 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 3/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/3 | 3/3 | 0/0 | 1/3 | 1/2 | 1/1 | 1/1 | | | |
| Acetic acid chloride | -> see: Acetyl chloride | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetic acid sodium salt | -> see: Sodium acetate | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetic aldehyde | -> see: Acetaldehyde | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetic anhydride | C ₂ H ₄ O ₃ | 000108-24-7 | techn. pure | C | X | 4/4 | 3/3 | 3/3 | 4/4 | 0/0 | 4/4 | (2) | 1/3 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 0/0 | 1/0 | 1/1 | 4/4 | 3/0 | 4/4 | 4/4 | 0/0 | (2) | 1/1 | 1/1 | 1/1 | | | |
| Acetic chloride | -> see: Acetyl chloride | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetone | C ₂ H ₆ O | 000067-64-1 | | F, Xi | X | 1/1 | 3/3 | 1/0 | 4/4 | 4/4 | 2/3 | 1/3 | 1/3 | 4/4 | 4/4 | 4/4 | 0/0 | 4/4 | 2/3 | (1) | 1/1 | 3/4 | 1/0 | 4/4 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | Propanone, 2-; Dimethyl ketone; Methyl ketone | |
| Acetonitrile | C ₂ H ₃ N | 000075-05-8 | | F, T | X | 1/1 | 1/1 | 1/0 | 4/4 | (4) | 3/4 | (3) | 3/4 | 4/4 | 4/4 | 4/4 | 0/0 | 0/0 | 1/1 | (1) | (1) | 1/1 | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | Methyl cyanide; Cyanomethane; Ethanenitrile | | |
| Acetyl chloride | -> see: Chloroacetone | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetophenone | C ₈ H ₈ O | 000098-86-2 | | Xn | | 0/0 | 1/0 | 1/0 | (4) | (4) | (4) | 1/0 | 1/3 | 0/4 | 0/0 | 4/4 | 4/4 | 0/4 | 1/1 | 0/0 | 1/1 | 1/3 | 1/0 | 4/4 | 4/4 | 0/0 | 1/1 | (1) | (1) | 0/0 | Phenylethanone, 1-; Phenyl methyl ketone; Acetylbenzene | | |
| Acetyl chloride | C ₂ H ₃ ClO | 000075-36-5 | 100 % | F, C | X | 0/0 | 0/0 | 4/4 | 4/4 | (4) | 4/4 | 3/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/0 | 1/1 | 4/4 | 1/0 | 4/4 | 0/0 | 4/4 | 1/2L | 1/1L | 0/0 | Acetic chloride; Ethanoyl chloride; Acetic acid chloride | | |
| Acetylene | C ₂ H ₂ | 000074-86-2 | 100 % | F+ | X | 1/0 | 1/0 | 1/0 | 1/0 | 1/1 | 0/0 | 1/0 | 0/0 | 0/0 | 2/0 | 4/4 | 3/0 | (1) | 1/1 | 1/0 | (1) | 1/0 | 1/0 | 0/0 | (1) | (1) | (1) | 1/1 | 1/1 | | Ethine; Ethyne | | |
| Acetyloxybenzoic acid, 2- | -> see: Acetylsalicylic acid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Acetylsalicylic acid | C ₉ H ₈ O ₄ | 000050-78-2 | 100 % | Xn | | 0/0 | 0/0 | 1/0 | 0/0 | (2) | 0/0 | (3) | 1/2 | 1/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/2 | (2) | (3) | 0/0 | 0/0 | 1/0 | 1/0 | 1/0 | 1/0 | Acetyloxybenzoic acid, 2-; | | |
| Acrylonitrile | C ₃ H ₃ N | 000107-13-1 | | F, T | X | 1/1 | 1/3 | 1/0 | 4/4 | (4) | 3/4 | (3) | 3/4 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 1/2 | 1/1 | 1/0 | 3/3 | 4/4 | 4/4 | 4/4 | 0/0 | 1/0 | 1/0 | 1/0 | 1/1 | Cyanoethylene; Propenenitrile, 2-; Vinyl cyanide | | |
| Adipic acid | C ₆ H ₁₀ O ₄ | 000124-04-9 | saturated | Xi | | 1/1 | 1/2 | 0/0 | 1/1 | (2) | 1/1 | 1/3 | 1/1 | 1/1 | 2/2 | 1/3 | 1/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 1/1 | 0/0 | 1/0 | (2) | (2) | 1/1 | Hexanedioic acid; Butanedicarboxylic acid, 1,4- | | |
| Alanine, L- | C ₃ H ₇ NO ₂ | 000056-41-7 | | — | | 1/1 | 1/1 | 1/1 | 4/4 | (2) | 1/1 | (1) | 1/1 | 1/1 | 4/4 | 4/4 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | (1) | 1/0 | (1) | 1/0 | (2) | (2) | (2) | | Aminopropanoic acid, L-2-; aminopropanoic acid, alpha- | | | |
| Allspice | — | ground | ? | | | 0/0 | 0/0 | (2) | 4/4 | 0/0 | (2) | 2 | 4/4 | 0/0 | 0/0 | 3/3 | 0/0 | (1) | (1) | (2) | (2) | (2) | 0/0 | (1) | (1) | (1) | | | | | | | |
| Allyl acetate | C ₅ H ₈ O ₂ | 000591-87-7 | 100 % | F, T | X | 0/0 | 1/3 | 4/4 | 4/4 | (4) | (4) | (2) | 1/3 | 4/4 | 0/0 | 0/0 | 4/4 | 0/0 | 0/0 | (1) | 1/1 | (2) | (3) | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | | | |
| Allyl alcohol | C ₃ H ₆ O | 000107-18-6 | 96 % | F, T | X | 1/3 | 3/3 | 3/0 | 3/3 | 1/0 | 1/2 | (2) | 2/2 | 2/4 | 2/3 | 2/3 | 4/4 | 4/4 | 1/1 | (1) | (2) | 1/0 | 4/4 | 3/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | Vinyl carbinol; Propenyl alcohol | | |
| Allyl chloride | C ₃ H ₅ Cl | 000107-05-1 | 100 % | F, T+ | X | (3) | 3/4 | 0/0 | (4) | (4) | (2) | 4/4 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | (1) | (1) | 4/4 | (3) | 4/4 | 0/0 | 1/0 | (1L) | (1L) | 0/0 | 0/0 | Chloro-1-propene, 3-; Chloropropylene, 3- | | | |
| Allyl mustard oil | C ₂ H ₅ NS | 000057-06-7 | | T | X | 0/0 | 0/0 | 0/0 | (4) | (3) | (4) | (2) | (2) | 0/0 | 0/0 | 0/0 | 4/4 | 0/0 | (1) | (1) | (2) | (3) | (3) | (4) | 0/0 | (1) | (1) | (1) | | oleum sinapis | | | |
| Almond oil, sweet | — | 008007-69-0 | | — | | 0/0 | 0/0 | (2) | 1/1 | 0/0 | (2) | (2) | 3/4 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | (1) | (2) | 0/0 | (1) | 1/1 | 1/1 | | | | | |
| Alumina acidic | C ₄ H ₇ AlO ₅ x H ₂ O | 000142-03-0 | saturated | Xi | | 1/1 | 1/0 | (2) | (2) | 0/0 | 1/0 | 1/1 | 0/0 | 1/0 | 1/0 | 1/1 | 1/1 | 1/1 | (1) | 1/0 | 4/4 | 3/3 | 0/0 | (1) | 1/1 | 1/1 | | | | | | | |
| Aluminium fluoride | AlF ₃ | 007789-18-1 | aqueous | Xi | | 1/1 | 1/1 | (3) | (2) | (2) | 1/1 | 3/4 | 1/1 | 0/0 | 0/0 | 1/3 | 1/3 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | | | |
| Aluminum ammonium sulfate dodecahydrate | (NH ₄) ₂ Al(SO ₄) ₂ | 007784-26-1 | saturated | Xi | | 1/1 | 1/1 | 3/4 | (2) | (2) | 0/0 | 3/4 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | (2) | 1/1 | 0/0 | 1/0 | 1/2 | 1/3 | 0/0 | | | |
| Aluminum chloride | AlCl ₃ | 007784-13-6 | 10 % | ? | | 1/1 | 1/2 | 1/0 | 1/0 | (2) | 1/1 | 3/4 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | 2/2 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 4/4 | 4/4 | 3/4 | 1/1 | | | |
| Aluminum chloride | AlCl ₃ | 007784-13-6 | solid | C | | 1/1 | 1/1 | 3/4 | (3) | 0/0 | 0/0 | 4/4 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (2) | (3) | (3) | (3) | 0/0 | 4/4 | 4/4 | 3/4 | 1/1 | | | | |
| Aluminum chloride | AlCl ₃ | 007784-13-6 | saturated | C | | 1/1 | 1/1 | 3/4 | (2) | 0/0 | 0/0 | 4/4 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | (1) | 1/1 | (2) | 1/0 | 1/1 | 0/0 | 4/4 | 4/4 | 3/4 | 1/1 | | | |
| Aluminum hydroxide | Al(OH) ₃ | 021645-51-2 | | Xi | | 1/1 | 1/2 | 1/1 | 1/1 | 1/1 | 1/2 | 1/1 | 1/2 | 2/2 | 2/2 | 1/2 | 1/1 | 1/1 | 1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | small solubility - no chemical effect expected | | |
| Aluminum nitrate | Al(NO ₃) ₃ | 013473-90-0 | aqueous | (O) | | 1/1 | 1/0 | 1/4 | 1/0 | (2) | 1/0 | 3/4 | 1/1 | 1/0 | 1/0 | 1/0 | 1/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | 1/0 | 1/0 | 1/1 | | | |
| Aluminum oxide, alpha- | Al ₂ O ₃ | 001344-28-1 | solid | — | | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | small solubility - no chemical effect expected | | |
| Aluminum potassium sulfate | KAl(SO ₄) ₂ x 12H ₂ O | 010043-67-1 | diluted | Xi | | 1/1 | 1/1 | 1/0 | 1/0 | (2) | 0/0 | 3/4 | 1/1 | 1/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/3 | 0/0 | 1/0 | 1/1 | 1/1 | 1/1 | | | | |
| Aluminum potassium sulfate | KAl(SO ₄) ₂ x 12H ₂ O | 010043-67-1 | saturated | Xi | | 1/1 | 1/1 | 1/0 | 1/0 | (2) | 0/0 | 3/4 | 1/1 | 1/0 | 1/3 | 1/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/3 | 0/0 | 1/0 | (1) | (1) | 0/0 | | | | |
| Aluminum sodium sulfate | NaAl(SO ₄) ₂ | 010102-71-3 | | ? | | 1/1 | 1/1 | (3) | (2) | (1) | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | (1) | (2) | 0/0 | 1/3 | (1) | (1) | | | | |
| Aluminum sulfate | Al ₂ (SO ₄) ₃ | 010043-01-3 | 10 % | ? | | 1/1 | 1/1 | 1/0 | 1/0 | (2) | 1/1 | 3/4 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 1/1 | 0/0 | 1/0 | 1/2 | 1/1 | 1/1 | | | |
| Aluminum sulfate | Al ₂ (SO ₄) ₃ | 010043-01-3 | saturated | Xn | | 1/1 | 1/1 | 3/4 | 1/0 | 0/0 | 1/1 | 3/4 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 1/0 | 2/2 | 1/2 | 1/1 | | | |
| Aminic acid | -> see: Formic acid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Aminoacetic acid | -> see: Glycine | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Aminoethanol | C ₂ H ₇ NO | 000141-43-5 | | Xn/Xi | | 0/0 | 0/0 | (3) | (3) | 0/0 | 0/0 | (3) | 1/2 | 4/4 | | | | | | | | | | | | | | | | | | | |

| | | thermoplastics ----- ----- | | | | | | | | | | | | | fluoroplastics -- | | elastomers -- | | metals ----- | | | | | | | | | | | | | | | | | | |
|---------------------------|--|----------------------------|---------------|--------------------------------|-----------|------|------|-----|-----|------|-----|-----|-----|-----|-------------------|----------|---------------|-----|--------------|-----|------|------|------|----------|-----|-----|-----|-----|-----|-------------|---------|-----|-----|-----|-----|---------------------------------------|---------------------------------|
| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE /ETFE | FEP | PTFE | PVDF | EPDM | FPM /FKM | NBR | SI | AL | V2A | V4A | Hastelloy C | COMMENT | | | | | | |
| | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Cinnamon oil | — | 008007-80-5 | | Xn, Xi | | 3/4 | 4/4 | (2) | 2/3 | 0/0 | 4/4 | (2) | 4/4 | 4/4 | 3/3 | 4/4 | 0/0 | 0/0 | 1/2 | 1/1 | (1) | (2) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | | | | | | | | |
| Citric acid | C ₆ H ₈ O ₇ | 000077-92-9 | 10 % | Xi | 1/1 | 1/1 | 1/1 | 1/2 | 1/3 | 1/1 | 2/4 | 1/1 | 1/2 | 1/1 | 1/3 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Citric acid | C ₆ H ₈ O ₇ | 000077-92-9 | 50 % | Xi | 1/1 | 1/1 | 3/0 | 1/0 | 0/0 | 1/0 | 2/0 | 1/1 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | (1) | 1/1 | 0/0 | 1/0 | 1/3 | 1/2 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Citric acid | C ₆ H ₈ O ₇ | 000077-92-9 | saturated | Xi | 1/1 | 1/1 | 3/0 | 1/0 | 0/0 | 1/0 | 2/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | (1) | 1/1 | 0/0 | 1/0 | 1/3 | 1/2 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Citrus juices | — | — | aqueous | — | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 1/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | (1) | 1/0 | 1/1 | 0/0 | (2) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Cleaning agents | — | — | — | ? | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | — | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | (2) | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Clophen A60 | — | 011096-82-5 | | Xn, N | 0/0 | 0/0 | (3) | 0/0 | 0/0 | (2) | 4/4 | 0/0 | 4/4 | 0/0 | 0/0 | 4/4 | 0/0 | 0/0 | 0/0 | (1) | (2) | 4/4 | 2/3 | 4/4 | 0/0 | 1/0 | 1/0 | 1/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | polychlorinated Biphenyls, PCB, Bayer | |
| Coal gas, without benzene | — | — | | F+, T | X | 1/0 | 1/0 | 1/0 | 1/0 | (2) | 1/0 | (2) | 1/0 | 1/0 | 0/0 | 1/0 | 1/0 | 0/0 | 0/0 | (1) | 1/0 | 1/0 | 4/4 | 1/0 | 3/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | | |
| Cobalt dichloride | CoCl ₂ | 007646-79-9 | aqueous | Xn | 1/1 | 1/1 | (2) | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | 1/0 | 1/0 | 0/0 | (3) | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Cocoa | — | — | | (—) | 1/1 | 1/1 | (2) | (1) | (2) | 0/0 | (1) | 2/1 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | (2) | (1) | (2) | 0/0 | (1) | (1) | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Cocoa butter | — | 008002-31-1 | | — | 0/0 | 0/0 | 1/0 | (1) | 1/0 | 0/0 | 1/1 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (1) | 4/4 | 1/0 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Coconut butter | — | — | | — | 0/0 | 0/0 | 1/0 | (2) | 1/0 | 0/0 | (2) | 2/1 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/1 | 1/0 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Coconut fatty alcohol | — | 068425-37-6 | techn. pure | (Xi) | 1/0 | 0/0 | (1) | (2) | 1/0 | 0/0 | (2) | 1/3 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/1 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Coconut oil | — | 008001-31-8 | techn. pure | — | 1/3 | 1/3 | 1/0 | (2) | 1/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/1 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Cod-liver oil | — | 008001-69-2 | | — | 1/3 | 1/3 | (2) | 1/0 | (2) | 0/0 | (2) | 1/3 | 1/1 | 0/0 | 1/0 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/0 | 1/0 | 0/0 | 1/0 | (1) | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Colza oil | — | 008002-13-9 | | — | 0/0 | 0/0 | (2) | 1/0 | 0/0 | (2) | 1/3 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 1/3 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Compressed air | — | — | oleaginous | — | 1/0 | 0/0 | (2) | (2) | (1) | 0/0 | (1) | 3/0 | 0/0 | 0/0 | 3/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | (3) | (1) | (2) | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Condy's crystals | — | — | | -> see: Potassium permanganate | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Copper acetate | C ₄ H ₆ CuO ₄ | 004180-12-5 | aqueous | Xn | 1/1 | 1/1 | (3) | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | (3) | 3/3 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | verdigris | |
| Copper sulfate | CuSO ₄ x 5H ₂ O | 007758-99-8 | aqueous | Xn | 1/1 | 1/1 | 1/0 | 1/0 | (2) | 1/0 | 1/0 | 1/1 | 1/1 | 1/0 | 1/3 | 1/0 | 1/1 | 1/1 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 2/0 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | blue stone | |
| Cotton oil | — | 008001-29-4 | techn. pure | ? | 0/0 | 0/0 | 1/0 | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 3/0 | 1/0 | 1/0 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Creosote | — | — | | (T) | 1/1 | 1/1 | 3/0 | (3) | 0/0 | 0/0 | (3) | 3/4 | 0/0 | 1/0 | 3/0 | 4/4 | 0/0 | 0/0 | (1) | 1/1 | (3) | 4/4 | (3) | 1/0 | 0/0 | (2) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Creosote | — | — | | -> see: Carbolinum | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Cresol (-mixtures) | C ₇ H ₈ O | 001319-77-3 | | T, C | 3/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 2/3 | 4/4 | 4/4 | 4/4 | 4/4 | 3/4 | 1/2 | 1/1 | 1/1 | 1/1 | 4/4 | 1/0 | 4/4 | 0/0 | 1/1 | 1/0 | 1/0 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Crotonaldehyde | C ₆ H ₈ O | 004170-30-3 | techn. pure | F, T | X | 1/0 | 0/0 | (2) | (4) | 0/0 | (4) | (2) | 1/0 | 0/0 | 0/0 | 4/4 | 0/0 | 0/0 | (1) | 1/0 | 1/3 | 1/0 | 3/0 | 4/4 | 0/0 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Crude oil | — | — | 100 % | (N) | 0/0 | 1/3 | 1/0 | (3) | 1/0 | 0/0 | 1/0 | 1/3 | 3/0 | 1/0 | 1/0 | 3/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/0 | 3/3 | 0/0 | (2) | (1) | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Cumene | C ₉ H ₁₂ | 000098-82-8 | | Xi | X | 2/3 | 3/4 | (2) | 4/4 | 0/0 | 4/4 | (2) | 3/4 | 4/4 | 4/4 | 4/4 | 0/0 | 0/0 | 1/2 | 1/1 | (1) | (2) | 4/4 | 1/0 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Cupric chloride | CuCl ₂ | 007447-39-4 | saturated | Xn | 1/3 | 1/1 | (3) | 1/0 | (2) | 1/0 | (2) | 1/3 | 0/0 | 0/0 | 1/1 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 0/0 | 4/4 | 4/4 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Cupric nitrate | Cu(NO ₃) ₂ | 003251-23-8 | saturated | O, Xn | 1/1 | 1/1 | 1/0 | (2) | (2) | 1/0 | 1/0 | 1/1 | 1/0 | 0/0 | 1/0 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 4/4 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Cupric nitrate | Cu(NO ₃) ₂ | 003251-23-8 | aqueous | O, Xn | 0/0 | 0/0 | (3) | (2) | (2) | 0/0 | 1/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Cuprous chloride | CuCl | 007758-89-6 | aqueous | Xn | 0/0 | 0/0 | (3) | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | 4/4 | 4/4 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Cuprous cyanide | CCuN | 000544-92-3 | saturated | T | 1/1 | 1/1 | (2) | (2) | (2) | 0/0 | (1) | 1/3 | 0/0 | 0/0 | 1/0 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | (3) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Curry | — | — | | ? | 0/0 | 0/0 | (2) | (2) | (2) | 0/0 | (1) | (2) | 3/3 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | (1) | (1) | (2) | (2) | (2) | 0/0 | (1) | (1) | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | possibility of discoloration |
| Cyanoethylene | — | — | | -> see: Acrylonitrile | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Cyanomethane | — | — | | -> see: Acetonitrile | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Cyclanon | — | — | | (Xn, Xi) | 1/1 | 1/1 | 1/0 | (2) | (1) | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | (1) | (2) | (2) | 1/1 | 0/0 | 3/4 | (1) | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | appliance for dyeing-mill; BASF |
| Cyclohexane | C ₆ H ₁₂ | 000110-82-7 | | F | X | 3/4 | 3/4 | 1/0 | 3/3 | 1/0 | 4/4 | 1/1 | 3/4 | 4/4 | 4/4 | 2/3 | 1/0 | | | | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | FLAMMABLE | thermoplastics | | | | | | | | | | | | | | fluoroelastics | | elastomers | | metals | | COMMENT | | | | |
|---|---|-------------|---------------|-------------|-----------|----------------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|-----|--------------|----------------|------|------------|------|-----------|-----|---------|------|-------------|---|----------------------|
| | | | | | | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | | SI | AL | V2A | V4A |
| Dimethylaniline | C ₉ H ₁₁ N | — | — | T | 0/0 | 0/0 | (3) | 4/4 | 0/0 | 0/0 | (2) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | isomer not indicated in the source | |
| Dinitro ethylene glycol | C ₂ H ₄ (NO ₂) ₂ | 000628-96-6 | diluted | (E, T+) | 0/0 | 0/0 | (3) | (3) | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | (1) | (1) | (3) | 1/0 | 1/0 | 4/4 | 0/0 | 0/0 | (1) | (1) | 0/0 | |
| Dinonyl phthalate (DNP) | C ₂₆ H ₄₂ O ₄ | 000084-76-4 | techn. pure | Xn | 3/0 | 0/0 | (2) | 3/0 | 0/0 | 0/0 | (2) | 1/3 | 0/0 | 0/0 | 4/4 | 0/0 | 0/0 | (1) | 1/0 | (2) | (3) | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | plasticiser | | |
| Diocetyl adipate | C ₂₂ H ₄₂ O ₄ | 000103-23-1 | ? | ? | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | (2) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | plasticiser | | |
| Diocetyl phthalate (DOP) | C ₂₂ H ₃₈ O ₄ | 000117-81-7 | techn. pure | Xn | 4/4 | 4/4 | 1/0 | 4/4 | 1/0 | 1/0 | (2) | 4/4 | 4/4 | 1/0 | 4/4 | 4/4 | 0/0 | 0/0 | 1/1 | 1/0 | (2) | 3/0 | 2/3 | 4/4 | 0/0 | (1) | (1) | (1) | plasticiser | |
| Diocetyl sebacate | C ₂₆ H ₅₀ O ₄ | 002432-87-3 | — | — | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 2/0 | 3/0 | 4/4 | 0/0 | (1) | (1) | (1) | plasticiser | | |
| Dioxane | C ₈ H ₁₆ O ₂ | 000123-91-1 | — | F, Xn | X | 2/2 | 2/3 | 1/0 | 4/4 | 1/0 | 2/3 | 1/2 | 3/3 | 4/4 | 2/3 | 3/4 | 4/4 | 1/3 | 1/1 | 1/1 | 3/3 | 2/0 | 4/4 | 4/4 | 0/0 | 1/1 | 1/0 | 1/0 | 0/0 | |
| Diphenyl ether | C ₁₂ H ₁₀ O | 000101-84-8 | — | Xn/Xi | 0/0 | 1/0 | 3/0 | (3) | (4) | 0/0 | 1/1 | 4/4 | 4/4 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | (1) | 1/0 | (2) | 4/4 | 3/0 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Diphenylamine | C ₁₂ H ₁₁ N | 000122-39-4 | — | T | 0/0 | 0/0 | 0/0 | (3) | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | 0/0 | 4/4 | 0/0 | (1) | (1) | (2) | (3) | (3) | (4) | 0/0 | (1) | (1) | (1) | 0/0 | | |
| Diphenyl ether | — | 008004-13-5 | — | ? | 0/0 | 0/0 | 1/1 | (3) | 4/4 | 0/0 | 1/1 | 4/4 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 3/0 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | mixture with diphenyl and diphenyl ether; Bayer | |
| Dipropyl ketone | C ₇ H ₁₄ O | 000123-19-3 | — | X | 0/0 | 0/0 | (3) | (4) | (4) | (4) | 1/0 | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | (3) | (4) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | | |
| Dipropylene glycol | C ₈ H ₁₆ O ₃ | 025265-71-8 | — | Xi | 1/1 | 1/1 | (2) | 2/3 | 0/0 | 1/1 | 1/0 | 1/1 | 1/1 | 2/2 | 2/3 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | (2) | 4/4 | 3/0 | 3/3 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Dipropylene glycol (mono)methyl ether | C ₈ H ₁₆ O ₂ | — | — | X | 0/0 | 0/0 | (3) | (3) | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 0/0 | 4/4 | 0/0 | (1) | (1) | (2) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | isomer not indicated in the source | |
| Disodium phosphate | Na ₂ HPO ₄ | 007558-79-4 | — | (Xi) | 1/1 | 1/1 | 1/0 | (2) | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | (1) | 0/0 | (1) | 1/1 | 1/1 | 0/0 | latex | |
| Dispersion of rubber | — | — | — | ? | 0/0 | 0/0 | 1/0 | (2) | (2) | 0/0 | 2/3 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (1) | (3) | (1) | (2) | 0/0 | (3) | (1) | (1) | 0/0 | | |
| Dithionous acid, disodium salt | -> see: Sodium hydrosulfite | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Divinylene oxide | -> see: Furan | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Dope, viscous ~ | — | — | — | (Xn, Xi) | 1/1 | 1/1 | 4/4 | (3) | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | (3) | (2) | 4/4 | 0/0 | (3) | 3/4 | 2/4 | 0/0 | | |
| Emulsifiers | — | — | — | ? | 0/0 | 0/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (1) | (2) | (2) | (3) | 0/0 | 0/0 | K | K | 0/0 | | |
| Emulsions for fotos | — | — | — | ? | 1/0 | 0/0 | 1/0 | (2) | (2) | 0/0 | 1/0 | 1/1 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | (2) | (2) | (1) | 0/0 | (2) | 0/0 | 0/0 | 0/0 | | |
| Ephetin | — | — | 10% in water | ? | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | | |
| Epichlorhydrin | C ₃ H ₅ ClO | 000106-89-8 | 100 % | F, T | X | 1/0 | 1/0 | 4/4 | (4) | 0/0 | (4) | 1/0 | 2/2 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | (1) | 1/0 | (3) | 3/0 | 4/4 | 4/4 | 0/0 | (3) | 0/0 | 0/0 | 0/0 | |
| Epoxyp propane, 1,2- | -> see: Propylene oxid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethanal | -> see: Acetaldehyde | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethanedioic acid | -> see: Oxalic acid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethanenitrile | -> see: Acetonitrile | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethanoyl chloride | -> see: Acetyl chloride | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethoxybenzene | C ₈ H ₁₀ O | 000103-73-1 | — | ? | 0/0 | 0/0 | (2) | (4) | 0/0 | (3) | (2) | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | Ethyl phenyl ether; Phenyl ethyl ether; Phenetole | |
| Ethyl acetate | C ₄ H ₈ O ₂ | 000141-78-6 | 100 % | F | X | 1/3 | 3/4 | 1/0 | 4/4 | 4/4 | 4/4 | 1/1 | 1/3 | 4/4 | 4/4 | 4/4 | 4/4 | 1/2 | 1/1 | 1/1 | 3/3 | 3/0 | 4/4 | 4/4 | 0/0 | 1/1 | (1) | (1) | 1/0 | |
| Ethyl acrylate | C ₈ H ₁₀ O ₂ | 000140-88-5 | 100 % | F, Xn | X | 4/4 | 4/4 | 1/0 | (4) | (4) | (4) | (2) | 4/4 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 1/1 | 1/0 | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 1/0 | |
| Ethyl alcohol | C ₂ H ₆ O | 000064-17-5 | 40 % | — | X | 1/1 | 1/2 | 1/0 | 1/2 | 1/1 | 1/2 | 1/1 | 2/3 | 1/2 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | | |
| Ethyl alcohol | C ₂ H ₆ O | 000064-17-5 | 50 % | — | X | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 1/0 | 1/2 | 1/1 | 1/0 | 1/0 | 1/0 | 3/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | (2) | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | |
| Ethyl alcohol | C ₂ H ₆ O | 000064-17-5 | 96 % | F | X | 1/0 | 1/3 | 1/0 | 1/3 | 1/1 | 1/2 | 1/2 | 1/1 | 3/4 | 1/2 | 1/3 | 3/0 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/0 | 3/3 | 0/0 | 1/1 | 1/1 | 1/1 | |
| Ethyl aldehyde | -> see: Acetaldehyde | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethyl benzoate | C ₉ H ₁₀ O ₂ | 000093-89-0 | — | Xn | 2/2 | 3/3 | (2) | 4/4 | 0/0 | 2/3 | (2) | 2/3 | 4/4 | 4/4 | 4/4 | 0/0 | 4/4 | 1/2 | 1/1 | 1/0 | (3) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethyl butyrate | C ₈ H ₁₂ O ₂ | 000105-54-4 | — | F | X | 2/3 | 2/4 | (2) | 4/4 | 0/0 | 3/4 | (2) | 2/4 | 4/4 | 4/4 | 4/4 | 0/0 | 0/0 | 1/2 | 1/1 | (1) | (2) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethyl chloride | -> see: Monochloroethane | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethyl chloroacetate | C ₄ H ₇ ClO ₂ | 000105-39-5 | techn. pure | T/Xi | 1/1 | 1/1 | (3) | 4/4 | (4) | (4) | (3) | 1/1 | 4/4 | 0/0 | 3/4 | 3/4 | 0/0 | 0/0 | (1) | 1/1 | 1/4 | 3/0 | 4/4 | 4/4 | 0/0 | 3/4 | 0/0 | 0/0 | 0/0 | |
| Ethyl cyanoacetate | C ₃ H ₇ NO ₂ | 000105-56-6 | — | Xn/Xi | 1/1 | 1/1 | 0/0 | 3/4 | 0/0 | 1/1 | (2) | 1/1 | 2/4 | 3/3 | 3/4 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | (3) | (2) | (3) | (3) | 0/0 | (2) | (1) | (1) | 0/0 | |
| Ethyl formate | C ₃ H ₆ O ₂ | 000109-94-4 | — | F | X | 0/0 | 0/0 | 0/0 | (4) | 0/0 | (4) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | (3) | (4) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethyl lactate | C ₂ H ₅ O ₃ | 000097-64-3 | — | X | 1/1 | 1/1 | (2) | 3/4 | 0/0 | 1/1 | (2) | 1/1 | 3/4 | 3/3 | 3/4 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 3/0 | (3) | (3) | (3) | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethyl mercaptan | C ₂ H ₆ S | 000075-08-1 | — | F, Xn | X | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethyl phenyl ether | -> see: Ethoxybenzene | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ethyl silicate | C ₈ H ₂₀ SiO ₄ | 000078-10-4 | — | Xn | X | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | (3) | (3) | 1/0 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethylbenzene | C ₈ H ₁₀ | 000100-41-4 | — | F, Xn | X | 2/3 | 3/4 | (2) | 4/4 | 0/0 | 3/4 | 1/0 | 3/4 | 4/4 | 4/4 | 4/4 | 4/4 | 2/3 | 1/1 | 1/0 | 1/1 | 4/4 | (2) | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethylene | C ₂ H ₄ | 000074-85-1 | — | F+ | X | 0/0 | 0/0 | 1/0 | (2) | 0/0 | 1/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | (3) | 3/0 | 3/3 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethylene dibromiden (EDB) | C ₂ H ₄ Br ₂ | 000106-93-4 | — | T | (4) | (4) | (2) | (4) | (4) | (4) | (4) | (2) | 4/4 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | 1/2 | 4/4 | (3) | 4/4 | 0/0 | (3) | 1/0L | 1/0L | 0/0 | Dibromoethane, 1,2-; |
| Ethylene glycol | C ₂ H ₆ O ₂ | 000107-21-1 | — | Xn | 1/1 | 1/1 | 3/3 | 2/3 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 3/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/2 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | |
| Ethylene glycol monobutyl ether | C ₈ H ₁₈ O ₂ | 000111-76-2 | 100 % | Xn | X | 0/0 | 1/0 | 1/0 | (2) | 1/0 | 0/0 | 1/0 | 1/0 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 1/1 | 1/0 | 1/1 | 3/0 | 3/4 | 3/4 | 0/0 | 1/1 | (1) | (1) | 0/0 |
| Ethylene glycol monoethyl ether | C ₆ H ₁₂ O ₂ | 000110-80-5 | 100 % | T | X | 0/0 | 4/4 | (3) | (2) | 0/0 | 0/0 | 1/0 | 2/4 | 4/4 | 1/0 | 4/4 | 4/4 | 0/0 | 1/1 | 1/0 | 1/1 | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethylene glycol monoethyl ether acetate | C ₈ H ₁₂ O ₃ | 000115-15-9 | — | Xn | X | 1/1 | 1/2 | 0/0 | 3/4 | 0/0 | 1/2 | (2) | 1/2 | 4/4 | 4/4 | 3/4 | 0/0 | 0/0 | 1/2 | 1/1 | (1) | 2/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | |
| Ethylene glycol monomethyl ether | C ₄ H ₈ O ₂ | 000109-86-4 | 100 % | T | X | 1/0 | | | | | | | | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | FLAMMABLE | thermoplastics | | | | | | | | | | | | | fluoroplastics | | elastomers | | metals | | COMMENT | | | | | | | | | |
|----------------------------------|---|-------------|---------------|-------------|-----------|----------------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|-----|----------------|-----|------------|------|--------|-----------|---------|-----|-----|------|------|----------------------|---|---------------------|-----|-----|
| | | | | | | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | | NBR | SI | AL | V2A | V4A | Haselloy C | | | |
| Hydrogen sulfide | H ₂ S | 007783-06-4 | saturated | F+, T+ | X | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | | | |
| Hydroquinone | C ₆ H ₂ O ₂ | 000123-31-9 | saturated | Xn | | 0/0 | 1/3 | 4/4 | (3) | 1/0 | 0/0 | (3) | 1/0 | 4/4 | 0/0 | 1/0 | 0/0 | 1/3 | 0/0 | (1) | 1/1 | (3) | 4/4 | 4/4 | 4/4 | 0/0 | (1) | 1/0 | 1/0 | 0/0 | 0/0 | Hydroquinol; Quinol | | |
| Hydroxylaluminium di(acetate) | C ₆ H ₇ AlO ₂ | 000139-12-8 | aqueous | Xn | | 1/1 | 1/1 | 1/1 | (1) | 1/0 | 1/1 | 0/0 | 0/0 | 1/3 | 1/3 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | (3) | 3/0 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | | | | | | | |
| Hydroxylamine disulfate | H ₂ N ₂ SO ₆ | 010039-54-0 | 12 % | Xn | | 1/1 | 1/1 | 0/0 | (2) | 0/0 | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 1/0 | 1/0 | 1/3 | 0/0 | (4) | 1/1 | 1/1 | 1/1 | | | | |
| Hydroxylamine disulfate | H ₂ N ₂ SO ₆ | 010039-54-0 | each | Xn | | 1/1 | 0/0 | 0/0 | (2) | 0/0 | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | (1) | (1) | (2) | 1/0 | 1/0 | 1/3 | 0/0 | (4) | 1/1 | 1/1 | 1/1 | | | | | |
| Hydroxymethyl furfural, 5- (HMF) | C ₆ H ₆ O ₅ | 000067-47-0 | | Xi | | 0/0 | 0/0 | (3) | (3) | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 4/4 | 0/0 | (1) | (1) | (3) | (3) | 4/4 | 0/0 | (1) | (1) | | | |
| Imidole | -> see: Pyrrole | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Iodine pentafluoride | JF ₅ | 007783-66-6 | | (T, C) | | 0/0 | 0/0 | 4/4 | (4) | (4) | 0/0 | 4/4 | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (2) | (3) | 4/4 | 4/4 | 4/4 | 0/0 | (3) | 0/0 | 0/0 |
| Iodine, tincture of | I ₂ | 007553-56-2 | | Xn | (X) | 1/3 | 1/3 | 4/4 | 3/4 | 0/0 | 1/1 | 1/1 | 1/2 | 3/3 | 0/0 | 4/4 | 4/4 | 3/3 | 1/1 | 0/0 | 1/1 | 1/1 | 2/0 | 1/1 | 3/3 | 0/0 | 1/0 | 2/0L | 1/0L | 1/1 | | | | |
| Iodoform | CHI ₃ | 000075-47-8 | 100 % | Xn | | 3/0 | 3/0 | (3) | 3/0 | 0/0 | 0/0 | (2) | 3/0 | 3/0 | 0/0 | 4/4 | 4/4 | 0/0 | (1) | 1/0 | (2) | 1/0 | 1/0 | (3) | 0/0 | (3) | (1) | (1) | 1/1 | | Triiodomethane; | | | |
| Isoamyl alcohol | C ₇ H ₁₆ O | 000123-51-3 | | Xn | X | 0/0 | 0/0 | (2) | 3/0 | 1/0 | 0/0 | 1/0 | 1/1 | 1/3 | 0/0 | 0/0 | 0/0 | 1/3 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 2/4 | 3/3 | 0/0 | (1) | (1) | (1) | | | | | |
| Isobutanol | C ₄ H ₁₀ O | 000078-83-1 | | Xn | X | 1/1 | 1/1 | (2) | 1/2 | (2) | 1/2 | 1/0 | 1/1 | 2/2 | 1/2 | 1/2 | 0/0 | 3/4 | 1/1 | 1/1 | (1) | 1/1 | 1/0 | 1/0 | 3/4 | 0/0 | 1/0 | (1) | (1) | 0/0 | Methyl-1-propanol, 2-; Isopropyl carbinol; Isobutyl alcohol | | | |
| Isobutyl acetate | C ₈ H ₁₆ O ₂ | 000110-19-0 | | F | X | 0/0 | 0/0 | (2) | (4) | 0/0 | (4) | 1/0 | (3) | 4/4 | 0/0 | 3/0 | 4/4 | 0/0 | 0/0 | (1) | 1/0 | (2) | 2/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0 | Methylpropyl acetate, 2-; Methylpropyl ethanoate, Beta- | | | |
| Isobutyl alcohol | -> see: Isobutanol | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Isobutyltrimethylmethane | -> see: Trimethylpentane, 2,2,4- | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| ISO-Fluid | --- | --- | liquid | Xn, N | X | 0/0 | 2/3 | (1) | (3) | 1/0 | (4) | 1/0 | 3/4 | 4/4 | 0/0 | 1/3 | 0/0 | 1/3 | 0/0 | (1) | 1/1 | (1) | 4/4 | 1/1 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | | | | |
| ISO-Fluid A | --- | --- | | (Xn, N) | (X) | 0/0 | 0/0 | (2) | (3) | 0/0 | (4) | (2) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 0/0 | 1/0 | 0/0 | (1) | (1) | (1) | | | | | |
| ISO-Fluid B | --- | --- | | (Xn, N) | (X) | 0/0 | 0/0 | (2) | (3) | 0/0 | (4) | (2) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 0/0 | 3/0 | 0/0 | (1) | (1) | (1) | | | | | |
| ISO-Fluid C | --- | --- | | (Xn, N) | (X) | 0/0 | 0/0 | (2) | (3) | 0/0 | (4) | (2) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 0/0 | 3/0 | 0/0 | (1) | (1) | (1) | | | | | |
| ISO-Fluid D | --- | --- | | (Xn, N) | (X) | 0/0 | 0/0 | (2) | (3) | 0/0 | (4) | (2) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 0/0 | 4/4 | 0/0 | (1) | (1) | (1) | | | | | |
| Iso-octane | -> see: Trimethylpentane, 2,2,4- | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Isopropyl acetate | C ₇ H ₁₄ O ₂ | 000108-21-4 | | F, Xi | X | 1/2 | 2/3 | 1/0 | 4/4 | (3) | 2/3 | 1/0 | 2/3 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 1/2 | 1/1 | 1/1 | (3) | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | 0/0 | | | | |
| Isopropyl alcohol | C ₃ H ₈ O | 000067-63-0 | techn. pure | F | X | 1/1 | 1/1 | 1/0 | 1/2 | 1/0 | 1/2 | 1/0 | 1/1 | 2/2 | 1/2 | 1/2 | 4/4 | 1/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 3/3 | 0/0 | (2) | (1) | (1) | 0/0 | | | | |
| Isopropyl carbinol | -> see: Isobutanol | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Isopropyl chloride | C ₃ H ₇ Cl | 000075-29-6 | | F, Xn | X | 0/0 | 0/0 | (2) | (4) | 0/0 | (4) | (2) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 1/0 | 4/4 | 0/0 | (3) | 0/0 | 0/0 | | | | | |
| Jam | --- | --- | | | | 1/1 | 1/1 | (1) | 1/1 | 1/1 | 0/0 | (2) | 1/1 | 1/1 | 0/0 | 1/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | (2) | 1/1 | 1/1 | 1/1 | | | |
| Juices | --- | --- | | | | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 1/0 | 1/1 | 1/1 | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | (2) | 1/1 | 1/1 | 1/1 | | | | | |
| Kapsolat | -> see: Ethylene glycol monomethyl ether oleate | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Kerosene | --- | 008008-20-6 | | (Xn) | | 2/2 | 3/4 | (1) | 4/4 | 1/1 | 2/3 | 1/1 | 3/3 | 4/4 | 2/3 | 1/1 | 0/0 | 0/0 | 2/3 | 1/1 | 1/1 | 1/1 | 4/4 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | lamp oil | | | |
| Kerosene | --- | --- | techn. pure | Xn, N | X | 1/3 | 3/4 | 1/0 | 3/0 | (1) | 0/0 | 1/1 | 1/3 | 4/4 | 1/0 | 1/0 | 3/0 | 3/4 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/0 | 1/1 | 0/0 | (2) | (1) | 1/1 | 1/1 | | | | |
| Lactames | --- | --- | | ? | | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 0/0 | 4/4 | 4/4 | 4/4 | 0/0 | (2) | (1) | (1) | | cyclic amides | | | | |
| Lactic acid | C ₃ H ₅ O ₃ | 000050-21-5 | 3 % | ? | | 1/1 | 1/2 | (3) | 1/2 | 1/0 | 1/2 | 2/4 | 1/2 | 2/2 | 1/1 | 2/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 3/4 | 1/1 | (2) | 0/0 | (1) | 1/1 | 1/1 | 1/1 | lactol | | | |
| Lactic acid | C ₃ H ₅ O ₃ | 000050-21-5 | 80 % | C | | 1/1 | 1/1 | 3/4 | 1/2 | 0/0 | 1/2 | 3/4 | 1/1 | 1/1 | 2/3 | 2/3 | 1/1 | 1/2 | 1/1 | 1/1 | 1/3 | 3/4 | 1/1 | 1/4 | 0/0 | 1/0 | 1/3 | 1/2 | 1/1 | lactol | | | | |
| Lactic acid | C ₃ H ₅ O ₃ | 000050-21-5 | 85 % | C | | 1/1 | 1/1 | 3/4 | 1/2 | 0/0 | 1/2 | 3/4 | 1/2 | 2/2 | 1/1 | 2/3 | 2/3 | 1/1 | 1/2 | 1/1 | 1/1 | 1/3 | 3/4 | 1/1 | 1/4 | 0/0 | 1/0 | 1/3 | 1/2 | 1/1 | lactol | | | |
| Lactose | C ₁₂ H ₂₂ O ₁₁ | 000063-42-3 | aqueous | --- | | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (1) | 1/1 | 1/1 | 0/0 | | | | |
| Lanolin | --- | 008006-54-0 | techn. pure | --- | | 3/3 | 3/3 | 1/0 | 1/0 | 1/0 | (2) | 3/3 | 1/1 | 0/0 | 3/3 | 3/3 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/1 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | | | | | |
| Lard | --- | --- | | --- | | 0/0 | 0/0 | (2) | (1) | 1/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 2/0 | 1/0 | 1/0 | 0/0 | (1) | 1/1 | 1/1 | | | | | | |
| Latex | --- | --- | | ? | | 0/0 | 0/0 | 1/0 | (2) | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | (1) | (3) | (1) | (2) | 0/0 | (2) | (1) | (1) | 1/1 | dispersion of rubber | | | | |
| Laurel | --- | --- | ground | ? | | 0/0 | 0/0 | (2) | (2) | (2) | 0/0 | (2) | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | (1) | (1) | (1) | (2) | (1) | (2) | 0/0 | (1) | (1) | (1) | | | | | |
| Lauryl alcohol | C ₁₂ H ₂₆ O | 000112-53-8 | 100 % | Xi | | 0/0 | 0/0 | (2) | (2) | 1/0 | 0/0 | (2) | 1/1 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/0 | 3/3 | 0/0 | (1) | (1) | (1) | 0/0 | | | | |
| Lauryl chloride | C ₁₂ H ₂₅ Cl | 000112-52-7 | 100 % | (Xi) | | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/0 | (1) | 4/4 | (1) | (3) | 0/0 | (3) | 0/0 | 0/0 | | | | | | |
| Lavender oil | --- | 008000-28-0 | | (Xi) | | 0/0 | 0/0 | (2) | (3) | 0/0 | (4) | (2) | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 1/0 | 3/0 | 0/0 | (1) | (1) | (1) | | | | | | |
| Lead acetate | C ₄ H ₆ PbO ₄ | 000301-04-2 | aqueous | T, N | | 1/1 | 1/1 | 3/0 | 1/0 | (2) | 1/0 | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 2/2 | 3/0 | 0/0 | 4/4 | 1/1 | 1/1 | | | | | |
| Lead acetate | C ₄ H ₆ PbO ₄ | 000301-04-2 | | T, N | | 1/1 | 1/1 | 3/0 | 1/0 | (2) | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 2/ | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | thermoplastics | | | | | | | | | | | | | | fluoroelastics | | elastomers | | metals | | COMMENT | | | | | | | |
|-----------------------------|---|-------------|-----------------------|---------------------------|----------------|------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|-----|----------------|-----|------------|------|--------|-----------|---------|-----|-----|------|------|-----|---|--|
| | | | | | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | | NBR | SI | AL | V2A | V4A | Haselloy C | |
| Molasses | — | — | — | — | 1/1 | 1/1 | 1/0 | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | (2) | (1) | (1) | | | | |
| Molasses wort | — | — | — | ? | 1/1 | 1/1 | 1/0 | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | (2) | (1) | (1) | | | | |
| Monochlorobenzene (MCB) | — | — | -> see: Chlorobenzene | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | | | |
| Monochloroethane | C ₂ H ₅ Cl | 000075-00-3 | — | F+, Xn | X | 3/3 | 3/4 | 1/0 | 4/4 | 0/0 | 3/4 | 1/0 | 3/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 1/1 | 1/1 | 1/0 | 1/1 | 4/4 | 3/0 | 4/4 | 0/0 | (3) | 1/1L | 1/1L | 0/0 | Ethyl chloride; Chloroethane, 1- | |
| Morpholine | C ₄ H ₉ NO | 000110-91-8 | — | techn. pure | C, Xn | X | 1/1 | 1/1 | (3) | (3) | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | (1) | 1/1 | 1/3 | 3/0 | 2/3 | 4/4 | 0/0 | 1/0 | (1) | (1) | 0/0 | |
| Motor oil | — | — | — | ? | ? | ? | 0/0 | 0/0 | 1/0 | (2) | (1) | 0/0 | 1/1 | 1/3 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | 1/1 | 4/4 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | | | |
| Mowliith D | — | — | — | ? | ? | ? | 1/0 | 0/0 | (2) | 0/0 | (2) | 0/0 | (2) | 1/0 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/0 | (2) | (2) | (2) | 0/0 | (2) | (1) | (1) | 0/0 | dispersion of polyvinyl acetate; Clariant | |
| Muscate | — | — | — | ground | ? | ? | 0/0 | 0/0 | (2) | 4/4 | (2) | 0/0 | (2) | 4/4 | 0/0 | 0/0 | 0/0 | 3/3 | 0/0 | (1) | (1) | (2) | (2) | (2) | 0/0 | (1) | (1) | (1) | | | | |
| Mustard | — | — | — | — | — | — | 0/0 | 0/0 | (2) | 1/0 | (1) | 0/0 | 1/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | (1) | (1) | (2) | 1/0 | 1/0 | 0/0 | (2) | 1/0L | 1/0L | | | |
| Naphtha | — | 008032-32-4 | — | (Xn) | — | — | 1/3 | 3/4 | 1/0 | (2) | (1) | 1/0 | 1/0 | 1/3 | 3/0 | 1/0 | 1/0 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 1/1 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | petroleum ether | |
| Naphthalene | C ₁₀ H ₈ | 000091-20-3 | — | 100 % | F, Xn | X | 0/0 | 1/3 | 1/0 | (3) | 0/0 | 0/0 | 1/2 | 1/3 | 3/4 | 1/0 | 4/4 | 4/4 | 1/4 | 0/0 | (1) | 1/1 | 1/3 | 4/4 | 1/1 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | |
| Naphthalene (in alcohol) | — | — | — | — | F, Xn | X | 1/4 | 1/4 | (2) | (3) | 0/0 | 0/0 | 1/2 | 1/3 | 3/4 | 0/0 | 0/0 | 0/0 | 3/4 | 0/0 | (1) | 1/1 | (2) | 4/4 | (3) | (3) | 0/0 | (1) | (1) | 0/0 | | |
| Neon | Ne | 007440-01-9 | — | — | — | — | 0/0 | 0/0 | 1/0 | (1) | 1/1 | 0/0 | 1/1 | (1) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (1) | 1/1 | 1/1 | 1/1 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | | | |
| Nickel acetate | C ₄ H ₇ NO ₄ | 000373-02-4 | — | aqueous | (T, N) | — | 1/1 | 1/1 | (3) | (2) | (1) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | (3) | 3/0 | 0/0 | 4/4 | 0/0 | 0/0 | | |
| Nickel dichloride | NiCl ₂ | 00718-54-9 | — | saturated | T | — | 1/1 | 1/1 | 1/0 | (2) | (1) | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | 2/0L | 2/0L | 1/1 | | |
| Nickel dichloride | NiCl ₂ | 00718-54-9 | — | aqueous | T | — | 1/1 | 1/1 | (3) | (2) | (1) | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | 2/0L | 2/0L | 1/1 | | |
| Nickel sulfate | NiSO ₄ | 007786-81-4 | — | saturated | Xn | — | 1/1 | 1/1 | 1/0 | 1/0 | (1) | 1/0 | 2/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/3 | 1/1 | 0/0 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | | |
| Nickel sulfate | NiSO ₄ | 007786-81-4 | — | aqueous | Xn | — | 1/1 | 1/1 | (3) | 1/0 | (1) | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | |
| Nickelous nitrate | Ni(NO ₃) ₂ | 013138-45-9 | — | saturated | (O, Xn) | — | 1/1 | 1/1 | (3) | (2) | (1) | 1/0 | (2) | 1/1 | 1/0 | 1/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | 1/0 | 1/0 | 1/1 | |
| Nicotine | C ₁₀ H ₁₄ N ₂ | 000054-11-5 | — | — | T+ | — | 1/0 | 1/0 | (3) | (3) | 0/0 | 0/0 | (2) | 1/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 1/0 | 1/0 | 1/0 | 0/0 | (1) | (1) | (1) | 0/0 | | |
| Nicotinic acid | C ₆ H ₇ NO ₂ | 000059-67-6 | — | diluted | Xi | — | 1/1 | 1/1 | (3) | (2) | 0/0 | 0/0 | (3) | 1/0 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 1/1 | (1) | (2) | (2) | (3) | (2) | 0/0 | (3) | 0/0 | 0/0 | 0/0 | |
| Nitric acid | HNO ₃ | 007697-37-2 | — | 1-10 % | C | — | 1/1 | 1/1 | 4/4 | 1/2 | (2) | 1/1 | 4/4 | 1/1 | 2/4 | 1/3 | 1/2 | 0/0 | 1/3 | 1/1 | 1/1 | 1/1 | 2/0 | 1/1 | 4/4 | 0/0 | 3/4 | 1/1 | 1/1 | 1/1 | | |
| Nitric acid | HNO ₃ | 007697-37-2 | — | 50 % | C+ | — | 2/4 | 3/4 | 4/4 | 4/4 | (2) | 2/4 | 4/4 | 3/4 | 4/4 | 2/3 | 2/3 | 0/0 | 0/3 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 1/0 | 4/4 | 0/0 | 4/4 | 1/2 | 1/2 | 1/2 | |
| Nitric acid | HNO ₃ | 007697-37-2 | — | 66 % | C+ | — | 2/4 | 3/4 | 4/4 | 4/4 | (4) | 2/3 | 4/4 | 4/4 | 4/4 | 3/4 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 1/0 | 4/4 | 0/0 | 4/4 | 1/2 | 1/2 | 1/2 | | |
| Nitric acid | HNO ₃ | 007697-37-2 | — | 100 % | O, C+ | — | 4/4 | 4/4 | 4/4 | 4/4 | (4) | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 4/4 | 0/0 | 4/4 | 0/0 | 0/0 | 1/1 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 1/1 | 2/3 | 3/3 | ? | |
| Nitric acid | HNO ₃ | 007697-37-2 | — | 70 % | O, C+ | — | 2/4 | 3/4 | 4/4 | 4/4 | (4) | 2/3 | 4/4 | 4/4 | 4/4 | 3/4 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 2/3 | 4/4 | 0/0 | 4/4 | 1/2 | 1/2 | 1/2 | | |
| Nitric acid | — | — | — | -> see: Ammonium nitrate | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | |
| Nitric acid, magnesium salt | — | — | — | -> see: Magnesium nitrate | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | |
| Nitric acid, potassium salt | — | — | — | -> see: Potassium nitrate | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | |
| Nitro benzoic acid | C ₇ H ₅ NO ₄ | — | — | (Xn) | — | — | 1/0 | 1/0 | (3) | (3) | 0/0 | 0/0 | (3) | 1/0 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 3/0 | (3) | (2) | 0/0 | (3) | 0/0 | 0/0 | | isomer not indicated in the source |
| Nitro reducer | — | — | — | ? | X | — | 0/0 | 0/0 | 3/0 | (4) | 0/0 | (4) | (3) | (3) | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | (3) | (4) | 4/4 | 0/0 | (1) | (1) | (1) | | solvent cleaner mixture |
| Nitrobenzene | C ₆ H ₅ NO ₂ | 000098-95-3 | — | T | — | — | 3/4 | 4/4 | 4/4 | 4/4 | 1/0 | 4/4 | 3/0 | 2/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 1/2 | 1/1 | 1/1 | 1/1 | 4/4 | 4/4 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | |
| Nitroethane | C ₂ H ₅ NO ₂ | 000079-24-3 | — | Xn | X | — | 0/0 | 0/0 | (3) | (4) | 0/0 | (3) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | | |
| Nitrogen | N ₂ | 007727-37-9 | — | — | — | — | 0/0 | 0/0 | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | | | |
| Nitrogen hydride | — | — | — | -> see: Hydrazine | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — |
| Nitrogen tetroxide | N ₂ O ₄ | 010544-72-6 | — | (O), T+, C | — | — | 0/0 | 0/0 | 3/0 | (3) | 1/0 | 0/0 | 4/4 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (2) | 4/4 | 4/4 | 4/4 | 0/0 | (2) | (1) | (1) | | | |
| Nitroglycerine | C ₃ H ₅ (NO ₃) ₃ | 000055-63-0 | — | diluted | (E, T+) | — | 0/0 | 0/0 | (3) | (3) | 0/0 | (2) | (2) | 0/0 | 0/0 | 3/0 | 4/4 | 0/0 | 0/0 | (1) | (1) | (3) | 1/0 | 1/0 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | | |
| Nitrohydrochloric acid | HNO ₃ + HCl | 008007-56-5 | — | — | C | — | 4/4 | 4/4 | 4/4 | 4/4 | 3/3 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 3/4 | 1/1 | (2) | 1/1 | 3/0 | 4/4 | 4/4 | 0/0 | 4/4 | 4/4 | 4/4 | 4/4 | | aqua regia: mixture of hydrochloric acid and nitric acid |
| Nitropropane | C ₃ H ₇ NO ₂ | — | — | (T) | — | — | 0/0 | 0/0 | (3) | (4) | 0/0 | (3) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | isomer not indicated in the source | |
| Nitrose gases | — | — | — | diluted | T | — | 1/1 | 0/0 | 3/0 | 4/4 | 0/0 | 4/4 | 1/4 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 3/0 | 4/4 | 0/0 | (2) | (1) | (1) | 0/0 | nitrogen monoxide + nitrogen dioxide | |
| Nitrotoluene | C ₇ H ₇ NO ₂ | 001321-12-6 | — | techn. pure | T | — | 1/3 | 1/3 | 4/4 | 4/4 | 1/0 | (4) | 3/0 | 1/3 | 4/4 | 0/0 | 4/4 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 4/4 | 4/4 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | | |
| Nitrous acid, sodium salt | — | — | — | -> see: Sodium nitrite | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | — | |
| Nitrous oxide | N ₂ O | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | thermoplastics | | | | | | | | | | | | | | | | fluoroplastics | | elastomers | | metals | | COMMENT | | | | | | | | |
|------------------------------------|---|-------------|---------------|-------------|----------------|------|------|-----|-----|------|-----|-----|-------|-----|-----|----------|-----------|-----|--------------|-----|----------------|------|------------|-----------|--------|-----|---------|------|------|-----|------------|-----|-----|--|--|
| | | | | | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | SI | | AL | V2A | V4A | Haselloy C | | | | |
| Propanone, 2- | -> see: Acetone | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Propargyl alcohol | C ₃ H ₄ O | 000107-19-7 | 7 % | Xn | | 1/1 | 1/1 | (3) | 1/0 | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/1 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/3 | 1/0 | 1/1 | 1/1 | 0/0 | 1/0 | (1) | (1) | 0/0 | | | | | |
| Propenenitrile, 2- | -> see: Acrylonitrile | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Propenyl alcohol | -> see: Allyl alcohol | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Propionic acid | C ₃ H ₆ O ₂ | 000079-09-4 | 50 % | C | | 1/3 | 1/3 | 3/3 | 4/4 | 0/0 | 0/0 | 4/4 | 1/1 | 4/4 | 4/4 | 1/3 | 3/3 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/1 | 4/4 | 0/0 | 1/1 | (1) | (1) | 1/1 | | | | | |
| Propionic acid | C ₃ H ₆ O ₂ | 000079-09-4 | | C | | 1/3 | 1/3 | 3/3 | 4/4 | 0/0 | 0/0 | 4/4 | 1/3 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | 0/0 | 1/0 | 1/1 | 1/1 | 4/4 | 3/0 | 4/4 | 0/0 | 1/1 | 1/2 | 1/1 | 1/1 | | | | | |
| Propyl acetate, normal | C ₆ H ₁₀ O ₂ | 000109-60-4 | | F | X | 0/0 | 0/0 | (1) | 4/4 | 0/0 | (4) | 1/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | | | | | | |
| Propyl alcohol | C ₃ H ₈ O | 000071-23-8 | | F | X | 1/1 | 1/1 | 1/0 | 1/0 | 0/0 | 1/1 | 3/0 | 0/0 | 2/2 | 3/3 | 1/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 3/3 | 0/0 | 1/1 | (1) | (1) | 0/0 | | | | | | | |
| Propyl carbinol | -> see: Butyl alcohol, normal | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Propyl nitrate | C ₃ H ₇ NO ₃ | 000627-13-4 | | (E, Xn) | (X) | 0/0 | 0/0 | (3) | (3) | 0/0 | 0/0 | (3) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | 3/0 | 4/4 | 4/4 | 0/0 | (2) | (1) | (1) | | | | | | |
| Propylamine, n- | C ₃ H ₉ N | 000107-10-8 | | F, C, Xn | X | 0/0 | 0/0 | 0/0 | (3) | 0/0 | 0/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 4/4 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | | | | | |
| Propylene | C ₃ H ₆ | 000115-07-1 | | F+ | X | 1/1 | 1/1 | 1/0 | (3) | 1/0 | 0/0 | 1/0 | 1/1 | 4/4 | 0/0 | 3/4 | 4/4 | 0/0 | 0/0 | (1) | 1/1 | (1) | 4/4 | 1/0 | 4/4 | 0/0 | 1/1 | 1/1 | | | | | | | |
| Propylene glycol | C ₃ H ₈ O ₂ | 000057-55-6 | | | | 1/1 | 1/1 | 4/4 | 2/3 | (2) | 1/1 | 1/0 | 1/1 | 1/1 | 2/2 | 3/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/3 | 0/0 | 1/1 | (1) | (1) | 1/1 | | | | | |
| Propylene oxid | C ₃ H ₆ O | 000075-56-9 | | F+, T | X | 1/1 | 1/2 | (3) | 2/3 | 0/0 | 1/2 | (2) | 1/2 | 4/4 | 2/2 | 3/4 | 0/0 | 4/4 | 3/4 | 1/1 | 1/0 | 1/4 | 3/0 | 4/4 | 4/4 | 0/0 | (1) | (1) | 0/0 | | | | | | |
| Pydraul C (312, 540) | | | | (Xn) | | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 0/0 | 4/4 | 1/0 | 4/4 | 0/0 | 0/0 | (1) | (1) | | | | | | |
| Pydraul E (29, 30, 50, 65, 90, 11) | | | | (Xn) | | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 0/0 | 1/0 | 1/0 | 4/4 | 0/0 | 0/0 | (1) | (1) | | | | | | |
| Pyridine | C ₅ H ₅ N | 000110-86-1 | | F, Xn | X | 1/3 | 0/2 | 1/0 | 4/4 | 0/0 | 0/2 | 1/1 | 3/3 | 4/4 | 4/4 | 4/4 | 4/4 | 1/1 | (2) | 1/1 | 1/3 | 4/4 | 4/4 | 4/4 | 0/0 | 1/1 | 1/1 | 0/0 | | | | | | | |
| Pyrogallic acid | C ₆ H ₆ O ₃ | 000087-66-1 | | Xn | | 0/0 | 0/0 | 1/0 | (3) | 0/0 | 0/0 | 3/4 | 1/0 | 3/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/3 | 0/0 | (1) | (1) | 1/1 | (3) | (3) | (3) | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | | | |
| Pyroigneous oil | | 008001-20-5 | | | | 0/0 | 0/0 | (1) | (2) | 1/0 | 0/0 | (1) | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (1) | 4/4 | (1) | 1/0 | 0/0 | 1/1 | (1) | (1) | | | | | | |
| Pyrrrole | C ₄ H ₅ N | 000109-97-7 | | Xn | X | 0/0 | 0/0 | (3) | (4) | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (3) | 4/4 | 4/4 | 4/4 | 0/0 | (1) | (1) | (1) | | | | | | |
| Quinine | C ₂₀ H ₂₄ N ₂ O ₂ | 000130-95-0 | | Xn | | 1/1 | 1/1 | (2) | (2) | (2) | 0/0 | (1) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | (1) | (2) | (2) | (1) | 0/0 | (2) | (1) | (1) | 0/0 | | | | |
| Quinol | -> see: Hydroquinone | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Ramasit | | | | ? | | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | | |
| Resorcinol | C ₆ H ₆ O ₂ | 000108-46-3 | 5 % | | | 1/1 | 1/1 | 4/4 | 2/3 | 0/0 | 1/1 | (3) | 1/1 | 2/3 | 4/4 | 2/4 | 0/0 | 3/3 | 1/3 | 1/1 | (1) | (3) | (3) | (3) | (3) | (3) | 0/0 | (2) | 0/0 | 0/0 | 0/0 | | | | |
| Resorcinol | C ₆ H ₆ O ₂ | 000108-46-3 | saturated | Xn | | 1/1 | 1/1 | 4/4 | 2/3 | 0/0 | 1/1 | (3) | 1/1 | 2/3 | 4/4 | 3/4 | 0/0 | 0/0 | 1/1 | (1) | (1) | (3) | (3) | (3) | (3) | 0/0 | (2) | 0/0 | 0/0 | 0/0 | | | | | |
| Roaster off-gas | | | each | (T) | | 0/0 | 0/0 | (2) | 0/0 | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 1/0 | 1/0 | 4/4 | 0/0 | (4) | (2) | (2) | 0/0 | | | | | |
| Rose oil | | 008007-01-0 | | ? | | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | 2 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 3/0 | 0/0 | (1) | (1) | (2) | (3) | (3) | (3) | 0/0 | (1) | (1) | (1) | | | | | |
| Rum ether | | 008030-89-5 | | ? | | 0/0 | 0/0 | (2) | (3) | 0/0 | 0/0 | (2) | 2 | 4/4 | 0/0 | 0/0 | 0/0 | 1/0 | 0/0 | (1) | (1) | (3) | (3) | (4) | (3) | 0/0 | (1) | (1) | (1) | | | | | | |
| Sagrotan | | | liquid | ? | | 1/2 | 1/3 | 0/0 | 3/0 | 0/0 | 0/0 | (3) | 1/3 | 3/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (1) | (2) | 1/0 | 1/0 | 3/0 | 0/0 | (2) | (1) | (1) | | | | | | |
| Salicyl acid | C ₇ H ₆ O ₃ | 000069-72-7 | saturated | (Xn, Xi) | | 1/1 | 1/1 | 1/0 | 1/2 | 1/0 | 1/1 | 4/4 | 1/1 | 1/2 | 1/1 | 2/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 1/0 | 3/3 | 0/0 | 1/0 | 1/0 | 1/0 | | | | | | |
| Salicyl acid | C ₇ H ₆ O ₃ | 000069-72-7 | powder | Xn, Xi | | 1/1 | 1/1 | 1/0 | 1/2 | (1) | 1/2 | (3) | 1/1 | 1/1 | 1/1 | 2/3 | 0/0 | 0/0 | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 1/0 | 3/3 | 0/0 | 1/0 | 1/0 | 1/0 | | | | | | |
| Salicylaldehyde | C ₇ H ₆ O ₂ | 000090-02-8 | | Xn, Xi | | 1/1 | 1/2 | (3) | 2/3 | 0/0 | 1/2 | (3) | 1/2 | 4/4 | 3/3 | 3/4 | 0/0 | 0/0 | 1/4 | 1/1 | (1) | (3) | (3) | (3) | 4/4 | 0/0 | (2) | (1) | (1) | 1/1 | | | | | |
| Salt spring | NaCl | 007647-14-5 | saturated | | | 1/1 | 1/1 | 1/0 | (1) | (1) | 0/0 | 1/2 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 3/4 | 1/3 | 1/2 | 0/0 | | | | | |
| Salt water, sea water | | | | | | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 3/4 | 1/3L | 1/2L | 1/1 | | | | | | |
| Saltpeter | -> see: Potassium nitrate | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Saturated steam condensate | | | | ? | | 0/0 | 0/0 | (2) | (2) | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | (2) | (2) | (2) | (2) | 0/0 | (2) | 1/1 | 1/1 | | | | | | |
| Sea water | | | | | | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 3/4 | 1/3L | 1/2L | 1/1 | | | | | |
| Silicofluoric acid | H ₂ SiF ₆ | 016961-83-4 | 32 % | C | | 1/1 | 1/1 | 4/4 | 1/0 | 4/4 | 0/0 | 4/4 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 3/0 | 2/2 | 3/4 | 0/0 | 4/4 | (2) | 1/1 | 1/1 | | | | | |
| Silicone greases | | | | (-) | | 0/0 | 0/0 | 1/0 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (1) | (1) | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | | | | | |
| Silicone oil | | | | ? | | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 1/1 | 1/1 | 3/3 | 1/0 | 1/4 | 0/0 | 1/1 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | | | | | |
| Silver acetate | C ₂ H ₃ AgO ₂ | 000563-63-3 | | Xi | | 1/1 | 1/1 | (2) | 1/2 | (2) | 1/1 | (2) | 1/1 | 2/2 | 1/1 | 2/2 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | (1) | (2) | (3) | 0/0 | (4) | 0/0 | 0/0 | 0/0 | | | | | | |
| Silver cyanide | CAgN | 000506-64-9 | | T | | 1/1 | 1/1 | (2) | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (1) | (1) | (1) | (1) | (3) | 0/0 | (4) | 0/0 | 0/0 | | | | | | |
| Silver nitrate | AgNO ₃ | 007761-88-8 | aqueous | C | | 1/1 | 0/0 | 1/0 | 1/1 | (2) | 0/0 | 1/0 | 1/1</ | | | | | | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | FLAMMABLE | thermoplastics | | | | | | | | | | | | | | | | | fluoro | elastomers | metals | COMMENT | | | | | | | |
|---------------------------------|---|-------------|---------------|-------------|-----------|----------------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|-----|--------------|-----|------|------|--------|------------|--------|---------|-----|------|------|------|--------------------------------|--|---|
| | | | | | | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | | SI | AL | V2A | V4A | Haselloy C | | |
| Sodium carbonate | Na ₂ CO ₃ | 000497-19-8 | | Xi | | 1/1 | 1/1 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 2/0 | 0/0 | 1/1 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 2/3 | 0/0 | 1/0 | 1/1L | 1/1L | 1/1 | Chloric acid, sodium salt; | |
| Sodium chlorate | NaClO ₃ | 007775-09-9 | each | O, Xn | | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 1/0 | 2/0 | 1/1 | 1/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 2/3 | 0/0 | 1/0 | 1/1L | 1/1L | 1/1 | Chloric acid, sodium salt; | | |
| Sodium chlorite | NaClO ₂ | 007775-09-9 | aqueous | O, Xn | | 0/0 | 0/0 | 3/0 | 1/0 | 1/0 | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 3/3 | 0/0 | 1/0 | 1/1L | 1/1L | 1/1 | | | |
| Sodium chloride | NaCl | 007647-14-5 | each | | | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 1/0 | 1/2 | 1/1 | 1/1 | 1/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 3/4 | 1/2 | 1/2 | 1/1 | | |
| Sodium chloride | NaCl | 007647-14-5 | aqueous | | | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/2 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 3/4 | 1/2 | 1/2 | 1/1 | | |
| Sodium chlorite | NaClO ₂ | 007758-19-2 | diluted | (O, Xn) | | 1/0 | 1/3 | 1/4 | (2) | 0/0 | 0/0 | (2) | 1/3 | 0/0 | 0/0 | 3/0 | 4/4 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 4/4 | 0/0 | 3/4 | 3/4 | 3/3 | 0/0 | | | |
| Sodium chromate | NaCrO ₄ | 007775-11-3 | diluted | T | | 1/0 | 1/0 | 1/1 | (2) | 0/0 | 0/0 | (2) | 1/1 | 1/1 | 0/0 | 1/3 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 1/3 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | | | |
| Sodium cyanide | CNNa | 000143-33-9 | aqueous | T | | 1/1 | 1/1 | 1/0 | (3) | 0/0 | 0/0 | 3/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 3/3 | 0/0 | 4/4 | (2) | (2) | 0/0 | Hydrocyanic acid, sodium salt; | | |
| Sodium cyanide | CNNa | 000143-33-9 | aqueous | T | | 1/1 | 1/1 | 1/0 | (3) | 1/0 | 0/0 | 3/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | (2) | (2) | 0/0 | | | |
| Sodium dichromate | Na ₂ Cr ₂ O ₇ | 010588-01-9 | | T | | 0/0 | 1/1 | 1/0 | 1/0 | 3/0 | 1/1 | (3) | 1/1 | 1/1 | 0/0 | 1/0 | 0/0 | 0/0 | 1/1 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 3/3 | 0/0 | 1/1 | (1) | (1) | 1/1 | | | |
| Sodium dithionite | -> see: Sodium hydrosulfite | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Sodium dodecylbenzene sulfonate | C ₁₈ H ₃₅ NaSO ₃ | 025155-30-0 | | Xn | | 1/1 | 1/1 | (2) | (2) | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | (1) | (1) | (1) | (2) | 0/0 | (2) | (1) | (1) | | | | |
| Sodium ferrocyanide | C ₆ FeNa ₆ N ₆ | 013601-19-9 | | Xn | | 1/1 | 1/1 | (1) | (2) | (1) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | (1) | (1) | (1) | (2) | 0/0 | (1) | (1) | (1) | | | |
| Sodium fluoride | NaF | 007681-49-4 | saturated | T | | 1/1 | 1/1 | 1/0 | (2) | (1) | 1/0 | 1/1 | 1/0 | 0/0 | 1/0 | 1/3 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | | | | |
| Sodium hydrosulfite | Na ₂ S ₂ O ₄ | 007775-14-6 | 10 % | Xn | | 1/1 | 0/0 | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/3 | 1/0 | 1/1 | 3/3 | 0/0 | 4/4 | 1/1 | 1/1 | | | | Sodium dithionite; Dithionous acid, disodium salt; Sodium sulfoxylate; | |
| Sodium hydrosulfite | Na ₂ S ₂ O ₄ | 007775-14-6 | | Xn | | 1/1 | 0/0 | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | 1/3 | 1/0 | 1/1 | 3/3 | 0/0 | 4/4 | 1/1 | 1/1 | | | | | |
| Sodium hydroxide | NaOH | 001310-73-2 | concentrated | C | | 1/1 | 1/1 | 1/3 | 4/4 | 4/4 | (3) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (2) | 1/0 | 4/4 | 3/4 | 0/0 | 4/4 | (2) | (2) | ? | | | caustic soda, sodium hydrate, soda lye | |
| Sodium hydroxide | NaOH | 001310-73-2 | 30 % | C+ | | 1/1 | 1/1 | 1/0 | 4/4 | 4/4 | 1/0 | 1/3 | 1/1 | 1/0 | 1/0 | 1/3 | 1/3 | 0/0 | 0/0 | 1/1 | 1/1 | (2) | 1/0 | (3) | 2/3 | 0/0 | 4/4 | 1/3 | 1/3 | 1/1 | | | caustic soda, sodium hydrate, soda lye |
| Sodium hydroxide | NaOH | 001310-73-2 | 45 % | C+ | | 1/1 | 1/1 | 1/0 | 4/4 | 4/4 | 1/0 | 1/3 | 1/1 | 1/1 | 1/0 | 1/3 | 1/3 | 1/1 | 0/0 | 0/0 | 1/1 | (2) | 1/0 | 2/4 | 2/3 | 0/0 | 4/4 | 1/3 | 1/3 | 1/1 | | | caustic soda, sodium hydrate, soda lye |
| Sodium hydroxide | NaOH | 001310-73-2 | 50 % | C+ | | 1/1 | 1/1 | 1/0 | 4/4 | 4/4 | 1/1 | 1/3 | 1/1 | 2/2 | 1/1 | 1/2 | 0/0 | 0/3 | 1/1 | 1/1 | 1/1 | 3/3 | 1/0 | 3/4 | 3/3 | 0/0 | 4/4 | 1/3 | 1/3 | 1/1 | | | caustic soda, sodium hydrate, soda lye |
| Sodium hydroxide | NaOH | 001310-73-2 | 60 % | C+ | | 1/1 | 1/1 | 1/0 | 4/4 | 4/4 | 1/0 | (3) | 1/1 | 1/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | (2) | 1/0 | 3/4 | 2/3 | 0/0 | 4/4 | 1/3 | 1/3 | 1/1 | | | caustic soda, sodium hydrate, soda lye |
| Sodium hydroxide | NaOH | 001310-73-2 | 1 % | Xi | | 1/1 | 1/1 | 1/0 | 3/4 | (3) | 1/1 | 1/1 | 2/2 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/3 | 0/0 | (4) | 1/1 | 1/1 | 1/1 | | | caustic soda, sodium hydrate, soda lye | |
| Sodium hypochlorite | NaClO | 007681-52-9 | diluted | (O, C) | | 2/3 | 2/3 | 4/4 | (3) | 3/0 | 1/3 | 4/4 | 2/3 | 1/3 | 1/1 | 1/3 | 1/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 3/0 | 1/3 | 4/4 | 0/0 | 4/4 | 3/3L | 2/2L | 0/0 | | | sodium oxychloride, sodium chloride oxide |
| Sodium hypochlorite | NaClO | 007681-52-9 | 15 % | O, C | | 2/3 | 2/3 | 4/4 | 2/3 | (3) | 1/3 | 4/4 | 2/3 | 1/3 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 3/4 | 3/0 | 1/3 | 4/4 | 0/0 | 4/4 | 3/3L | 2/2L | 0/0 | | | sodium oxychloride, sodium chloride oxide |
| Sodium hypochlorite | NaClO | 007681-52-9 | saturated | O, C | | 2/3 | 2/3 | 4/4 | 2/3 | (3) | 1/3 | 4/4 | 2/3 | 1/3 | 1/1 | 1/3 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | (3) | 3/0 | 1/3 | 4/4 | 0/0 | 4/4 | 3/3L | 2/2L | 0/0 | | | sodium oxychloride, sodium chloride oxide |
| Sodium hypochlorite | NaClO | 007681-52-9 | 12,5 % Cl | O, C | | 2/3 | 2/3 | 4/4 | 2/3 | (3) | 1/3 | 4/4 | 2/3 | 1/3 | 1/1 | 1/3 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 3/0 | 1/3 | 4/4 | 0/0 | 4/4 | 3/3L | 2/2L | 0/0 | | | sodium oxychloride, sodium chloride oxide |
| Sodium iodide | NaI | 007681-82-5 | each | Xi | | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | 1/1 | 1/0 | 0/0 | 1/3 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/3 | (1) | (1) | 1/1 | 0/0 | 1/1 | 3/4 | 3/4 | 0/0 | | | | |
| Sodium metabisulfite | Na ₂ S ₂ O ₅ | 007681-57-4 | each | Xn | | 1/1 | 1/1 | 1/0 | (2) | (2) | 0/0 | 4/4 | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 1/0 | 1/1 | 1/1 | | | | |
| Sodium nitrate | NaNO ₃ | 007631-99-4 | saturated | O, Xn | | 1/1 | 1/1 | 1/0 | 1/0 | (1) | 1/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 2/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | | chile saltpeter |
| Sodium nitrate | NaNO ₃ | 007631-99-4 | aqueous | O, Xn | | 1/1 | 1/1 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | | chile saltpeter |
| Sodium nitrite | NaNO ₂ | 007632-00-0 | saturated | O, T | | 1/1 | 1/1 | 1/0 | (2) | (1) | 1/0 | 1/1 | 1/1 | 1/1 | 0/0 | 1/0 | 1/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 2/3 | 0/0 | 1/0 | 1/1 | 1/1 | 1/1 | | | Nitrous acid, sodium salt; |
| Sodium nitrite | NaNO ₂ | 007632-00-0 | aqueous | O, T | | 1/1 | 1/1 | 1/0 | (2) | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | 1/0 | 1/1 | 1/1 | 1/1 | | | |
| Sodium oxalate | C ₂ Na ₂ O ₄ | 000062-76-0 | saturated | Xn | | 1/1 | 1/1 | (1) | (1) | (1) | 0/0 | 1/1 | 1/1 | 0/0 | 1/3 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/3 | (1) | 1/0 | 1/0 | 0/0 | 1/1 | (2) | (2) | | | | | |
| Sodium perborate | NaBO ₂ (HO) ₂ x 3H ₂ O | 013517-20-9 | saturated | (O, Xn) | | 1/1 | 1/1 | 4/4 | (2) | 0/0 | 0/0 | 2/0 | 1/1 | 1/1 | 0/0 | 1/0 | 3/0 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 3/0 | 0/0 | 1/0 | 1/0 | 1/0 | 1/0 | | | |
| Sodium perborate | NaBO ₂ (HO) ₂ x 3H ₂ O | 013517-20-9 | aqueous | (O, Xn) | | 1/1 | 1/1 | 4/4 | (2) | 3/0 | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | 3/0 | 0/0 | 1/0 | 1/0 | 1/0 | 1/0 | | | |
| Sodium perchlorate | NaClO ₄ | 007601-89-0 | saturated | O, Xn | | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | (1) | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | | |
| Sodium peroxide | Na ₂ O ₂ | 001313-60-6 | 10 % | O, C+ | | 0/0 | 1/3 | 4/4 | (3) | (4) | 0/0 | 4/4 | 2/2 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/0 | 1/0 | 3/0 | 0/0 | 4/4 | 1/1 | 1/1 | 0/0 | | | | |
| Sodium peroxide | Na ₂ O ₂ | 001313-60-6 | saturated | O, C+ | | 0/0 | 3/3 | 4/4 | (3) | (4) | 0/0 | 4/4 | 2/2 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/0 | 1/0 | (4) | 0/0 | 4/4 | (2) | (2) | 0/0 | | | |
| Sodium persulfate | Na ₂ S ₂ O ₈ | 007775-27-1 | saturated | O, Xi | | 1/1 | 0/0 | 4/4 | (2) | 0/0 | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 1/3 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/0 | 1/0 | (3) | 0/0 | 4/4 | 0/0 | 1/0 | 0/0 | | | |
| Sodium phosphate | Na ₃ PO ₄ x 12H ₂ O | 010101-89-0 | saturated | Xi | | 1/1 | 1/1 | 1/0 | (2) | (1) | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 | 1/3 | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | thermoplastics | | | | | | | | | | | | | fluoroelastics | | | elastomers | | | metals | | | COMMENT | | | |
|-------------------------------|---|-------------|--------------------------|-------------|----------------|------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|----------------|--------------|-----|------------|------|------|-----------|-----|------|---------|-----|-----|--------------------------|
| | | | | | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | SI | | AL | V2A | V4A |
| Spindle oil | --- | --- | ? | ? | 3/3 | 2/3 | (2) | (2) | 1/0 | 0/0 | (2) | 1/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/0 | (3) | (2) | 4/4 | 0/0 | (4) | 3/4 | 2/4 | 0/0 | |
| Spinning bath acid | --- | --- | 100mg CS ₂ /l | ? | 1/0 | 0/0 | 4/4 | (3) | 0/0 | 0/0 | 4/4 | 1/0 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/0 | (3) | (2) | 4/4 | 0/0 | (4) | 3/4 | 2/4 | 0/0 | |
| Spirit (of wine) | C ₂ H ₆ O | --- | --- | F | X | 1/0 | 1/3 | 1/0 | 1/3 | 1/1 | 1/2 | 1/2 | 1/1 | 3/4 | 1/2 | 1/3 | 3/0 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/0 | 3/3 | 0/0 | 1/1 | 1/1 | 1/1 | ethyl alcohol |
| Spirits | C ₂ H ₆ O | --- | --- | --- | --- | 1/1 | 1/0 | 1/0 | 1/1 | 1/1 | 0/0 | 1/2 | 1/1 | 0/0 | 1/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | ethyl alcohol 40 % |
| Spirits of Turpentine | --- | 008006-64-2 | --- | Xn | X | 2/2 | 3/4 | 1/0 | 4/4 | 1/0 | 3/3 | 1/1 | 4/4 | 4/4 | 2/3 | 4/4 | 3/3 | 1/1 | 1/1 | 1/0 | 1/3 | 4/4 | 1/1 | 3/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Spirits of wine | C ₂ H ₆ O | --- | 50 % | (F) | X | 1/0 | 1/1 | 1/0 | 1/1 | 1/1 | 1/0 | 1/2 | 1/1 | 1/0 | 1/0 | 1/0 | 3/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | (2) | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | ethyl alcohol |
| Spirits of wine | C ₂ H ₆ O | --- | 96 % | F | X | 1/0 | 1/3 | 1/0 | 1/3 | 1/1 | 1/2 | 1/2 | 1/1 | 3/4 | 1/2 | 1/3 | 3/0 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 3/0 | 3/3 | 0/0 | 1/1 | 1/1 | 1/1 | ethyl alcohol |
| Spruce oil | --- | 008008-80-8 | --- | ? | ? | 1/2 | 2/4 | (2) | 2/3 | 0/0 | 2/3 | (2) | 1/2 | 4/4 | 3/3 | 3/4 | 0/0 | 3/4 | 1/2 | 1/1 | (1) | (2) | 4/4 | 1/0 | 3/3 | 0/0 | (1) | (1) | (1) | pinus sylvestris |
| Stannic chloride | SnCl ₄ | 007646-78-8 | aqueous | C | 1/1 | 1/1 | 4/4 | (3) | 0/0 | 0/0 | (4) | 1/1 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | 4/4 | 4/4 | 3/4 | | |
| Stannous chloride | SnCl ₂ | 007772-99-8 | aqueous | (C, Xn) | --- | 1/1 | 1/1 | (4) | (2) | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | (2) | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 4/4 | 4/4 | 3/4 | 1/1 |
| Stannous chloride | SnCl ₂ | 007772-99-8 | saturated | C, Xn | --- | 1/1 | 1/1 | 4/4 | 1/0 | 0/0 | 0/0 | (2) | 1/1 | 1/1 | 0/0 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 4/4 | 4/4 | 3/4 | 1/1 |
| Starch solution | (C ₆ H ₁₀ O ₅) _n | --- | each | --- | --- | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 |
| Starch syrup | --- | --- | --- | --- | --- | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 0/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 |
| Stauffer grease, thick | --- | --- | --- | (-) | --- | 0/0 | 0/0 | (2) | (2) | (1) | 0/0 | (1) | (2) | 1/4 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | (1) | 4/4 | (1) | (2) | 0/0 | (1) | 1/1 | 1/1 | 0/0 |
| Steam | H ₂ O | --- | up to 150°C | ? | 4 | 4 | 4/4 | 0/0 | 0 | (3) | (3) | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 1 | 0 | 1 | 3 | 4/4 | 0 | (1) | 1/1 | 1/1 | |
| Stearic acid | C ₁₈ H ₃₆ O ₂ | 000057-11-4 | crystals | Xi | 1/3 | 1/3 | 1/0 | 1/2 | 1/0 | 1/1 | 1/0 | 1/3 | 1/2 | 2/2 | 1/2 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 3/0 | 1/1 | 3/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Strontium bromide | SrBr ₂ | 010476-81-0 | --- | Xi | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | (1) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | 1/1 | (1) | (1) | (1) | (2) | 0/0 | (3) | 0/0 | 0/0 | | |
| Strychnine | C ₂₁ H ₂₂ N ₂ O ₂ | 000057-24-9 | --- | T+ | 1/1 | 1/1 | (1) | (1) | (2) | 0/0 | (2) | (1) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | (2) | (2) | (2) | 0/0 | (2) | (1) | (1) | |
| Styrene | C ₈ H ₈ | 000100-42-5 | 100 % | Xn, Xi | X | 4/4 | 3/4 | 1/1 | 4/4 | 1/1 | (4) | 1/1 | 3/4 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 1/0 | 1/1 | (2) | 4/4 | 3/0 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 0/0 |
| Succinic acid | C ₄ H ₆ O ₄ | 000110-15-6 | 50 % | Xi | 1/1 | 1/1 | (3) | (2) | 0/0 | 0/0 | (3) | 1/1 | 0/0 | 0/0 | 2/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | (1) | 0/0 | 1/1 | 1/0 | 1/0 | 1/1 | | |
| Succinic acid | C ₄ H ₆ O ₄ | 000110-15-6 | saturated | Xi | 1/1 | 1/1 | (3) | (2) | 0/0 | 0/0 | (3) | 1/1 | 1/1 | 0/0 | 1/3 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/0 | 1/0 | ? | |
| Sugar acid | --- | --- | saturated | (Xi) | 1/1 | 1/1 | (3) | (2) | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | (1) | (1) | 0/0 | (3) | 0/0 | 0/0 | | |
| Sugar beet juice | --- | --- | --- | --- | --- | 1/1 | 1/1 | 1/0 | 1/0 | 0/0 | 1/0 | 1/1 | 1/1 | 1/0 | 0/0 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | (2) | (1) | (1) | | |
| Sugar syrup | --- | --- | --- | --- | --- | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/3 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | |
| Sulfur | S ₈ | 007704-34-9 | techn. pure | Xi | 1/1 | 1/1 | 1/0 | 1/0 | (2) | 0/0 | 1/0 | 1/1 | 1/1 | 0/0 | 3/0 | 3/4 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/1 | 4/4 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | flower of sulfur |
| Sulfur (mono)chloride | S ₂ Cl ₂ | 010025-67-9 | --- | C | 0/0 | 0/0 | 4/4 | (3) | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/0 | 1/1 | 1/0 | 4/4 | 1/0 | 4/4 | 0/0 | 3/4 | 1/1L | 1/1L | 0/0 | | |
| Sulfur dioxide | SO ₂ | 007446-09-5 | damp | T, C | 1/1 | 1/1 | (3) | (3) | 0/0 | 1/1 | 4/4 | 1/3 | 3/4 | 2/2 | 1/2 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/4 | 1/0 | 4/4 | 4/4 | 0/0 | 3/4 | 1/1 | 1/1 | 1/0 | with H2O->sulfurous acid |
| Sulfur dioxide | SO ₂ | 007446-09-5 | liquid | T, C | 3/4 | 4/4 | (3) | 3/4 | 0/0 | 4/4 | 4/4 | 4/4 | 4/4 | 2/2 | 3/4 | 0/0 | 0/0 | 1/2 | 1/1 | 1/1 | 4/4 | 1/0 | 4/4 | 4/4 | 0/0 | (3) | (1) | (1) | 1/0 | with H2O->sulfurous acid |
| Sulfur hexafluoride | SF ₆ | 002551-62-4 | --- | --- | 0/0 | 0/0 | 1/0 | (2) | 1/0 | 0/0 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/0 | 0/0 | 0/0 | (1) | (2) | 1/0 | 3/0 | 1/0 | 0/0 | (1) | (1) | (1) | | |
| Sulfur trioxide | SO ₃ | 007446-11-9 | --- | C+ | 4/4 | 4/4 | 4/4 | (4) | (4) | 0/0 | 4/4 | 4/4 | 0/0 | 4/4 | 0/0 | 0/0 | 0/0 | (2) | (2) | 3/4 | 3/0 | 1/0 | 4/4 | 0/0 | (3) | (1) | (1) | 0/0 | | |
| Sulfur, melted, 121 °C | S ₈ | 007704-34-9 | ? | ? | 0 | 0 | (4) | (3) | 0 | 4 | 4 | 4 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | (1) | 0 | 4 | 1 | 4 | 0 | (3) | 1 | 1 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 40 % | C+ | 1/1 | 1/1 | 4/4 | 2/0 | (4) | 1/2 | 4/4 | 1/1 | 2/0 | 3/0 | 1/3 | 1/3 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (3) | 1/1 | 4/4 | 0/0 | 3/4 | 2/3 | 2/3 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 60 % | C+ | 1/3 | 1/3 | 4/4 | 3/3 | (4) | 1/2 | 4/4 | 1/3 | 2/4 | 1/1 | 1/2 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 1/1 | 4/4 | 0/0 | 4/4 | 4/4 | 3/4 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 80 % | C+ | 1/1 | 1/1 | 4/4 | 3/4 | 4/4 | 1/2 | 4/4 | 1/1 | 3/4 | 3/0 | 1/1 | 1/3 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 1/1 | 4/4 | 0/0 | 4/4 | 2/4 | 2/3 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 95 % | C+ | 3/4 | 3/4 | 4/4 | 4/4 | 2/2 | 4/4 | 3/4 | 4/4 | 4/4 | 2/4 | 0/0 | 4/4 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 4/4 | 1/1 | 4/4 | 0/0 | 4/4 | 1/3 | 1/3 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | fuming | C+ | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 0/0 | (1) | 1/0 | 4/4 | 4/4 | 1/0 | 4/4 | 0/0 | (3) | 1/2 | 1/1 | 0/0 | oleum |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 1-6 % | Xi | 1/1 | 1/1 | 4/4 | 1/1 | 0/0 | 1/1 | 4/4 | 1/1 | 1/2 | 1/1 | 1/2 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 3/0 | 0/0 | (3) | 2/2 | 1/2 | 0/0 | |
| Sulfuric acid | H ₂ SO ₄ | 007664-93-9 | 20 % | Xi | 1/1 | 1/1 | 4/4 | 1/2 | 0/0 | 1/2 | 4/4 | 1/2 | 1/2 | 1/1 | 1/2 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 2/0 | 1/1 | 4/4 | 0/0 | (3) | 2/3 | 2/3 | | |
| Sulfuric acid | -> see: Battery acid | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Sulfurous acid | H ₂ SO ₃ | 007782-99-2 | saturated | (C) | 1/1 | 1/1 | 4/4 | 4/4 | 1/0 | 0/0 | 4/4 | 1/1 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 3/0 | (3) | 3/4 | 0/0 | 3/4 | 1/1 | 1/1 | 1/1 | |
| Sulfurous acid, disodium salt | -> see: Sodium sulfite | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| Sulfuryl chloride | Cl ₂ SO ₂ | 007791-25-5 | techn. pure | C | 4/4 | 4/4 | 4/4 | 1/0 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 4/4 | 4/4 | 0/0 | 0/0 | 0/0 | 1/0 | 3/0 | 3/0 | 1/0 | 4/4 | 0/0 | 3/4 | 0/0 | 0/0 | | |
| Tallow | --- | --- | techn. pure | --- | 1/1 | 1/1 | 1/0 | (1) | 1/0 | 0/0 | 1/0 | 1/1 | 0/0 | 0/0 | 1/1 | 1/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 3/0 | 1/1 | 1/1 | 0/0 | (1) | 1/1 | 1/1 | 0/0 | |
| Tannic acid | C ₁₂ H ₁₀ O ₄₈ | 001401-55-4 | 10 % | Xi | 1/1 | | | | | | | | | | | | | | | | | | | | | | | | | |

| CHEMICALS | FORMULA | CAS-NR. | CONCENTRATION | HAZARD NOTE | thermoplastics | | | | | | | | | | | | | fluoroplastics | | | elastomers | | | metals | | COMMENT | | | | |
|-----------------------|--|-------------|---------------|-------------|----------------|------|------|-----|-----|------|-----|-----|-----|-----|-----|----------|-----------|----------------|--------------|-----|------------|------|------|-----------|-----|---------|------|------|--|--|
| | | | | | FLAMMABLE | HDPE | LDPE | PA | PC | PETG | PMP | POM | PP | PS | PSU | PVC HART | PVC WEICH | SAN | ECTFE / ETFE | FEP | PTFE | PVDF | EPDM | FPM / FKM | NBR | | SI | AL | V2A | V4A |
| Wines | — | — | — | — | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 1/0 | 2/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/0 | 0/0 | (4) | 1/1 | 1/1 | 1/1 | | |
| Wort for fermentation | — | — | — | ? | 1/1 | 1/1 | (2) | (2) | (1) | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | (2) | (1) | 1/0 | 4/4 | 0/0 | (2) | (1) | (1) | 0/0 | |
| Xenon | Xe | 007440-63-3 | — | — | 0/0 | 0/0 | 1/0 | (1) | 1/1 | 0/0 | 1/1 | (2) | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | | | |
| Xylene | C ₈ H ₁₀ | 001330-20-7 | — | (F), Xn X | 3/4 | 3/4 | 1/0 | 4/4 | 0/0 | 3/4 | 1/2 | 4/4 | 4/4 | 4/4 | 4/4 | 4/4 | 1/2 | 1/1 | 1/0 | 1/3 | 4/4 | 1/3 | 4/4 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | | |
| Yeast | — | — | each | — | 1/1 | 1/1 | 1/0 | (1) | 1/0 | 0/0 | 1/1 | 1/1 | 0/0 | 0/0 | 1/0 | 1/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | (1) | (1) | | |
| Zinc acetate | C ₄ H ₆ ZnO ₄ | 000557-34-6 | aqueous | Xn, Xi | 1/1 | 1/1 | (2) | (2) | (2) | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | (1) | 1/0 | (3) | 3/3 | 0/0 | (3) | (1) | (1) | | | |
| Zinc bromide | ZnBr ₂ | 007699-45-8 | — | C, Xn | 1/1 | 1/1 | 4/4 | (2) | 0/0 | 0/0 | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 1/1 | (1) | (2) | (1) | (2) | 0/0 | (3) | 0/0 | 0/0 | | | |
| Zinc carbonate | ZnCO ₃ | 003486-35-9 | saturated | ? | 1/1 | 1/1 | (1) | 1/1 | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | small solubility - no chemical effect expected | |
| Zinc chloride | ZnCl ₂ | 007646-85-7 | aqueous | (C, Xn) | 1/1 | 1/1 | 3/4 | (2) | 0/0 | 0/0 | 2/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/1 | 0/0 | 3/4 | 1/4L | 1/3L | 1/1 | | |
| Zinc nitrate | Zn(NO ₃) ₂ | 007779-88-6 | — | O, C, Xn | 1/1 | 1/1 | 1/4 | (2) | 0/0 | 0/0 | (2) | 1/1 | 1/0 | 1/0 | 1/0 | 1/0 | 1/1 | 0/0 | 1/1 | (1) | 1/0 | (1) | (2) | 0/0 | (3) | (1) | (1) | 0/0 | | |
| Zinc oxide | ZnO | 001314-13-2 | solid | Xn, Xi | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (2) | 1/1 | 1/1 | | small solubility - no chemical effect expected |
| Zinc oxide ointment | — | — | — | ? | 0/0 | 0/0 | (1) | (2) | (2) | 0/0 | (2) | (2) | 1/1 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | (1) | 1/1 | (2) | (4) | (2) | (2) | 0/0 | (2) | (1) | (1) | | |
| Zinc phosphate | Zn ₃ (PO ₄) ₂ | 007779-90-0 | saturated | ? | 1/1 | 1/1 | (1) | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (2) | (1) | (1) | 0/0 | | |
| Zinc sludge | — | — | — | ? | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 1/1 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | 0/0 | (1) | (2) | 0/0 | 0/0 | 0/0 | (3) | 0/0 | 0/0 | | | | |
| Zinc stearate | C ₃₆ H ₇₀ ZnO ₄ | 000557-05-1 | — | Xi | 1/1 | 1/1 | (1) | 1/1 | 0/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/2 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | (2) | 1/1 | (2) | 0/0 | (2) | (1) | (1) | | | |
| Zinc sulfate | ZnSO ₄ | 007733-02-0 | 10 % | — | 1/1 | 1/1 | (3) | 1/0 | (2) | 1/0 | 2/0 | 1/1 | 1/1 | 0/0 | 1/1 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 1/0 | 0/0 | 3/4 | 1/1 | 1/1 | | |
| Zinkchlorid | ZnCl ₂ | 007646-85-7 | 10 % | C, Xn | 1/1 | 1/1 | 3/4 | 1/0 | 0/0 | 1/1 | 2/0 | 1/1 | 1/3 | 0/0 | 1/3 | 1/0 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/1 | 1/0 | 1/1 | 0/0 | 3/4 | 1/4L | 1/3L | 1/1 | |

Chemical resistance

Two values are given per substance
left number = value at +20°C / right number = value at +50°C.

| | |
|------------|--|
| 0 | no data available |
| 1 | resistant |
| 2 | practically resistant |
| 3 | partially resistant |
| 4 | not resistant |
| K | no general information available |
| L | danger of pitting or stress-cracking corrosion |
| () | estimated value |

Hazard notes

| | |
|-----------|-------------------------------|
| E | explosive |
| O | oxidizing |
| F | highly flammable |
| F+ | extremely flammable |
| T | toxic |
| T+ | very toxic |
| C | corrosive |
| Xn | harmful |
| Xi | irritant |
| N | dangerous for the environment |

Description of the materials

Thermoplastics

| | |
|-------------|---|
| HDPE | Polyethylene (high density) |
| LDPE | Polyethylene (low density) |
| PA | Polyamide (Nylon) |
| PC | Polycarbonate |
| PETG | Polyethylene terephthalate glycol (PET copolymer) |
| PMP | Polymethylpentene (TPX) |
| POM | Polyoxymethylene, polyacetal |
| PP | Polypropylene |
| PS | Polystyrene |
| PSU | Polysulfone |
| PVC | Polyvinyl chloride |
| SAN | Styrene-acrylonitrile |

Fluoroplastics

| | |
|---------------|--|
| E-CTFE | Ethylene-chlorotrifluoroethylene (Halar) |
| ETFE | Ethylene-tetrafluoroethylene |
| FEP | Tetrafluoroethylene-perfluoropropylene (Teflon, FEP) |
| PTFE | Polytetrafluoroethylene (Teflon) |
| PVDF | Polyvinylidene fluoride |

Elastomers

| | |
|----------------|---------------------------------|
| EPDM | Ethylene-propylene-diene rubber |
| FPM/FKM | Fluorinated rubber (Viton) |
| NBR | Acryl-nitrile-butadiene rubber |
| SI | Silicone rubber |

Metals

| | |
|--------------------|-----------------------------------|
| Al | Aluminium |
| V2A | Stainless steel 1.4301 (AISI 304) |
| V4A | Stainless steel 1.4401 (AISI 316) |
| Hastelloy C | Nickel-chromium-molybdenum alloy |